



ZEUS[®]

POLYMER EXTRUSIONS



CATALOG 11



CATALOG 11



Table of Contents

TABLE OF CONTENTS

| | | | |
|---|-----------|--|-----------|
| Applications | 3 | Peek Insulated Wire | 42 |
| Medical | 4 | Special Shapes - Multi-Lumen. | 43 |
| Industrial. | 5 | Performance Fiber | 44 |
| Extruded Sizes | 7 | Lay Flat Tubing®. | 45 |
| Extruded Tubing (AWG). | 9 | Dual Tube®. | 46 |
| Heavy Construction Tubing. | 13 | Splines - Wires, Cables, Coaxial Cores. | 47 |
| Heavy Wall Tubing | 14 | Snaptube® | 47 |
| Monofilament | 15 | Absorv™ | 48 |
| Convoluted Tubing | | Aeos® ePTFE Tubing and Monofilament. | 49 |
| PTFE | 16 | Value Added Services | 51 |
| FEP. | 17 | Benefits of ZEUS Value Added Services and Operations. | 53 |
| ETFE | 18 | Bump/Draw-down | 53 |
| Spiral-Cut Cable Wrap | 19 | Custom-Cutting | 54 |
| Extruded Metric Tubing | | Custom Packaging & Labeling | 54 |
| 0.50mm Wall Tubing | 20 | Drilling. | 54 |
| Extruded Metric Tubing | | Etching. | 54 |
| 1.00mm Wall Tubing | 21 | Flaring and Flanging | 54 |
| Extruded Metric Tubing | | Heat Sealing | 55 |
| 1.50/2.00mm Wall Tubing | 22 | Heat Shrinking over Mandrels. | 55 |
| Heat Shrinkable Extrusions | 23 | Product Analysis & Enhancement | 55 |
| ZEUS Heat Shrink Fluoropolymer Tubing | 25 | Product Assembly - High Volume. | 56 |
| PTFE Heat Shrink 2 to 1 Shrink Ratio. | 26 | Product Assembly - Light. | 56 |
| PTFE Heat Shrink 4 to 1 Shrink Ratio | 30 | Retractable Coil Tubing. | 56 |
| FEP Heat Shrink 1.3 to 1 Shrink Ratio. | 31 | Scoring. | 57 |
| FEP Heat Shrink 1.6 to 1 Shrink Ratio. | 33 | Slitting | 57 |
| FEP Roll Covers | 34 | Striping | 57 |
| PTFE/FEP Dual-Shrink® Tubing | 35 | Thermosetting/Forming | 57 |
| Specialty Products | 37 | Tube Tipping | 57 |
| PTFE Sub-Lite-Wall® | | PTFE Slitting and Cuffing | 58 |
| Extruded & Heat Shrinkable Tubing | 38 | Technical Information | 59 |
| PEEK™ Tubing | 40 | Resin Properties. | 62 |
| PEEKshrink® | 41 | General Information. | 72 |
| | | Technical Notes | 75 |



ZEUS[®]

APPLICATIONS

APPLICATIONS





WWW.ZEUSINC.COM

Applications Medical

APPLICATIONS

As the leading supplier of fluoropolymer tubing in the medical device market, ZEUS is adapted to servicing a wide range of customer needs. We are experienced at working with all of the organizational elements of a medical device manufacturer. To assist these specialized requests we established a medical department within our sales force and staffed it with highly-trained and medical device oriented Technical Account Manager. ZEUS is a true pioneer of high performance plastics in this industry.



For the R&D engineer working on a new innovative product we offer quick turnaround, technical support, and free samples for prototyping. We work with production engineers to help improve yields and throughput. Regulatory specialists appreciate our quality systems and USP Class VI certified polymers. Purchasing



agents appreciate our stocking programs and the level of service and delivery we offer the industry. We offer a true cross functional relationship to our customers.

On the materials side, we offer a wide range of fluoropolymers and specialized plastics with a history of success in medical device applications. Many of our extruded, heat shrink, and multi-lumen tubes have been chosen for their pure, smooth, non-toxic, non-allergenic properties, as well as their compatibility with human tissues and fluids.



Most of what we manufacture for the medical device industry is extremely tight toleranced tubing. With our staff of skilled polymer experts and 45+ years of extrusion experience we are experts at customizing the properties of our polymers through process and material modification technologies.



WWW.ZEUSINC.COM

Applications Industrial

APPLICATIONS

With more than 438,000+ sq ft. of manufacturing space ZEUS is ready to meet the challenges of the industrial markets. We have a strong working knowledge of a multitude of industries, including: automotive, chemical processing, electronic, aerospace and defense, fiber optics, environmental and analytical. We understand that new products and material enhancements are critical for our customers to remain competitive and successful. ZEUS offers a wide variety of standard and specialized products to meet your needs. ZEUS' knowledgeable Technical Account Managers are standing by to help you design the product you need.



High purity resins are used to extrude tubing with the lowest levels of extractables and the smoothest surface finish for use in semiconductor and pharmaceutical applications. FEP Lined Polyethylene tubing for environmental applications and PEEK™ tubing for analytical applications are a few of the specialty markets served. FEP, PFA and MFA tubing support applications ranging from laboratory plumbing, food processing and adhesive transfer systems to fuel, paint and hydraulic lines.



Increasing barrier properties creates tubing with the lowest water vapor transmission rates of any plastic. This is an example of the advances ZEUS has made to remain a leader in highly engineered extrusions. As new applications develop the need for our exceptional polymer product line increases significantly.



Fluid Handling

The demand for fluoropolymer tubing in fluid applications continues to increase as requirements become more specific. With ID from .002" up to 2.0", ZEUS' line of chemically resistant extrusions withstands corrosive fluids like sulfuric acid, hydrocarbon fuels and strong mineral acids.



WWW.ZEUSINC.COM

Applications Industrial


APPLICATIONS

Electrical/Mechanical

ZEUS has the broadest product line of fluoropolymer tubing used for applications demanding unsurpassed



mechanical properties. The low friction, light weight and high temperature characteristics of fluoropolymer tubing are applied in applications where other plastics would fail. ZEUS tubing has met or exceeded the critical environments in aviation programs worldwide. Some of



these products include AWG tubing and heat shrinkable tubing for insulation, in addition to spiral cut cable wrap and convoluted tubing for

wire harnesses and cable assemblies.

A few examples of the wide array of electrical applications includes microware

cable insulation featuring extrusions directly over wire, connector and terminal sleeves, fiber optic cable jacketing, hermetic motor insulation and battery pack and capacitor encapsulation.

Mechanical applications are not limited to the industry standard materials. Chemical modifiers are used for enhanced push-pull cable jacketing, wafer thin bushings, watertight encapsulation,

greaseless bearings, tire valve seals and chafe guards. To extend the life of many



components, ZEUS also supplies a wide range of heat shrinkable extrusions that have become an effective means of applying a tight jacketing that stands up to the hostile environments of heat, abrasion and shock.



ZEUS[®]



**EXTRUDED
SIZES**



EXTRUDED SIZES



WWW.ZEUSINC.COM

PTFE, FEP, PFA, ETFE

Extruded Tubing

EXTRUDED SIZES

Dimensions (Inches)



| AWG Size | INSIDE DIAMETER | | | WALL DIMENSIONS | | | | | |
|----------|-----------------|-------|-------|--------------------|--------------------|----------------|----------------|-----------------------|-----------------------|
| | Min. | Nom. | Max. | Standard Wall Nom. | Standard Wall Tol. | Thin Wall Nom. | Thin Wall Tol. | Lightweight Wall Nom. | Lightweight Wall Tol. |
| *32 | 0.008 | 0.010 | 0.012 | 0.005 | ±.002 | 0.005 | ±.002 | - | - |
| 30 | 0.010 | 0.012 | 0.015 | 0.009 | ±.002 | 0.009 | ±.002 | 0.006 | ±.002 |
| 28 | 0.013 | 0.015 | 0.018 | 0.009 | ±.002 | 0.009 | ±.002 | 0.006 | ±.002 |
| 26 | 0.016 | 0.018 | 0.021 | 0.009 | ±.002 | 0.009 | ±.002 | 0.006 | ±.002 |
| 24 | 0.020 | 0.022 | 0.026 | 0.012 | ±.002 | 0.010 | ±.003 | 0.006 | ±.002 |
| *23 | 0.023 | 0.026 | 0.029 | 0.012 | ±.002 | 0.010 | ±.003 | 0.006 | ±.002 |
| 22 | 0.025 | 0.028 | 0.032 | 0.012 | ±.002 | 0.010 | ±.003 | 0.006 | ±.002 |
| *21 | 0.029 | 0.032 | 0.035 | 0.012 | ±.002 | 0.010 | ±.003 | 0.006 | ±.002 |
| 20 | 0.032 | 0.034 | 0.038 | 0.016 | ±.003 | 0.012 | ±.003 | 0.006 | ±.002 |
| 19 | 0.036 | 0.038 | 0.042 | 0.016 | ±.003 | 0.012 | ±.003 | 0.006 | ±.002 |
| 18 | 0.040 | 0.042 | 0.046 | 0.016 | ±.003 | 0.012 | ±.003 | 0.006 | ±.002 |
| 17 | 0.045 | 0.047 | 0.052 | 0.016 | ±.003 | 0.012 | ±.003 | 0.006 | ±.002 |
| 16 | 0.051 | 0.053 | 0.058 | 0.016 | ±.003 | 0.012 | ±.003 | 0.006 | ±.002 |
| 15 | 0.057 | 0.059 | 0.065 | 0.016 | ±.003 | 0.012 | ±.003 | 0.006 | ±.002 |
| 14 | 0.064 | 0.066 | 0.072 | 0.016 | ±.003 | 0.012 | ±.003 | 0.008 | ±.002 |
| 13 | 0.072 | 0.076 | 0.081 | 0.016 | ±.003 | 0.012 | ±.003 | 0.008 | ±.002 |
| 12 | 0.081 | 0.085 | 0.091 | 0.016 | ±.003 | 0.012 | ±.003 | 0.008 | ±.002 |
| 11 | 0.091 | 0.095 | 0.101 | 0.016 | ±.003 | 0.012 | ±.003 | 0.008 | ±.002 |
| 10 | 0.102 | 0.106 | 0.112 | 0.016 | ±.003 | 0.012 | ±.003 | 0.008 | ±.002 |
| 9 | 0.114 | 0.118 | 0.124 | 0.020 | ±.004 | 0.015 | ±.003 | 0.008 | ±.002 |
| 8 | 0.129 | 0.133 | 0.139 | 0.020 | ±.004 | 0.015 | ±.003 | 0.008 | ±.002 |
| 7 | 0.144 | 0.148 | 0.155 | 0.020 | ±.004 | 0.015 | ±.003 | 0.008 | ±.002 |
| 6 | 0.162 | 0.166 | 0.174 | 0.020 | ±.004 | 0.015 | ±.003 | 0.010 | ±.003 |
| 5 | 0.182 | 0.186 | 0.195 | 0.020 | ±.004 | 0.015 | ±.003 | 0.010 | ±.003 |
| 4 | 0.204 | 0.208 | 0.218 | 0.020 | ±.004 | 0.015 | ±.003 | 0.010 | ±.003 |
| 3 | 0.229 | 0.234 | 0.244 | 0.020 | ±.004 | 0.015 | ±.003 | 0.010 | ±.003 |
| 2 | 0.258 | 0.263 | 0.273 | 0.020 | ±.004 | 0.015 | ±.003 | 0.010 | ±.003 |
| 1 | 0.289 | 0.294 | 0.305 | 0.020 | ±.004 | 0.015 | ±.003 | 0.010 | ±.003 |
| 0 | 0.325 | 0.330 | 0.342 | 0.020 | ±.004 | 0.015 | ±.003 | 0.012 | ±.003 |

Material and dimensions comply with ASTM 3295, 3296; AMS 3653, 3654, 3655 and MIL-I-22129. Lot to lot testing available upon request.

*AWG 32, AWG 23 & AWG 21 not covered under ASTM 3295 or MIL standards.

On all cases of military or commercial specifications, latest revisions apply. Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request.

ZEUS' TUBING complies with UL-224, has been assigned UL FILE NO. E-64007, and is listed under the UL "RECOGNIZED COMPONENT PROGRAM". (CSA-OPT) File # 082582 has been awarded for PTFE.



PTFE, FEP, PFA, ETFE Extruded Tubing

EXTRUDED SIZES

Metric Dimensions (mm)



| AWG Size | INSIDE DIAMETER | | | WALL DIMENSIONS | | | | | |
|----------|-----------------|------|------|-----------------|------|-----------|------|------------------|------|
| | Min. | Nom. | Max. | Standard Wall | | Thin Wall | | Lightweight Wall | |
| | | | | Nom. | Tol. | Nom. | Tol. | Nom. | Tol. |
| *32 | 0.20 | 0.25 | 0.30 | 0.13 | ±.05 | 0.13 | ±.05 | – | – |
| 30 | 0.25 | 0.30 | 0.38 | 0.23 | ±.05 | 0.23 | ±.05 | 0.15 | ±.05 |
| 28 | 0.33 | 0.38 | 0.46 | 0.23 | ±.05 | 0.23 | ±.05 | 0.15 | ±.05 |
| 26 | 0.41 | 0.46 | 0.53 | 0.23 | ±.05 | 0.23 | ±.05 | 0.15 | ±.05 |
| 24 | 0.51 | 0.56 | 0.66 | 0.30 | ±.05 | 0.25 | ±.08 | 0.15 | ±.05 |
| *23 | 0.58 | 0.66 | 0.74 | 0.30 | ±.05 | 0.25 | ±.08 | 0.15 | ±.05 |
| 22 | 0.64 | 0.71 | 0.81 | 0.30 | ±.05 | 0.25 | ±.08 | 0.15 | ±.05 |
| *21 | 0.74 | 0.81 | 0.89 | 0.30 | ±.05 | 0.25 | ±.08 | 0.15 | ±.05 |
| 20 | 0.81 | 0.86 | 0.97 | 0.41 | ±.08 | 0.30 | ±.08 | 0.15 | ±.05 |
| 19 | 0.91 | 0.97 | 1.07 | 0.41 | ±.08 | 0.30 | ±.08 | 0.15 | ±.05 |
| 18 | 1.02 | 1.07 | 1.17 | 0.41 | ±.08 | 0.30 | ±.08 | 0.15 | ±.05 |
| 17 | 1.14 | 1.19 | 1.32 | 0.41 | ±.08 | 0.30 | ±.08 | 0.15 | ±.05 |
| 16 | 1.30 | 1.35 | 1.47 | 0.41 | ±.08 | 0.30 | ±.08 | 0.15 | ±.05 |
| 15 | 1.45 | 1.50 | 1.65 | 0.41 | ±.08 | 0.30 | ±.08 | 0.15 | ±.05 |
| 14 | 1.63 | 1.68 | 1.83 | 0.41 | ±.08 | 0.30 | ±.08 | 0.20 | ±.05 |
| 13 | 1.83 | 1.93 | 2.06 | 0.41 | ±.08 | 0.30 | ±.08 | 0.20 | ±.05 |
| 12 | 2.06 | 2.16 | 2.31 | 0.41 | ±.08 | 0.30 | ±.08 | 0.20 | ±.05 |
| 11 | 2.31 | 2.41 | 2.57 | 0.41 | ±.08 | 0.30 | ±.08 | 0.20 | ±.05 |
| 10 | 2.59 | 2.69 | 2.84 | 0.41 | ±.08 | 0.30 | ±.08 | 0.20 | ±.05 |
| 9 | 2.90 | 3.00 | 3.15 | 0.51 | ±.10 | 0.38 | ±.08 | 0.20 | ±.05 |
| 8 | 3.28 | 3.38 | 3.53 | 0.51 | ±.10 | 0.38 | ±.08 | 0.20 | ±.05 |
| 7 | 3.66 | 3.76 | 3.94 | 0.51 | ±.10 | 0.38 | ±.08 | 0.20 | ±.05 |
| 6 | 4.11 | 4.22 | 4.42 | 0.51 | ±.10 | 0.38 | ±.08 | 0.25 | ±.08 |
| 5 | 4.62 | 4.72 | 4.95 | 0.51 | ±.10 | 0.38 | ±.08 | 0.25 | ±.08 |
| 4 | 5.18 | 5.28 | 5.54 | 0.51 | ±.10 | 0.38 | ±.08 | 0.25 | ±.08 |
| 3 | 5.82 | 5.94 | 6.20 | 0.51 | ±.10 | 0.38 | ±.08 | 0.25 | ±.08 |
| 2 | 6.55 | 6.68 | 6.93 | 0.51 | ±.10 | 0.38 | ±.08 | 0.25 | ±.08 |
| 1 | 7.34 | 7.47 | 7.75 | 0.51 | ±.10 | 0.38 | ±.08 | 0.25 | ±.08 |
| 0 | 8.26 | 8.38 | 8.69 | 0.51 | ±.10 | 0.38 | ±.08 | 0.30 | ±.08 |

*Material and dimensions comply with ASTM 3295, 3296; AMS 3653, 3654, 3655 and MIL-I-22129. Lot to lot testing available upon request.

*AWG 32, AWG 23 & AWG 21 not covered under ASTM 3295 or MIL standards.

On all cases of military or commercial specifications, latest revisions apply. Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request.

ZEUS' TUBING complies with UL-224, has been assigned UL FILE NO. E-64007, and is listed under the UL "RECOGNIZED COMPONENT PROGRAM". (CSA-OPT) File # 082582 has been awarded for PTFE.



PTFE, FEP, PFA, ETFE

Extruded Tubing

EXTRUDED SIZES

Dimensions (Inches)



| INSIDE DIAMETER | | | | WALL DIMENSIONS | | | | | |
|--------------------------|-------|-------|-------|-----------------|-------|-----------|-------|------------------|-------|
| Frac. Sizes Spec'd by ID | Min. | Nom. | Max. | Standard Wall | | Thin Wall | | Lightweight Wall | |
| | | | | Nom. | Tol. | Nom. | Tol. | Nom. | Tol. |
| 1/8 | 0.120 | 0.125 | 0.130 | 0.020 | ±.004 | 0.015 | ±.003 | — | — |
| 1/8 | 0.125 | 0.130 | 0.135 | — | — | — | — | 0.008 | ±.002 |
| 3/16 | 0.188 | 0.192 | 0.198 | 0.020 | ±.004 | 0.015 | ±.003 | 0.010 | ±.003 |
| 1/4 | 0.250 | 0.255 | 0.260 | 0.020 | ±.004 | 0.015 | ±.003 | 0.010 | ±.003 |
| 5/16 | 0.313 | 0.321 | 0.332 | 0.020 | ±.004 | 0.015 | ±.003 | 0.012 | ±.003 |
| 3/8 | 0.375 | 0.387 | 0.394 | 0.025 | ±.005 | 0.015 | ±.003 | 0.015 | ±.005 |
| 7/16 | 0.438 | 0.451 | 0.458 | 0.025 | ±.005 | 0.018 | ±.004 | 0.018 | ±.005 |
| 1/2 | 0.500 | 0.515 | 0.520 | 0.025 | ±.005 | 0.018 | ±.004 | 0.018 | ±.005 |
| 5/8 | 0.625 | 0.643 | 0.650 | 0.025 | ±.005 | 0.020 | ±.004 | 0.020 | ±.005 |
| 3/4 | 0.750 | 0.772 | 0.775 | 0.030 | ±.006 | 0.025 | ±.005 | 0.020 | ±.005 |
| 7/8 | 0.875 | 0.902 | 0.927 | 0.035 | ±.007 | — | — | — | — |
| 1 | 1.000 | 1.030 | 1.060 | 0.035 | ±.007 | — | — | — | — |
| 1-1/4 | 1.250 | 1.287 | 1.325 | 0.040 | ±.007 | — | — | — | — |
| 1-1/2 | 1.500 | 1.550 | 1.580 | 0.045 | ±.007 | — | — | — | — |

Metric Dimensions (mm)

| INSIDE DIAMETER | | | | WALL DIMENSIONS | | | | | |
|--------------------------|-------|-------|-------|-----------------|------|-----------|------|------------------|------|
| Frac. Sizes Spec'd by ID | Min. | Nom. | Max. | Standard Wall | | Thin Wall | | Lightweight Wall | |
| | | | | Nom. | Tol. | Nom. | Tol. | Nom. | Tol. |
| 1/8 | 3.05 | 3.18 | 3.30 | 0.51 | ±.10 | 0.38 | ±.08 | — | — |
| 1/8 | 3.18 | 3.30 | 3.43 | — | — | — | — | 0.20 | ±.05 |
| 3/16 | 4.78 | 4.88 | 5.03 | 0.51 | ±.10 | 0.38 | ±.08 | 0.25 | ±.08 |
| 1/4 | 6.35 | 6.48 | 6.60 | 0.51 | ±.10 | 0.38 | ±.08 | 0.25 | ±.08 |
| 5/16 | 7.95 | 8.15 | 8.43 | 0.51 | ±.10 | 0.38 | ±.08 | 0.30 | ±.08 |
| 3/8 | 9.53 | 9.83 | 10.01 | 0.64 | ±.13 | 0.38 | ±.08 | 0.38 | ±.13 |
| 7/16 | 11.13 | 11.46 | 11.63 | 0.64 | ±.13 | 0.46 | ±.10 | 0.46 | ±.13 |
| 1/2 | 12.70 | 13.08 | 13.21 | 0.64 | ±.13 | 0.46 | ±.10 | 0.46 | ±.13 |
| 5/8 | 15.88 | 16.33 | 16.51 | 0.64 | ±.13 | 0.51 | ±.10 | 0.51 | ±.13 |
| 3/4 | 19.05 | 19.61 | 19.69 | 0.76 | ±.15 | 0.64 | ±.13 | 0.51 | ±.13 |
| 7/8 | 22.23 | 22.91 | 23.55 | 0.89 | ±.18 | — | — | — | — |
| 1 | 25.40 | 26.16 | 26.92 | 0.89 | ±.18 | — | — | — | — |
| 1-1/4 | 31.75 | 32.69 | 33.66 | 1.02 | ±.18 | — | — | — | — |
| 1-1/2 | 38.10 | 39.37 | 40.13 | 1.14 | ±.18 | — | — | — | — |



WWW.ZEUSINC.COM

PTFE, FEP, PFA, ETFE Extruded Tubing

EXTRUDED SIZES

Dimensions (Inches)



| INDUSTRIAL SPECIFICATION TUBING | | | |
|----------------------------------|------------|------------|-----------------|
| Frac. Sizes Spec'd by ID & OD | I.D. | O.D. | Nominal Wall |
| 1/32 | 0.031±.004 | 0.063±.004 | .015 |
| 1/16 | 0.063±.005 | 0.125±.005 | .030 |
| 3/32 | 0.094±.005 | 0.156±.005 | .030 |
| 1/8 | 0.125±.005 | 0.188±.005 | .030 |
| 3/16 | 0.188±.005 | 0.250±.005 | .030 |
| 1/4 | 0.250±.005 | 0.313±.005 | .030 |
| 5/16 | 0.313±.005 | 0.375±.005 | .030 |
| 3/8 | 0.375±.005 | 0.438±.005 | .030 |
| 7/16 | 0.438±.005 | 0.500±.006 | .030 |
| 1/2 | 0.500±.006 | 0.563±.006 | .030 |

| INDUSTRIAL SPECIFICATION TUBING | | | |
|----------------------------------|------------|------------|-----------------|
| Frac. Sizes Spec'd by ID & OD | I.D. | O.D. | Nominal Wall |
| 9/16 | 0.563±.006 | 0.625±.006 | .030 |
| 5/8 | 0.625±.006 | 0.688±.006 | .030 |
| 11/16 | 0.688±.006 | 0.750±.006 | .032 |
| 3/4 | 0.750±.006 | 0.830±.006 | .040 |
| 7/8 | 0.875±.006 | 0.965±.006 | .045 |
| 1 | 1.000±.010 | 1.10±.010 | .050 |
| 1-1/8 | 1.125±.015 | 1.215±.015 | .045 |
| 1-1/4 | 1.250±.015 | 1.340±.015 | .045 |
| 1-1/2 | 1.500±.015 | 1.580±.015 | .040 |

Metric Dimensions (mm)

| INDUSTRIAL SPECIFICATION TUBING | | | |
|----------------------------------|------------|------------|-----------------|
| Frac. Sizes Spec'd by ID & OD | I.D. | O.D. | Nominal Wall |
| 1/32 | 0.79±0.10 | 1.60±0.10 | .38 |
| 1/16 | 1.60±0.13 | 3.18±0.13 | .76 |
| 3/32 | 2.39±0.13 | 3.96±0.13 | .76 |
| 1/8 | 3.18±0.13 | 4.78±0.13 | .76 |
| 3/16 | 4.78±0.13 | 6.35±0.13 | .76 |
| 1/4 | 6.35±0.13 | 7.95±0.13 | .76 |
| 5/16 | 7.95±0.13 | 9.53±0.13 | .76 |
| 3/8 | 9.53±0.13 | 11.13±0.13 | .76 |
| 7/16 | 11.13±0.13 | 12.70±0.15 | .76 |
| 1/2 | 12.70±0.15 | 14.30±0.15 | .76 |

| INDUSTRIAL SPECIFICATION TUBING | | | |
|----------------------------------|------------|------------|-----------------|
| Frac. Sizes Spec'd by ID & OD | I.D. | O.D. | Nominal Wall |
| 9/16 | 14.30±0.15 | 15.88±0.15 | .76 |
| 5/8 | 15.88±0.15 | 17.48±0.15 | .76 |
| 11/16 | 17.48±0.15 | 19.05±0.15 | .81 |
| 3/4 | 19.05±0.15 | 21.08±0.15 | 1.02 |
| 7/8 | 22.23±0.15 | 24.51±0.15 | 1.14 |
| 1 | 25.40±0.25 | 27.94±0.25 | 1.27 |
| 1-1/8 | 28.58±0.38 | 30.86±0.38 | 1.14 |
| 1-1/4 | 31.75±0.38 | 34.04±0.38 | 1.14 |
| 1-1/2 | 38.10±0.38 | 40.13±0.38 | 1.02 |

"Material and dimensions comply with ASTM 3295, 3296; AMS 3653, 3654, 3655 and MIL-I-22129. Lot to lot testing available upon request."

On all cases of military or commercial specifications, latest revisions apply. Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request.

ZEUS' TUBING complies with UL-224, has been assigned UL FILE NO. E-64007, and is listed under the UL "RECOGNIZED COMPONENT PROGRAM". CSA File # 082582 has been awarded for PTFE.



PTFE, FEP, PFA, ETFE

Heavy Construction Tubing

EXTRUDED SIZES

Dimensions (Inches)



| Fractional Spec'd by OD | O.D. | I.D. | Nominal Wall Thickness |
|-------------------------|---------------|---------------|------------------------|
| 1/4 | 0.250+/- .005 | 0.125+/- .005 | 0.063 |
| 5/16 | 0.313+/- .005 | 0.188+/- .005 | 0.063 |
| 3/8 | 0.375+/- .005 | 0.250+/- .005 | 0.063 |
| 7/16 | 0.438+/- .005 | 0.313+/- .005 | 0.063 |
| 1/2 | 0.500+/- .006 | 0.375+/- .006 | 0.063 |
| 9/16 | 0.563+/- .006 | 0.438+/- .006 | 0.063 |
| 5/8 | 0.625+/- .006 | 0.500+/- .006 | 0.063 |
| 11/16 | 0.688+/- .006 | 0.563+/- .006 | 0.063 |
| 3/4 | 0.750+/- .006 | 0.625+/- .006 | 0.063 |
| 13/16 | 0.813+/- .006 | 0.688+/- .006 | 0.063 |
| 7/8 | 0.875+/- .006 | 0.750+/- .006 | 0.063 |
| 15/16 | 0.938+/- .006 | 0.813+/- .006 | 0.063 |
| 1 | 1.000+/- .010 | 0.875+/- .010 | 0.063 |

Metric Dimensions (mm)

| Fractional Spec'd by OD | O.D. | I.D. | Nominal Wall Thickness |
|-------------------------|--------------|--------------|------------------------|
| 1/4 | 6.35+/- .13 | 3.18+/- .13 | 1.60 |
| 5/16 | 7.92+/- .13 | 4.78+/- .13 | 1.60 |
| 3/8 | 9.52+/- .13 | 6.35+/- .13 | 1.60 |
| 7/16 | 11.13+/- .13 | 7.95+/- .13 | 1.60 |
| 1/2 | 12.70+/- .15 | 9.52+/- .15 | 1.60 |
| 9/16 | 14.30+/- .15 | 11.13+/- .15 | 1.60 |
| 5/8 | 15.88+/- .15 | 12.70+/- .15 | 1.60 |
| 11/16 | 17.48+/- .15 | 14.30+/- .15 | 1.60 |
| 3/4 | 19.05+/- .15 | 15.88+/- .15 | 1.60 |
| 13/16 | 20.65+/- .15 | 17.48+/- .15 | 1.60 |
| 7/8 | 22.23+/- .15 | 19.05+/- .15 | 1.60 |
| 15/16 | 23.83+/- .15 | 20.65+/- .15 | 1.60 |
| 1 | 25.40+/- .25 | 22.23+/- .25 | 1.60 |



WWW.ZEUSINC.COM

PTFE, FEP, PFA, ETFE

Heavy Wall Tubing

EXTRUDED SIZES

Dimensions (Inches)



| AWG | INSIDE DIAMETER | | | WALL DIMENSIONS | |
|-----|-----------------|------------|------------|-----------------|-----------|
| | ID Minimum | ID Nominal | ID Maximum | Wall Nominal | Tolerance |
| 24 | .020 | .022 | .026 | .016 | +/- .003 |
| *23 | .024 | .027 | .030 | .016 | +/- .003 |
| 22 | .025 | .0285 | .032 | .016 | +/- .003 |
| *21 | .030 | .033 | .036 | .016 | +/- .003 |
| 20 | .032 | .036 | .040 | .018 | +/- .003 |
| 19 | .036 | .040 | .044 | .020 | +/- .004 |
| 18 | .040 | .0445 | .049 | .020 | +/- .004 |
| 17 | .045 | .0495 | .054 | .020 | +/- .004 |
| 16 | .051 | .056 | .061 | .020 | +/- .004 |
| 15 | .057 | .062 | .067 | .020 | +/- .004 |
| 14 | .064 | .069 | .074 | .020 | +/- .004 |
| 13 | .072 | .077 | .082 | .020 | +/- .004 |
| 12 | .081 | .086 | .091 | .020 | +/- .004 |
| 11 | .091 | .096 | .101 | .020 | +/- .004 |
| 10 | .102 | .107 | .112 | .025 | +/- .005 |
| 9 | .114 | .119 | .124 | .025 | +/- .005 |
| 8 | .129 | .135 | .141 | .030 | +/- .005 |
| 7 | .144 | .151 | .158 | .030 | +/- .005 |
| 6 | .162 | .17 | .178 | .030 | +/- .005 |
| 5 | .182 | .19 | .198 | .032 | +/- .005 |

*AWG 23 & AWG 21 not covered under ASTM 3295 -Class 5.

| Fractional Spec'd by ID/OD | O.D. | I.D. | Nominal Wall Thickness |
|----------------------------|---------------|---------------|------------------------|
| 5/32* | 0.250+/- .005 | 0.156+/- .005 | 0.047 |

* This product is specified as HW and dimensionally manufactured to ID/OD



WWW.ZEUSINC.COM

PTFE Monofilament

EXTRUDED SIZES

Dimensions (Inches)

| Ordered As Diameter | Tolerances |
|---------------------|------------|
| 0.028 | ±.002 |
| 0.031 | ±.002 |
| 0.035 | ±.002 |
| 0.039 | ±.002 |
| 0.047 | ±.002 |
| 0.050 | ±.002 |
| 0.055 | ±.002 |
| 0.062 | ±.002 |
| 0.070 | ±.002 |
| 0.078 | ±.003 |
| 0.094 | ±.003 |
| 0.100 | ±.003 |
| 0.109 | ±.003 |
| 0.125 | ±.003 |
| 0.150 | ±.003 |

Metric Dimensions (mm)

| Ordered As Diameter | Tolerances |
|---------------------|------------|
| 0.71 | ±.05 |
| 0.79 | ±.05 |
| 0.89 | ±.05 |
| 0.99 | ±.05 |
| 1.19 | ±.05 |
| 1.27 | ±.05 |
| 1.40 | ±.05 |
| 1.57 | ±.05 |
| 1.78 | ±.05 |
| 1.98 | ±.08 |
| 2.39 | ±.08 |
| 2.54 | ±.08 |
| 2.77 | ±.08 |
| 3.17 | ±.08 |
| 3.81 | ±.08 |



Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request. Material and dimensions comply with ASTM 3295. Lot to lot testing available upon request.
ASTM-D-3295 (Group 05)



WWW.ZEUSINC.COM

Convoluted Tubing

PTFE

SPECIALTY PRODUCTS



Standard Flex Convoluted

| Part Number | Military Spec. | Identifier | Max I.D. | Min I.D. | Max O.D. | Max. Wall Thick | Conv/Inch +/-1" | Weight (LBS) Per CFT Maximum | Min. Bend Radius |
|-------------|----------------|------------|----------|----------|----------|-----------------|-----------------|------------------------------|------------------|
| ZCT-TS-012 | AS81914/1 | **01 | 0.188 | 0.181 | 0.32 | 0.023 | 8 | 2.0 | 0.500 |
| ZCT-TS-018 | AS81914/1 | **02 | 0.281 | 0.273 | 0.414 | 0.027 | 7 1/2 | 2.9 | 0.750 |
| ZCT-TS-020 | AS81914/1 | **03 | 0.312 | 0.303 | 0.45 | 0.027 | 7 1/2 | 3.6 | 0.875 |
| ZCT-TS-024 | AS81914/1 | **04 | 0.375 | 0.364 | 0.53 | 0.029 | 7 | 4.2 | 1.000 |
| ZCT-TS-028 | AS81914/1 | **05 | 0.437 | 0.425 | 0.59 | 0.029 | 7 | 4.9 | 1.250 |
| ZCT-TS-032 | AS81914/1 | **06 | 0.500 | 0.485 | 0.66 | 0.029 | 7 | 5.2 | 1.500 |
| ZCT-TS-040 | AS81914/1 | **07 | 0.625 | 0.608 | 0.78 | 0.035 | 7 | 6.9 | 1.750 |
| ZCT-TS-048 | AS81914/1 | **08 | 0.750 | 0.730 | 0.975 | 0.035 | 6 | 10.4 | 1.875 |
| ZCT-TS-056 | AS81914/1 | **09 | 0.875 | 0.850 | 1.10 | 0.035 | 6 | 11.3 | 2.250 |
| ZCT-TS-064 | AS81914/1 | **10 | 1.000 | 0.975 | 1.26 | 0.035 | 4 1/2 | 12.6 | 2.500 |
| ZCT-TS-072 | AS81914/1 | **11 | 1.125 | 1.105 | 1.39 | 0.035 | 4 1/2 | 13.8 | 2.750 |
| ZCT-TS-080 | AS81914/1 | **12 | 1.250 | 1.210 | 1.539 | 0.035 | 4 | 15.5 | 3.000 |
| ZCT-TS-096* | AS81914/1 | **13 | 1.500 | 1.440 | 1.85 | 0.040 | 4 | 21.7 | 3.750 |

The table above details ZEUS and AMS-Spec. numbers and dimensions for our standard PTFE convoluted tubing. Custom sizes and configurations are also available.

Extra Flex Convoluted

| Part Number | Military Spec. | Identifier | Max I.D. | Min I.D. | Max O.D. | Max. Wall Thick | Conv/Inch +/-1 | Weight (LBS) Per CFT Maximum | Min. Bend Radius |
|-------------|----------------|------------|----------|----------|----------|-----------------|----------------|------------------------------|------------------|
| ZCT-TE-012 | AS81914/2 | **01 | 0.188 | 0.181 | 0.32 | 0.023 | 10 | 2.2 | 0.313 |
| ZCT-TE-018 | AS81914/2 | **02 | 0.281 | 0.273 | 0.414 | 0.026 | 9 | 3.8 | 0.438 |
| ZCT-TE-020 | AS81914/2 | **03 | 0.312 | 0.306 | 0.450 | 0.027 | 9 | 4.8 | 0.438 |
| ZCT-TE-024 | AS81914/2 | **04 | 0.375 | 0.364 | 0.530 | 0.029 | 9 | 5.6 | 0.500 |
| ZCT-TE-028 | AS81914/2 | **05 | 0.437 | 0.427 | 0.590 | 0.029 | 9 | 6.5 | 0.500 |
| ZCT-TE-032 | AS81914/2 | **06 | 0.500 | 0.485 | 0.660 | 0.029 | 9 | 6.9 | 0.750 |
| ZCT-TE-040 | AS81914/2 | **07 | 0.625 | 0.608 | 0.780 | 0.035 | 9 | 9.2 | 0.750 |
| ZCT-TE-048 | AS81914/2 | **08 | 0.750 | 0.730 | 0.975 | 0.035 | 8 | 13.8 | 0.938 |
| ZCT-TE-056 | AS81914/2 | **09 | 0.875 | 0.860 | 1.100 | 0.035 | 8 | 15 | 0.938 |
| ZCT-TE-064 | AS81914/2 | **10 | 1.000 | 0.975 | 1.260 | 0.035 | 7 | 16.8 | 1.125 |
| ZCT-TE-072 | AS81914/2 | **11 | 1.125 | 1.105 | 1.390 | 0.035 | 6 | 17.5 | 1.125 |
| ZCT-TE-080 | AS81914/2 | **12 | 1.250 | 1.210 | 1.539 | 0.035 | 6 | 19.6 | 1.250 |
| ZCT-TE-096* | AS81914/2 | **13 | 1.500 | 1.450 | 1.810 | 0.038 | 6 | 26 | 2.000 |

The table above details ZEUS and AMS-Spec. numbers and dimensions for our Extra-Flex PTFE convoluted tubing. Custom sizes and configurations are also available.* Material and Dimensions comply with AS81914. Lot to lot testing available upon request.



WWW.ZEUSINC.COM

Convoluted Tubing

FEP

SPECIALTY PRODUCTS

Custom Sizes Available

Standard Convoluted

| Part Number | Military Spec. | Identifier | Max I.D. | Min I.D. | Max O.D. | Max. Wall Thick | Conv/Inch +/-1" | Weight (LBS) Per CFT Maximum | Min. Bend Radius |
|-------------|----------------|------------|----------|----------|----------|-----------------|-----------------|------------------------------|------------------|
| ZCT-FS-012 | AS81914/3 | **01 | .188 | .181 | .320 | .018 | 8 | 1.5 | .500 |
| ZCT-FS-018 | AS81914/3 | **02 | .281 | .273 | .414 | .018 | 8 | 1.7 | .750 |
| ZCT-FS-020 | AS81914/3 | **03 | .312 | .306 | .450 | .018 | 8 | 1.9 | .750 |
| ZCT-FS-024 | AS81914/3 | **04 | .375 | .364 | .510 | .018 | 8 | 2.2 | .875 |
| ZCT-FS-028 | AS81914/3 | **05 | .437 | .427 | .571 | .018 | 8 | 3.1 | .875 |
| ZCT-FS-032 | AS81914/3 | **06 | .500 | .485 | .650 | .023 | 7 | 4.0 | 1.250 |
| ZCT-FS-040 | AS81914/3 | **07 | .625 | .608 | .770 | .023 | 7 | 4.8 | 1.500 |
| ZCT-FS-048 | AS81914/3 | **08 | .750 | .730 | .930 | .023 | 6 | 6.1 | 1.750 |
| ZCT-FS-056 | AS81914/3 | **09 | .875 | .860 | 1.073 | .023 | 5 | 7.0 | 2.000 |
| ZCT-FS-064 | AS81914/3 | **10 | 1.000 | .975 | 1.226 | .023 | 5 | 8.5 | 2.370 |
| ZCT-FS-072 | AS81914/3 | **11 | 1.125 | 1.105 | 1.390 | .023 | 5 | 9.3 | 2.370 |
| ZCT-FS-080 | AS81914/3 | **12 | 1.250 | 1.210 | 1.539 | .023 | 4 | 10.9 | 2.750 |
| ZCT-FS-096 | AS81914/3 | **13 | 1.500 | 1.437 | 1.832 | .023 | 4 | 12.6 | 3.375 |

The table above details ZEUS and AMS-Spec. numbers and dimensions for our standard FEP convoluted tubing. Custom sizes and configurations are also available.

Extra Flexible Convoluted

| Part Number | Military Spec. | Identifier | Max I.D. | Min I.D. | Max O.D. | Max. Wall Thick | Conv/Inch +/-1" | Weight (LBS) Per CFT Maximum | Min. Bend Radius |
|-------------|----------------|------------|----------|----------|----------|-----------------|-----------------|------------------------------|------------------|
| ZCT-FE-012 | AS81914/4 | **01 | .188 | .181 | .320 | .018 | 10 | 1.7 | .31 |
| ZCT-FE-018 | AS81914/4 | **02 | .281 | .273 | .414 | .018 | 10 | 2.0 | .41 |
| ZCT-FE-020 | AS81914/4 | **03 | .312 | .306 | .450 | .018 | 10 | 2.1 | .41 |
| ZCT-FE-024 | AS81914/4 | **04 | .375 | .359 | .510 | .018 | 10 | 2.5 | .50 |
| ZCT-FE-028 | AS81914/4 | **05 | .437 | .427 | .571 | .018 | 10 | 3.9 | .50 |
| ZCT-FE-032 | AS81914/4 | **06 | .500 | .480 | .650 | .023 | 9 | 4.6 | .75 |
| ZCT-FE-040 | AS81914/4 | **07 | .625 | .603 | .770 | .023 | 9 | 5.5 | .75 |
| ZCT-FE-048 | AS81914/4 | **08 | .750 | .725 | .930 | .023 | 8 | 6.9 | .93 |
| ZCT-FE-056 | AS81914/4 | **09 | .875 | .860 | 1.073 | .023 | 7 | 8.9 | 1.25 |
| ZCT-FE-064 | AS81914/4 | **10 | 1.000 | .970 | 1.226 | .023 | 7 | 9.5 | 1.25 |
| ZCT-FE-072 | AS81914/4 | **11 | 1.125 | 1.105 | 1.390 | .023 | 7 | 10.5 | 1.43 |
| ZCT-FE-080 | AS81914/4 | **12 | 1.250 | 1.205 | 1.539 | .023 | 6.5 | 11.2 | 1.43 |
| ZCT-FE-096 | AS81914/4 | **13 | 1.500 | 1.437 | 1.832 | .023 | 5.5 | 12.0 | 1.75 |

The table above details ZEUS and AMS-Spec. numbers and dimensions for our Extra Flexible FEP convoluted tubing. Custom sizes and configurations are also available. Specs shown are for only Class 1 tubing. Material and Dimensions comply with AS81914. Lot to lot testing available upon request.



WWW.ZEUSINC.COM

Convoluted Tubing

ETFE

SPECIALTY PRODUCTS



| Standard Convoluted | | | | | | | | Weight (LBS) Per CFT Maximum | Min. Bend Radius |
|---------------------|----------------|------------|----------|----------|----------|-----------------|----------------|------------------------------|------------------|
| Part Number | Military Spec. | Identifier | Max I.D. | Min I.D. | Max O.D. | Max. Wall Thick | Conv/Inch +/-1 | | |
| ZCT-ES-012 | AS81914/6 | **01 | .188 | .181 | .320 | .018 | 8 | 1.2 | .500 |
| ZCT-ES-018 | AS81914/6 | **02 | .281 | .273 | .414 | .018 | 8 | 1.4 | .750 |
| ZCT-ES-020 | AS81914/6 | **03 | .312 | .306 | .450 | .018 | 8 | 1.5 | .750 |
| ZCT-ES-024 | AS81914/6 | **04 | .375 | .364 | .510 | .018 | 8 | 1.8 | .880 |
| ZCT-ES-028 | AS81914/6 | **05 | .437 | .427 | .571 | .018 | 8 | 2.5 | .880 |
| ZCT-ES-032 | AS81914/6 | **06 | .500 | .485 | .650 | .023 | 7 | 3.2 | 1.250 |
| ZCT-ES-040 | AS81914/6 | **07 | .625 | .608 | .770 | .023 | 7 | 3.9 | 1.500 |
| ZCT-ES-048 | AS81914/6 | **08 | .750 | .730 | .930 | .023 | 6 | 4.9 | 1.750 |
| ZCT-ES-056 | AS81914/6 | **09 | .875 | .860 | 1.073 | .023 | 5 | 5.6 | 2.000 |
| ZCT-ES-064 | AS81914/6 | **10 | 1.000 | .975 | 1.226 | .023 | 5 | 6.8 | 2.37 |
| ZCT-ES-072 | AS81914/6 | **11 | 1.125 | 1.105 | 1.390 | .023 | 5 | 7.5 | 2.37 |
| ZCT-ES-080 | AS81914/6 | **12 | 1.250 | 1.210 | 1.539 | .023 | 4 | 8.8 | 2.75 |
| ZCT-ES-096 | AS81914/6 | **13 | 1.500 | 1.437 | 1.832 | .023 | 4 | 10.2 | 3.38 |

The table above details ZEUS and AMS-Spec. numbers and dimensions for our standard ETFE convoluted tubing. Custom sizes and configurations are also available.

| Extra Flexible Convoluted | | | | | | | | Weight (LBS) Per CFT Maximum | Min. Bend Radius |
|---------------------------|----------------|------------|----------|----------|----------|-----------------|----------------|------------------------------|------------------|
| Part Number | Military Spec. | Identifier | Max I.D. | Min I.D. | Max O.D. | Max. Wall Thick | Conv/Inch +/-1 | | |
| ZCT-EE-012 | AS81914/5 | **01 | .188 | .181 | .320 | .018 | 10 | 1.4 | .31 |
| ZCT-EE-018 | AS81914/5 | **02 | .281 | .273 | .414 | .018 | 10 | 1.6 | .41 |
| ZCT-EE-020 | AS81914/5 | **03 | .312 | .306 | .450 | .018 | 10 | 1.7 | .41 |
| ZCT-EE-024 | AS81914/5 | **04 | .375 | .359 | .510 | .018 | 10 | 2.0 | .50 |
| ZCT-EE-028 | AS81914/5 | **05 | .437 | .427 | .571 | .018 | 10 | 3.1 | .50 |
| ZCT-EE-032 | AS81914/5 | **06 | .500 | .480 | .650 | .023 | 9 | 3.7 | .75 |
| ZCT-EE-040 | AS81914/5 | **07 | .625 | .603 | .770 | .023 | 9 | 4.4 | .75 |
| ZCT-EE-048 | AS81914/5 | **08 | .750 | .725 | .930 | .023 | 8 | 5.6 | .93 |
| ZCT-EE-056 | AS81914/5 | **09 | .875 | .860 | 1.073 | .023 | 7 | 7.1 | 1.25 |
| ZCT-EE-064 | AS81914/5 | **10 | 1.000 | .970 | 1.226 | .023 | 7 | 7.6 | 1.25 |
| ZCT-EE-072 | AS81914/5 | **11 | 1.125 | 1.105 | 1.390 | .023 | 7 | 8.4 | 1.43 |
| ZCT-EE-080 | AS81914/5 | **12 | 1.250 | 1.205 | 1.539 | .023 | 6 | 9.0 | 1.43 |
| ZCT-EE-096 | AS81914/5 | **13 | 1.500 | 1.437 | 1.832 | .023 | 5 | 9.6 | 1.75 |

The table above details ZEUS and AMS-Spec. numbers and dimensions for our Extra Flexible ETFE convoluted tubing. Custom sizes and configurations are also available*. Specs shown are for only Class 1 tubing. Material and Dimensions comply with AS81914. Lot to lot testing available upon request.



WWW.ZEUSINC.COM

PTFE, FEP, PFA & ETFE Spiral-Cut Cable Wrap

SPECIALTY PRODUCTS



Dimensions (inches)

| Ordered by Outside Diameter A | Cut From PTFE, FEP, PFA, ETFE Industrial Tubing Size I.D. B | Wall C | Bundle Diameter Maximum D | Pitch of Helical Cut E |
|-------------------------------------|---|-----------|---------------------------------|------------------------------|
| 1/8 (.125) | 1/16 | 0.030 | 1/2 | (.218) |
| 3/16 (.188) | 1/8 | 0.030 | 1 | (.312) |
| 1/4 (.250) | 3/16 | 0.030 | 2 | (.375) |
| 5/16 (.313) | 1/4 | 0.030 | 2-1/2 | (.375) |
| 3/8 (.375) | 5/16 | 0.030 | 3 | (.437) |
| 1/2 (.500) | 7/16 | 0.030 | 4 | (.562) |
| 5/8 (.625) | 9/16 | 0.030 | 5 | (.625) |
| 3/4 (.750) | 11/16 | 0.035 | 6 | (.875) |
| 1 (1.000) | 15/16 | 0.040 | 8 | (1.000) |

Metric Dimensions (mm)

| Ordered by Outside Diameter A | Cut From PTFE, FEP, PFA, ETFE Industrial Tubing Size I.D. B | Wall C | Bundle Diameter Maximum D | Pitch of Helical Cut E |
|-------------------------------------|---|-----------|---------------------------------|------------------------------|
| 3.18 | 1.59 | 0.76 | 12.70 | 5.54 |
| 4.78 | 3.18 | 0.76 | 25.40 | 7.92 |
| 6.35 | 4.76 | 0.76 | 50.80 | 9.53 |
| 7.94 | 6.35 | 0.76 | 63.50 | 9.53 |
| 9.53 | 7.94 | 0.76 | 76.20 | 11.11 |
| 12.70 | 11.11 | 0.76 | 101.60 | 14.27 |
| 15.88 | 14.29 | 0.76 | 127.00 | 15.88 |
| 19.05 | 17.46 | .89 | 152.40 | 22.23 |
| 25.40 | 23.81 | 1.02 | 203.20 | 25.40 |

Supplied in natural unless otherwise specified.
Custom Pantone colors or ZEUS standard colors available on request.

OD tolerance +/- .005", Wall Tolerance +/- .005",
Pitch Tolerance +/- .030".

Material and dimensions comply with ASTM 3295 Group 4 PTFE. Lot to lot testing
available upon request.

ZEUS SPIRAL-CUT CABLE WRAPS are expandable abrasion-resistant wraps for harnessing and insulating wires, cable, and bundles. ZEUS SPIRAL CUT CABLE WRAP is extruded to close tolerances and then precision cut.

Use chart and letters shown when ordering





"A" = O.D. of PTFE Tubing

"B" = I.D.

"C" = Wall Thickness

"D" = Maximum Bundle Diameter

"E" = Pitch





WWW.ZEUSINC.COM

PTFE, FEP, PFA, ETFE

Extruded Metric Tubing

0.50mm Wall Tubing

EXTRUDED SIZES



| Ordering Size (ID/OD) | I.D. | Tolerance + / - | Wall Thickness |
|-----------------------|-------|-----------------|----------------|
| 0.50/1.50 | 0.50 | 0.05 | 0.50+/-0.07 |
| 1.00/2.00 | 1.00 | 0.05 | 0.50+/-0.07 |
| 1.50/2.50 | 1.50 | 0.10 | 0.50+/-0.07 |
| 2.00/3.00 | 2.00 | 0.10 | 0.50+/-0.07 |
| 2.50/3.50 | 2.50 | 0.15 | 0.50+/-0.07 |
| 3.00/4.00 | 3.00 | 0.15 | 0.50+/-0.07 |
| 3.50/4.50 | 3.50 | 0.15 | 0.50+/-0.07 |
| 4.00/5.00 | 4.00 | 0.15 | 0.50+/-0.07 |
| 4.50/5.50 | 4.50 | 0.20 | 0.50+/-0.07 |
| 5.00/6.00 | 5.00 | 0.20 | 0.50+/-0.07 |
| 5.50/6.50 | 5.50 | 0.20 | 0.50+/-0.07 |
| 6.00/7.00 | 6.00 | 0.20 | 0.50+/-0.07 |
| 6.50/7.50 | 6.50 | 0.20 | 0.50+/-0.07 |
| 7.00/8.00 | 7.00 | 0.20 | 0.50+/-0.07 |
| 7.50/8.50 | 7.50 | 0.20 | 0.50+/-0.07 |
| 8.00/9.00 | 8.00 | 0.20 | 0.50+/-0.07 |
| 8.50/9.50 | 8.50 | 0.30 | 0.50+/-0.07 |
| 9.00/10.00 | 9.00 | 0.30 | 0.50+/-0.07 |
| 12.00/13.00 | 12.00 | 0.30 | 0.50+/-0.07 |
| 13.00/14.00 | 13.00 | 0.50 | 0.50+/-0.07 |

Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request.



PTFE, FEP, PFA, ETFE

Extruded Metric Tubing

1.00mm Wall Tubing

EXTRUDED SIZES



| Ordering Size (ID/OD) | I.D. | Tolerance + / - | Wall Thickness |
|-----------------------|-------|-----------------|----------------|
| 1.00/3.00 | 1.00 | 0.05 | 1.00+/-0.15 |
| 2.00/4.00 | 2.00 | 0.10 | 1.00+/-0.15 |
| 2.50/4.50 | 2.50 | 0.15 | 1.00+/-0.15 |
| 3.00/5.00 | 3.00 | 0.15 | 1.00+/-0.15 |
| 3.50/5.50 | 3.50 | 0.15 | 1.00+/-0.15 |
| 4.00/6.00 | 4.00 | 0.15 | 1.00+/-0.15 |
| 4.50/6.50 | 4.50 | 0.20 | 1.00+/-0.15 |
| 5.00/7.00 | 5.00 | 0.20 | 1.00+/-0.15 |
| 5.50/7.50 | 5.50 | 0.20 | 1.00+/-0.15 |
| 6.00/8.00 | 6.00 | 0.20 | 1.00+/-0.15 |
| 6.50/8.50 | 6.50 | 0.20 | 1.00+/-0.15 |
| 7.00/9.00 | 7.00 | 0.20 | 1.00+/-0.15 |
| 7.50/9.50 | 7.50 | 0.20 | 1.00+/-0.15 |
| 8.00/10.00 | 8.00 | 0.20 | 1.00+/-0.15 |
| 8.50/10.50 | 8.50 | 0.30 | 1.00+/-0.15 |
| 9.00/11.00 | 9.00 | 0.30 | 1.00+/-0.15 |
| 9.50/11.50 | 9.50 | 0.30 | 1.00+/-0.15 |
| 10.00/12.00 | 10.00 | 0.30 | 1.00+/-0.15 |
| 10.50/12.50 | 10.50 | 0.30 | 1.00+/-0.15 |
| 11.00/13.00 | 11.00 | 0.30 | 1.00+/-0.15 |
| 12.00/14.00 | 12.00 | 0.30 | 1.00+/-0.15 |
| 13.00/15.00 | 13.00 | 0.30 | 1.00+/-0.15 |
| 14.00/16.00 | 14.00 | 0.30 | 1.00+/-0.15 |
| 15.00/17.00 | 15.00 | 0.40 | 1.00+/-0.15 |
| 16.00/18.00 | 16.00 | 0.40 | 1.00+/-0.15 |
| 18.00/20.00 | 18.00 | 0.40 | 1.00+/-0.15 |
| 19.00/21.00 | 19.00 | 0.40 | 1.00+/-0.15 |
| 19.50/21.50 | 19.50 | 0.40 | 1.00+/-0.15 |

| Ordering Size (ID/OD) | I.D. | Tolerance + / - | Wall Thickness |
|-----------------------|-------|-----------------|----------------|
| 20.00/22.00 | 20.00 | 0.40 | 1.00+/-0.15 |
| 21.00/23.00 | 21.00 | 0.50 | 1.00+/-0.15 |
| 22.00/24.00 | 22.00 | 0.50 | 1.00+/-0.15 |
| 22.50/24.50 | 22.50 | 0.50 | 1.00+/-0.15 |
| 23.00/25.00 | 23.00 | 0.50 | 1.00+/-0.15 |
| 23.50/25.50 | 23.50 | 0.50 | 1.00+/-0.15 |
| 25.00/27.00 | 25.00 | 0.50 | 1.00+/-0.15 |
| 26.00/28.00 | 26.00 | 0.50 | 1.00+/-0.15 |
| 27.00/29.00 | 27.00 | 0.50 | 1.00+/-0.15 |
| 28.00/30.00 | 28.00 | 0.50 | 1.00+/-0.15 |
| 29.00/31.00 | 29.00 | 0.50 | 1.00+/-0.15 |
| 30.00/32.00 | 30.00 | 0.60 | 1.00+/-0.15 |
| 32.00/34.00 | 32.00 | 0.60 | 1.00+/-0.15 |
| 37.00/39.00 | 37.00 | 0.60 | 1.00+/-0.15 |
| 38.00/40.00 | 38.00 | 0.60 | 1.00+/-0.15 |
| 40.00/42.00 | 40.00 | 0.75 | 1.00+/-0.15 |
| 42.00/44.00 | 42.00 | 0.75 | 1.00+/-0.15 |
| 43.00/45.00 | 43.00 | 0.75 | 1.00+/-0.15 |
| 45.00/47.00 | 45.00 | 0.75 | 1.00+/-0.15 |
| 45.50/47.50 | 45.50 | 0.75 | 1.00+/-0.15 |
| 48.00/50.00 | 48.00 | 0.75 | 1.00+/-0.15 |
| 50.00/52.00 | 50.00 | 0.75 | 1.00+/-0.15 |

Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request.



WWW.ZEUSINC.COM

PTFE, FEP, PFA, ETFE

Extruded Metric Tubing

1.50/2.00mm Wall Tubing

EXTRUDED SIZES



1.50mm Wall Tubing

| Ordering Size (ID/OD) | I.D. | Tolerance + / - | Wall Thickness |
|-----------------------|-------|-----------------|----------------|
| 1.50/4.50 | 1.50 | 0.10 | 1.50+/-0.20 |
| 2.00/5.00 | 2.00 | 0.15 | 1.50+/-0.20 |
| 3.00/6.00 | 3.00 | 0.15 | 1.50+/-0.20 |
| 5.00/8.00 | 5.00 | 0.20 | 1.50+/-0.20 |
| 6.00/9.00 | 6.00 | 0.20 | 1.50+/-0.20 |
| 10.00/13.00 | 10.00 | 0.30 | 1.50+/-0.20 |
| 12.00/15.00 | 12.00 | 0.30 | 1.50+/-0.20 |
| 13.00/16.00 | 13.00 | 0.30 | 1.50+/-0.20 |
| 14.00/17.00 | 14.00 | 0.30 | 1.50+/-0.20 |
| 16.00/19.00 | 16.00 | 0.40 | 1.50+/-0.20 |
| 18.00/21.00 | 18.00 | 0.40 | 1.50+/-0.20 |
| 19.00/22.00 | 19.00 | 0.40 | 1.50+/-0.20 |
| 20.00/23.00 | 20.00 | 0.50 | 1.50+/-0.20 |
| 21.00/24.00 | 21.00 | 0.50 | 1.50+/-0.20 |
| 22.00/25.00 | 22.00 | 0.50 | 1.50+/-0.20 |
| 25.00/28.00 | 25.00 | 0.50 | 1.50+/-0.20 |
| 28.00/31.00 | 28.00 | 0.50 | 1.50+/-0.20 |
| 29.00/32.00 | 29.00 | 0.50 | 1.50+/-0.20 |
| 30.00/33.00 | 30.00 | 0.60 | 1.50+/-0.20 |
| 40.00/43.00 | 40.00 | 0.75 | 1.50+/-0.20 |
| 49.00/52.00 | 49.00 | 0.75 | 1.50+/-0.20 |

2.00mm Wall Tubing

| Ordering Size (ID/OD) | I.D. | Tolerance + / - | Wall Thickness |
|-----------------------|-------|-----------------|----------------|
| 2.00/6.00 | 2.00 | 0.10 | 2.00+/-0.20 |
| 4.00/8.00 | 4.00 | 0.15 | 2.00+/-0.20 |
| 6.00/10.00 | 6.00 | 0.20 | 2.00+/-0.20 |
| 8.00/12.00 | 8.00 | 0.20 | 2.00+/-0.20 |
| 10.00/14.00 | 10.00 | 0.30 | 2.00+/-0.20 |
| 12.00/16.00 | 12.00 | 0.30 | 2.00+/-0.20 |
| 14.00/18.00 | 14.00 | 0.40 | 2.00+/-0.20 |
| 16.00/20.00 | 16.00 | 0.40 | 2.00+/-0.20 |
| 20.00/24.00 | 20.00 | 0.50 | 2.00+/-0.20 |
| 25.00/29.00 | 25.00 | 0.50 | 2.00+/-0.20 |
| 28.00/32.00 | 28.00 | 0.50 | 2.00+/-0.20 |
| 28.50/32.50 | 28.50 | 0.50 | 2.00+/-0.20 |
| 32.00/36.00 | 32.00 | 0.60 | 2.00+/-0.20 |
| 36.00/40.00 | 36.00 | 0.60 | 2.00+/-0.20 |
| 40.00/44.00 | 40.00 | 0.75 | 2.00+/-0.20 |
| 46.00/50.00 | 46.00 | 0.75 | 2.00+/-0.20 |

Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request.



ZEUS[®]

HEAT SHRINKABLE EXTRUSIONS



HEAT SHRINKABLE EXTRUSIONS





ZEUS Heat Shrink Fluoropolymer Tubing

WWW.ZEUSINC.COM

HEAT SHRINKABLE EXTRUSIONS

ZEUS heat shrink tubing offers a unique combination of properties in its tubing, including outstanding electrical characteristics; excellent chemical and solvent resistances; purity; lubricity and outstanding performance reliability.



ZEUS has mastered the art of manufacturing fluoropolymer heat shrink tubing and can supply it with recovered walls as thin as .002". Please contact a ZEUS representative to learn more about customer sizes, packaging, lengths and colors.


Heat Shrink Application Tips

1. Always assure good ventilation in the immediate work area prior to beginning the heat shrinking process.

Caution: Fumes may cause nausea and dizziness.

2. The mandrel to be covered by the heat shrink must be able to withstand the required temperature for material recovery (see table at right).
3. The mandrel being covered may act as a heat sink (especially metal mandrels). Therefore, ZEUS recommends preheating mandrels.
4. Heat shrink should be allowed to recover a minimum of 20%. Highly restricted radial recovery tends to induce longitudinal change and increase the tendency for splitting.

TOP VIEW - ROLLER IN LATHE



SAME PROCEDURE APPLIES FOR MANUAL ROTATION

5. Ovens are the most reliable way to recover heat shrink products due to their ability to ensure even heating and reduce the risk of over heating the material which can lead to brittleness and cracking. If a heat gun will be used please refer to the picture above illustrating the proper application of heat to achieve the most uniform recovery.
6. See Chart for recovery temperatures.

HEAT SHRINK RECOVERY TEMPERATURE

| Material | Recovery Temperature |
|------------------------|--------------------------------|
| PTFE | 654°F - 670°F 346°C - 354°C |
| FEP (1" ID or less) | 400°F - 420°F 204°C - 216°C |
| FEP (1" ID or greater) | 420°F - 440°F 216°C - 227°C |

The heat shrink temperatures listed in this catalog are general guidelines. Actual shrink temperatures may be higher or lower depending on the design and dimensions of the heat shrink, application techniques and other factors. Please contact a ZEUS Technical Account Manager for more information.



WWW.ZEUSINC.COM

PTFE Heat Shrink

2 to 1 Shrink Ratio

Approximate Ratio of Expanded I.D. to Recovered I.D. – AWG Sizes

HEAT SHRINKABLE EXTRUSIONS

Dimensions (inches)



| STANDARD WALL, Class 2 | | | | | THIN WALL, Class 3 | | | | | LIGHTWEIGHT WALL, Class 4 | | | | |
|-------------------------|--------------------|---------------------|-------------------------------|-------------------------------|-------------------------|--------------------|---------------------|-------------------------------|-------------------------------|---------------------------|--------------------|---------------------|-------------------------------|-------------------------------|
| Ordered as AWG Size No. | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness Nom. | Recovered Wall Thickness Tol. | Ordered as AWG Size No. | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness Nom. | Recovered Wall Thickness Tol. | Ordered as AWG Size No. | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness Nom. | Recovered Wall Thickness Tol. |
| 30* | 0.034 | 0.015 | 0.009 | ±.002 | 30 | 0.034 | 0.015 | 0.009 | ±.002 | 30* | 0.034 | 0.015 | 0.006 | ±.002 |
| 28* | 0.038 | 0.018 | 0.009 | ±.002 | 28 | 0.038 | 0.018 | 0.009 | ±.002 | 28* | 0.038 | 0.018 | 0.006 | ±.002 |
| 26* | 0.046 | 0.022 | 0.010 | ±.002 | 26 | 0.046 | 0.022 | 0.010 | ±.002 | 26* | 0.046 | 0.022 | 0.006 | ±.002 |
| 24 | 0.050 | 0.027 | 0.012 | ±.002 | 24 | 0.050 | 0.027 | 0.010 | ±.002 | 24 | 0.050 | 0.025 | 0.006 | ±.002 |
| 22 | 0.055 | 0.032 | 0.012 | ±.002 | 22 | 0.055 | 0.032 | 0.012 | ±.003 | 22 | 0.055 | 0.031 | 0.006 | ±.002 |
| 20 | 0.060 | 0.039 | 0.016 | ±.003 | 20 | 0.060 | 0.039 | 0.012 | ±.003 | 20 | 0.060 | 0.038 | 0.006 | ±.002 |
| 19 | 0.065 | 0.043 | 0.016 | ±.003 | 19 | 0.065 | 0.043 | 0.012 | ±.003 | 19 | 0.065 | 0.043 | 0.006 | ±.002 |
| 18 | 0.076 | 0.049 | 0.016 | ±.003 | 18 | 0.076 | 0.049 | 0.012 | ±.003 | 18 | 0.076 | 0.046 | 0.006 | ±.002 |
| 17 | 0.085 | 0.054 | 0.016 | ±.003 | 17 | 0.085 | 0.054 | 0.012 | ±.003 | 17 | 0.085 | 0.054 | 0.006 | ±.002 |
| 16 | 0.093 | 0.061 | 0.016 | ±.003 | 16 | 0.093 | 0.061 | 0.012 | ±.003 | 16 | 0.093 | 0.057 | 0.006 | ±.002 |
| 15 | 0.110 | 0.067 | 0.016 | ±.003 | 15 | 0.110 | 0.067 | 0.012 | ±.003 | 15 | 0.110 | 0.063 | 0.006 | ±.002 |
| 14 | 0.120 | 0.072 | 0.016 | ±.003 | 14 | 0.120 | 0.072 | 0.012 | ±.003 | 14 | 0.120 | 0.072 | 0.008 | ±.002 |
| 13 | 0.140 | 0.080 | 0.016 | ±.003 | 13 | 0.140 | 0.080 | 0.012 | ±.003 | 13 | 0.140 | 0.080 | 0.008 | ±.002 |
| 12 | 0.150 | 0.089 | 0.016 | ±.003 | 12 | 0.150 | 0.089 | 0.012 | ±.003 | 12 | 0.150 | 0.089 | 0.008 | ±.002 |
| 11 | 0.170 | 0.101 | 0.016 | ±.003 | 11 | 0.170 | 0.101 | 0.012 | ±.003 | 11 | 0.170 | 0.099 | 0.008 | ±.002 |
| 10 | 0.191 | 0.112 | 0.016 | ±.003 | 10 | 0.191 | 0.112 | 0.012 | ±.003 | 10 | 0.191 | 0.110 | 0.008 | ±.002 |
| 9 | 0.205 | 0.124 | 0.020 | ±.004 | 9 | 0.205 | 0.124 | 0.015 | ±.004 | 9 | 0.205 | 0.122 | 0.008 | ±.002 |
| 8 | 0.240 | 0.141 | 0.020 | ±.004 | 8 | 0.240 | 0.141 | 0.015 | ±.004 | 8 | 0.240 | 0.139 | 0.008 | ±.002 |
| 7 | 0.270 | 0.158 | 0.020 | ±.004 | 7 | 0.270 | 0.158 | 0.015 | ±.004 | 7 | 0.270 | 0.154 | 0.008 | ±.002 |
| 6 | 0.302 | 0.178 | 0.020 | ±.004 | 6 | 0.302 | 0.178 | 0.015 | ±.004 | 6 | 0.302 | 0.172 | 0.010 | ±.003 |
| 5 | 0.320 | 0.198 | 0.020 | ±.004 | 5 | 0.320 | 0.198 | 0.015 | ±.004 | 5 | 0.320 | 0.192 | 0.010 | ±.003 |
| 4 | 0.370 | 0.224 | 0.020 | ±.004 | 4 | 0.370 | 0.224 | 0.015 | ±.004 | 4 | 0.370 | 0.214 | 0.010 | ±.003 |
| 3 | 0.390 | 0.249 | 0.020 | ±.004 | 3 | 0.390 | 0.249 | 0.015 | ±.004 | 3 | 0.390 | 0.241 | 0.010 | ±.003 |
| 2 | 0.430 | 0.278 | 0.020 | ±.004 | 2 | 0.430 | 0.278 | 0.015 | ±.004 | 2 | 0.430 | 0.270 | 0.010 | ±.003 |
| 1 | 0.450 | 0.311 | 0.020 | ±.004 | 1 | 0.450 | 0.311 | 0.015 | ±.004 | 1 | 0.450 | 0.301 | 0.010 | ±.003 |
| 0 | 0.470 | 0.347 | 0.020 | ±.004 | 0 | 0.470 | 0.347 | 0.015 | ±.004 | 0 | 0.470 | 0.347 | 0.012 | ±.003 |

AMS-DTL-23053/12

*AWG 30, 28, 26 SW and LW are not covered under AMS-DTL-23053/12.

PACKAGING: Standard 4ft lengths, unless otherwise specified.

On all cases of military or commercial specifications, latest revisions apply. Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request.



WWW.ZEUSINC.COM

PTFE Heat Shrink

2 to 1 Shrink Ratio

Approximate Ratio of Expanded I.D. to Recovered I.D. – AWG Sizes

HEAT SHRINKABLE EXTRUSIONS

Metric Dimensions (mm)



| STANDARD WALL | | | | | THIN WALL | | | | | LIGHTWEIGHT WALL | | | | |
|-------------------------|--------------------|---------------------|--------------------------|------|-------------------------|--------------------|---------------------|--------------------------|------|-------------------------|--------------------|---------------------|--------------------------|------|
| Ordered as AWG Size No. | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness | | Ordered as AWG Size No. | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness | | Ordered as AWG Size No. | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness | |
| | | | Nom. | Tol. | | | | Nom. | Tol. | | | | Nom. | Tol. |
| 30* | 0.86 | 0.38 | 0.23 | ±.05 | 30 | 0.86 | 0.38 | 0.23 | ±.05 | 30* | 0.86 | 0.38 | 0.15 | ±.05 |
| 28* | 0.96 | 0.46 | 0.23 | ±.05 | 28 | 0.96 | 0.46 | 0.23 | ±.05 | 28* | 0.96 | 0.46 | 0.15 | ±.05 |
| 26* | 1.17 | 0.56 | 0.25 | ±.05 | 26 | 1.17 | 0.56 | 0.25 | ±.05 | 26* | 1.17 | 0.56 | 0.15 | ±.05 |
| 24 | 1.27 | 0.69 | 0.30 | ±.05 | 24 | 1.27 | 0.69 | 0.25 | ±.05 | 24 | 1.27 | 0.64 | 0.15 | ±.05 |
| 22 | 1.40 | 0.81 | 0.30 | ±.05 | 22 | 1.40 | 0.81 | 0.30 | ±.08 | 22 | 1.40 | 0.79 | 0.15 | ±.05 |
| 20 | 1.52 | 0.99 | 0.41 | ±.08 | 20 | 1.52 | 0.99 | 0.30 | ±.08 | 20 | 1.52 | 0.97 | 0.15 | ±.05 |
| 19 | 1.65 | 1.09 | 0.41 | ±.08 | 19 | 1.65 | 1.09 | 0.30 | ±.08 | 19 | 1.65 | 1.09 | 0.15 | ±.05 |
| 18 | 1.93 | 1.24 | 0.41 | ±.08 | 18 | 1.93 | 1.24 | 0.30 | ±.08 | 18 | 1.93 | 1.17 | 0.15 | ±.05 |
| 17 | 2.16 | 1.37 | 0.41 | ±.08 | 17 | 2.16 | 1.37 | 0.30 | ±.08 | 17 | 2.16 | 1.37 | 0.15 | ±.05 |
| 16 | 2.36 | 1.55 | 0.41 | ±.08 | 16 | 2.36 | 1.55 | 0.30 | ±.08 | 16 | 2.36 | 1.45 | 0.15 | ±.05 |
| 15 | 2.79 | 1.70 | 0.41 | ±.08 | 15 | 2.79 | 1.70 | 0.30 | ±.08 | 15 | 2.79 | 1.60 | 0.15 | ±.05 |
| 14 | 3.05 | 1.83 | 0.41 | ±.08 | 14 | 3.05 | 1.83 | 0.30 | ±.08 | 14 | 3.05 | 1.83 | 0.20 | ±.05 |
| 13 | 3.56 | 2.03 | 0.41 | ±.08 | 13 | 3.56 | 2.03 | 0.30 | ±.08 | 13 | 3.56 | 2.03 | 0.20 | ±.05 |
| 12 | 3.81 | 2.26 | 0.41 | ±.08 | 12 | 3.81 | 2.26 | 0.30 | ±.08 | 12 | 3.81 | 2.26 | 0.20 | ±.05 |
| 11 | 4.32 | 2.57 | 0.41 | ±.08 | 11 | 4.32 | 2.57 | 0.30 | ±.08 | 11 | 4.32 | 2.51 | 0.20 | ±.05 |
| 10 | 4.85 | 2.84 | 0.41 | ±.08 | 10 | 4.85 | 2.84 | 0.30 | ±.08 | 10 | 4.85 | 2.79 | 0.20 | ±.05 |
| 9 | 5.21 | 3.15 | 0.51 | ±.10 | 9 | 5.21 | 3.15 | 0.38 | ±.10 | 9 | 5.21 | 3.10 | 0.20 | ±.05 |
| 8 | 6.10 | 3.58 | 0.51 | ±.10 | 8 | 6.10 | 3.58 | 0.38 | ±.10 | 8 | 6.10 | 3.53 | 0.20 | ±.05 |
| 7 | 6.86 | 4.01 | 0.51 | ±.10 | 7 | 6.86 | 4.01 | 0.38 | ±.10 | 7 | 6.86 | 3.91 | 0.20 | ±.05 |
| 6 | 7.67 | 4.52 | 0.51 | ±.10 | 6 | 7.67 | 4.52 | 0.38 | ±.10 | 6 | 7.67 | 4.37 | 0.25 | ±.08 |
| 5 | 8.13 | 5.03 | 0.51 | ±.10 | 5 | 8.13 | 5.03 | 0.38 | ±.10 | 5 | 8.13 | 4.88 | 0.25 | ±.08 |
| 4 | 9.40 | 5.69 | 0.51 | ±.10 | 4 | 9.40 | 5.69 | 0.38 | ±.10 | 4 | 9.40 | 5.44 | 0.25 | ±.08 |
| 3 | 9.91 | 6.32 | 0.51 | ±.10 | 3 | 9.91 | 6.32 | 0.38 | ±.10 | 3 | 9.91 | 6.12 | 0.25 | ±.08 |
| 2 | 10.92 | 7.06 | 0.51 | ±.10 | 2 | 10.92 | 7.06 | 0.38 | ±.10 | 2 | 10.92 | 6.86 | 0.25 | ±.08 |
| 1 | 11.43 | 7.90 | 0.51 | ±.10 | 1 | 11.43 | 7.90 | 0.38 | ±.10 | 1 | 11.43 | 7.65 | 0.25 | ±.08 |
| 0 | 11.94 | 8.81 | 0.51 | ±.10 | 0 | 11.94 | 8.81 | 0.38 | ±.10 | 0 | 11.94 | 8.81 | 0.30 | ±.08 |

AMS-DTL-23053/12

*AWG 30, 28, 26 SW and LW are not covered under AMS-DTL-23053/12.

PACKAGING: Standard 4ft lengths, unless otherwise specified.

Custom Pantone colors or ZEUS standard colors available on request.



WWW.ZEUSINC.COM

PTFE Heat Shrink

2 to 1 Shrink Ratio

Approximate Ratio of Expanded I.D. to Recovered I.D. – Fractional Inch Sizes

HEAT SHRINKABLE EXTRUSIONS



Dimensions (inches)

| STANDARD WALL, Class 2 | | | | | THIN WALL, Class 3 | | | | | INDUSTRIAL WALL, Class 1 | | | | |
|------------------------|--------------------|---------------------|-------------------------------|-------|--------------------|--------------------|---------------------|-------------------------------|-------|--------------------------|--------------------|---------------------|-------------------------------|-------|
| Ordered as ID | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness Nom. | Tol. | Ordered as ID | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness Nom. | Tol. | Ordered as ID | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness Nom. | Tol. |
| 1/8 | 0.215 | 0.130 | 0.020 | ±.004 | 1/8 | 0.215 | 0.130 | 0.015 | ±.003 | 1/8 | 0.166 | 0.130 | 0.030 | ±.005 |
| 1/4 | 0.410 | 0.260 | 0.020 | ±.004 | 1/4 | 0.410 | 0.260 | 0.015 | ±.003 | 3/16 | 0.250 | 0.193 | 0.030 | ±.005 |
| 5/16 | 0.470 | 0.329 | 0.020 | ±.004 | 5/16 | 0.470 | 0.329 | 0.015 | ±.003 | 1/4 | 0.333 | 0.257 | 0.030 | ±.005 |
| 3/8 | 0.560 | 0.399 | 0.025 | ±.006 | 3/8 | 0.560 | 0.399 | 0.015 | ±.003 | 5/16 | 0.415 | 0.320 | 0.030 | ±.005 |
| 7/16 | 0.655 | 0.462 | 0.025 | ±.006 | 7/16 | 0.655 | 0.462 | 0.018 | ±.004 | 3/8 | 0.498 | 0.383 | 0.030 | ±.005 |
| 1/2 | 0.750 | 0.524 | 0.025 | ±.006 | 1/2 | 0.750 | 0.524 | 0.018 | ±.004 | 7/16 | 0.580 | 0.448 | 0.030 | ±.006 |
| 5/8 | 0.930 | 0.655 | 0.030 | ±.006 | 5/8 | 0.930 | 0.655 | 0.020 | ±.004 | 1/2 | 0.666 | 0.510 | 0.030 | ±.006 |
| 3/4 | 1.125 | 0.786 | 0.035 | ±.008 | 3/4 | 1.125 | 0.786 | 0.025 | ±.005 | 9/16 | 0.748 | 0.572 | 0.030 | ±.006 |
| 7/8 | 1.310 | 0.911 | 0.035 | ±.008 | 7/8 | 1.310 | 0.911 | 0.030 | ±.006 | 5/8 | 0.830 | 0.637 | 0.030 | ±.006 |
| 1 | 1.500 | 1.036 | 0.035 | ±.008 | 1 | 1.500 | 1.036 | 0.030 | ±.006 | 11/16 | 0.915 | 0.700 | 0.032 | ±.006 |
| | | | | | | | | | | 3/4 | 1.000 | 0.764 | 0.040 | ±.007 |
| | | | | | | | | | | 7/8 | 1.170 | 0.891 | 0.045 | ±.007 |
| | | | | | | | | | | 1 | 1.330 | 1.020 | 0.050 | ±.008 |

| LIGHTWEIGHT WALL, Class 4 | | | | |
|---------------------------|--------------------|---------------------|-------------------------------|-------|
| Ordered as ID | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness Nom. | Tol. |
| 1/8 | 0.215 | 0.130 | 0.008 | ±.002 |
| 1/4 | 0.410 | 0.260 | 0.010 | ±.003 |
| 5/16 | 0.470 | 0.329 | 0.012 | ±.003 |



WWW.ZEUSINC.COM

PTFE Heat Shrink

2 to 1 Shrink Ratio

Approximate Ratio of Expanded I.D. to Recovered I.D. – Fractional Inch Sizes

HEAT SHRINKABLE EXTRUSIONS

Metric Dimensions (mm)



| STANDARD WALL, Class 2 | | | | | THIN WALL, Class 3 | | | | | INDUSTRIAL WALL, Class 1 | | | | |
|------------------------|--------------------|---------------------|--------------------------|------|--------------------|--------------------|---------------------|--------------------------|------|--------------------------|--------------------|---------------------|--------------------------|------|
| Ordered as ID | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness | | Ordered as ID | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness | | Ordered as ID | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness | |
| | | | Nom. | Tol. | | | | Nom. | Tol. | | | | Nom. | Tol. |
| 1/8 | 5.46 | 3.30 | 0.51 | ±.10 | 1/8 | 5.46 | 3.30 | 0.38 | ±.08 | 1/8 | 4.22 | 3.30 | 0.76 | ±.13 |
| 1/4 | 10.41 | 6.60 | 0.51 | ±.10 | 1/4 | 10.41 | 6.60 | 0.38 | ±.08 | 3/16 | 6.35 | 4.90 | 0.76 | ±.13 |
| 5/16 | 11.94 | 8.36 | 0.51 | ±.10 | 5/16 | 11.94 | 8.36 | 0.38 | ±.08 | 1/4 | 8.46 | 6.53 | 0.76 | ±.13 |
| 3/8 | 14.22 | 10.13 | 0.64 | ±.15 | 3/8 | 14.22 | 10.13 | 0.38 | ±.08 | 5/16 | 10.54 | 8.13 | 0.76 | ±.13 |
| 7/16 | 16.64 | 11.73 | 0.64 | ±.15 | 7/16 | 16.64 | 11.73 | 0.46 | ±.10 | 3/8 | 12.65 | 9.73 | 0.76 | ±.13 |
| 1/2 | 19.05 | 13.31 | 0.64 | ±.15 | 1/2 | 19.05 | 13.31 | 0.46 | ±.10 | 7/16 | 14.73 | 11.38 | 0.76 | ±.15 |
| 5/8 | 23.62 | 16.64 | 0.76 | ±.15 | 5/8 | 23.62 | 16.64 | 0.51 | ±.10 | 1/2 | 16.92 | 12.95 | 0.76 | ±.15 |
| 3/4 | 28.58 | 19.96 | 0.89 | ±.20 | 3/4 | 28.58 | 19.96 | 0.64 | ±.13 | 9/16 | 19.00 | 14.53 | 0.76 | ±.15 |
| 7/8 | 33.27 | 23.14 | 0.89 | ±.20 | 7/8 | 33.27 | 23.14 | 0.76 | ±.15 | 5/8 | 21.08 | 16.18 | 0.76 | ±.15 |
| 1 | 38.10 | 26.31 | 0.89 | ±.20 | 1 | 38.10 | 26.31 | 0.76 | ±.15 | 11/16 | 23.24 | 17.78 | 0.81 | ±.15 |
| | | | | | | | | | | 3/4 | 25.40 | 19.41 | 1.02 | ±.18 |
| | | | | | | | | | | 7/8 | 29.72 | 22.63 | 1.14 | ±.18 |
| | | | | | | | | | | 1 | 33.78 | 25.91 | 1.27 | ±.20 |

LIGHTWEIGHT WALL, Class 4

| Ordered as ID | Expanded I.D. Min. | Recovered I.D. Max. | Recovered Wall Thickness | |
|---------------|--------------------|---------------------|--------------------------|------|
| | | | Nom. | Tol. |
| 1/8 | 5.46 | 3.30 | 0.20 | ±.05 |
| 1/4 | 10.41 | 6.60 | 0.25 | ±.07 |
| 5/16 | 11.94 | 8.36 | 0.30 | ±.07 |



WWW.ZEUSINC.COM

PTFE Heat Shrink

4 to 1 Shrink Ratio

Approximate Ratio of Expanded I.D. to Recovered I.D. – Fractional Inch Sizes

HEAT SHRINKABLE EXTRUSIONS

Dimensions (inches)

| Ordered As Fractional I.D. | Expanded I.D. | RECOVERED – AFTER HEAT SHRINK | | |
|----------------------------|---------------|-------------------------------|---------------------|---------------------|
| | | I.D. Max. | Wall Thickness Nom. | Wall Thickness Tol. |
| 5/64 | 0.078 | 0.025 | 0.009 | ±.002 |
| 1/8 | 0.125 | 0.037 | 0.012 | ±.002 |
| 3/16 | 0.187 | 0.050 | 0.012 | ±.002 |
| 1/4 | 0.250 | 0.063 | 0.012 | ±.002 |
| 5/16 | 0.312 | 0.078 | 0.012 | ±.002 |
| 3/8 | 0.375 | 0.096 | 0.012 | ±.002 |
| 7/16 | 0.438 | 0.112 | 0.012 | ±.002 |
| 1/2 | 0.500 | 0.144 | 0.015 | ±.004 |
| 9/16 | 0.562 | 0.155 | 0.015 | ±.004 |
| 5/8 | 0.625 | 0.178 | 0.015 | ±.004 |
| 11/16 | 0.687 | 0.198 | 0.015 | ±.004 |
| 3/4 | 0.750 | 0.224 | 0.015 | ±.004 |
| 7/8 | 0.875 | 0.244 | 0.015 | ±.004 |
| 1 | 1.000 | 0.278 | 0.015 | ±.004 |
| 1-1/4 | 1.250 | 0.347 | 0.015 | ±.004 |
| 1-1/2 | 1.500 | 0.400 | 0.015 | ±.004 |
| 1-3/4 | 1.750 | 0.450 | 0.015 | ±.004 |
| 2 | 2.000 | 0.520 | 0.020 | ±.005 |
| 2-1/4 | 2.250 | 0.585 | 0.020 | ±.005 |
| 2-1/2 | 2.500 | 0.650 | 0.020 | ±.005 |
| 2-3/4 | 2.750 | 0.710 | 0.020 | ±.005 |
| 3 | 3.000 | 0.775 | 0.020 | ±.005 |
| 3-1/4 | 3.250 | 0.835 | 0.020 | ±.005 |
| 3-1/2 | 3.500 | 0.900 | 0.025 | ±.005 |
| 3-3/4 | 3.750 | 0.960 | 0.025 | ±.005 |
| 4 | 4.000 | 1.025 | 0.025 | ±.005 |

Metric Dimensions (mm)



| Ordered As Fractional I.D. | Expanded I.D. | RECOVERED – AFTER HEAT SHRINK | | |
|----------------------------|---------------|-------------------------------|---------------------|---------------------|
| | | I.D. Max. | Wall Thickness Nom. | Wall Thickness Tol. |
| 5/64 | 1.98 | 0.64 | 0.23 | ±.05 |
| 1/8 | 3.18 | 0.94 | 0.31 | ±.05 |
| 3/16 | 4.75 | 1.27 | 0.31 | ±.05 |
| 1/4 | 6.35 | 1.60 | 0.31 | ±.05 |
| 5/16 | 7.92 | 1.98 | 0.31 | ±.05 |
| 3/8 | 9.53 | 2.44 | 0.31 | ±.05 |
| 7/16 | 11.13 | 2.84 | 0.31 | ±.05 |
| 1/2 | 12.70 | 3.66 | 0.38 | ±.10 |
| 9/16 | 14.27 | 3.94 | 0.38 | ±.10 |
| 5/8 | 15.88 | 4.52 | 0.38 | ±.10 |
| 11/16 | 17.45 | 5.03 | 0.38 | ±.10 |
| 3/4 | 19.05 | 5.69 | 0.38 | ±.10 |
| 7/8 | 22.23 | 6.20 | 0.38 | ±.10 |
| 1 | 25.40 | 7.06 | 0.38 | ±.10 |
| 1-1/4 | 31.75 | 8.81 | 0.38 | ±.10 |
| 1-1/2 | 38.10 | 10.16 | 0.38 | ±.10 |
| 1-3/4 | 44.45 | 11.43 | 0.38 | ±.10 |
| 2 | 50.80 | 13.21 | 0.51 | ±.13 |
| 2-1/4 | 57.15 | 14.86 | 0.51 | ±.13 |
| 2-1/2 | 63.50 | 16.51 | 0.51 | ±.13 |
| 2-3/4 | 69.85 | 18.03 | 0.51 | ±.13 |
| 3 | 76.20 | 19.68 | 0.51 | ±.13 |
| 3-1/4 | 82.50 | 21.21 | 0.51 | ±.13 |
| 3-1/2 | 88.90 | 22.86 | 0.64 | ±.13 |
| 3-3/4 | 92.95 | 24.38 | 0.64 | ±.13 |
| 4 | 101.60 | 26.03 | 0.64 | ±.13 |

Custom Pantone colors or ZEUS standard colors available on request.

Complies with AMS-DTL-23053/12. Class 5.



WWW.ZEUSINC.COM

FEP Heat Shrink

1.3 to 1 Shrink Ratio

Approximate Ratio of Expanded I.D. to Recovered I.D. – AWG/Fractional Inch Sizes

HEAT SHRINKABLE EXTRUSIONS



Dimensions (inches)

| Ordered as AWG Size | As Supplied Inside Diameter Min. | Recovered – After Shrinking | | | |
|------------------------|--|---------------------------------|-------|------------------------|-------|
| | | I.D. Will Shrink to at Least | Min. | Wall Thickness Nom. | Max. |
| 24 | 0.031 | 0.027 | 0.006 | 0.008 | 0.010 |
| 22 | 0.036 | 0.032 | 0.006 | 0.008 | 0.010 |
| 20 | 0.045 | 0.039 | 0.006 | 0.008 | 0.010 |
| 18 | 0.060 | 0.049 | 0.006 | 0.008 | 0.010 |
| 16 | 0.075 | 0.061 | 0.007 | 0.009 | 0.011 |
| 14 | 0.092 | 0.072 | 0.007 | 0.009 | 0.011 |
| 12 | 0.115 | 0.089 | 0.007 | 0.009 | 0.011 |
| 10 | 0.141 | 0.114 | 0.007 | 0.010 | 0.013 |
| 9 | 0.158 | 0.124 | 0.007 | 0.010 | 0.013 |
| 8 | 0.180 | 0.143 | 0.007 | 0.010 | 0.013 |
| 7 | 0.197 | 0.158 | 0.007 | 0.011 | 0.015 |
| 6 | 0.225 | 0.180 | 0.007 | 0.011 | 0.015 |
| 5 | 0.248 | 0.198 | 0.007 | 0.011 | 0.015 |
| 4 | 0.290 | 0.226 | 0.007 | 0.011 | 0.015 |
| 3 | 0.310 | 0.249 | 0.007 | 0.011 | 0.015 |
| 2 | 0.365 | 0.280 | 0.008 | 0.012 | 0.016 |
| 1 | 0.400 | 0.311 | 0.008 | 0.012 | 0.016 |
| 0 | 0.440 | 0.349 | 0.008 | 0.012 | 0.016 |

Fractional Inch (decimal) Tubing

| Size | As Supplied Inside Diameter Min. | Recovered – After Shrinking | | | |
|---------------|--|---------------------------------|-------|------------------------|-------|
| | | I.D. Will Shrink to at Least | Min. | Wall Thickness Nom. | Max. |
| 3/8 (0.375) | 0.500 | 0.383 | 0.011 | 0.015 | 0.019 |
| 7/16 (0.438) | 0.580 | 0.448 | 0.016 | 0.020 | 0.024 |
| 1/2 (0.500) | 0.666 | 0.510 | 0.016 | 0.020 | 0.024 |
| 5/8 (0.625) | 0.830 | 0.637 | 0.021 | 0.025 | 0.029 |
| 3/4 (0.750) | 1.000 | 0.764 | 0.026 | 0.030 | 0.034 |
| 7/8 (0.875) | 1.170 | 0.891 | 0.031 | 0.035 | 0.039 |
| 1 (1.000) | 1.330 | 1.020 | 0.031 | 0.035 | 0.039 |
| 1-1/8 (1.125) | 1.500 | 1.145 | 0.031 | 0.035 | 0.039 |
| 1-1/4 (1.250) | 1.666 | 1.270 | 0.031 | 0.035 | 0.039 |
| 1-3/8 (1.375) | 1.833 | 1.390 | 0.031 | 0.035 | 0.039 |
| 1-1/2 (1.500) | 2.000 | 1.570 | 0.031 | 0.035 | 0.039 |

COMPLIES WITH: AMS-DTL-23053/11Class 1

COLOR: Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request.

CUSTOM SPECIFICATIONS AND TOLERANCES QUOTED UPON REQUEST



FEP Heat Shrink

1.3 to 1 Shrink Ratio

Approximate Ratio of Expanded I.D. to Recovered I.D. – AWG/Fractional Inch Sizes

WWW.ZEUSINC.COM

HEAT SHRINKABLE EXTRUSIONS



Metric Dimensions (mm)

| Ordered as AWG Size | As Supplied Inside Diameter Min. | Recovered - After Shrinking | | | |
|------------------------|--|---------------------------------|------|------------------------|------|
| | | I.D. Will Shrink to at Least | Min. | Wall Thickness Nom. | Max. |
| 24 | 0.79 | 0.69 | 0.15 | 0.20 | 0.25 |
| 22 | 0.91 | 0.81 | 0.15 | 0.20 | 0.25 |
| 20 | 1.14 | 0.99 | 0.15 | 0.20 | 0.25 |
| 18 | 1.52 | 1.25 | 0.15 | 0.20 | 0.25 |
| 16 | 1.91 | 1.55 | 0.18 | 0.23 | 0.28 |
| 14 | 2.34 | 1.83 | 0.18 | 0.23 | 0.28 |
| 12 | 2.92 | 2.26 | 0.18 | 0.23 | 0.28 |
| 10 | 3.58 | 2.90 | 0.18 | 0.25 | 0.33 |
| 9 | 4.01 | 3.15 | 0.18 | 0.25 | 0.33 |
| 8 | 4.57 | 3.63 | 0.18 | 0.25 | 0.33 |
| 7 | 5.00 | 4.01 | 0.18 | 0.28 | 0.38 |
| 6 | 5.72 | 4.57 | 0.18 | 0.28 | 0.38 |
| 5 | 6.30 | 5.03 | 0.18 | 0.28 | 0.38 |
| 4 | 7.37 | 5.74 | 0.18 | 0.28 | 0.38 |
| 3 | 7.87 | 6.32 | 0.18 | 0.28 | 0.38 |
| 2 | 9.27 | 7.11 | 0.20 | 0.30 | 0.41 |
| 1 | 10.16 | 7.90 | 0.20 | 0.30 | 0.41 |
| 0 | 11.18 | 8.86 | 0.20 | 0.30 | 0.41 |

Fractional Inch (mm) Tubing

| Size | As Supplied Inside Diameter Min. | Recovered - After Shrinking | | | |
|---------------|--|---------------------------------|------|------------------------|------|
| | | I.D. Will Shrink to at Least | Min. | Wall Thickness Nom. | Max. |
| 3/8 (9.53) | 12.70 | 9.73 | 0.28 | 0.38 | 0.48 |
| 7/16 (11.13) | 14.73 | 11.38 | 0.41 | 0.51 | 0.61 |
| 1/2 (12.70) | 16.92 | 12.95 | 0.41 | 0.51 | 0.61 |
| 5/8 (15.88) | 21.08 | 16.18 | 0.53 | 0.64 | 0.74 |
| 3/4 (19.05) | 25.40 | 19.41 | 0.66 | 0.76 | 0.86 |
| 7/8 (22.23) | 29.72 | 22.63 | 0.79 | 0.89 | 0.99 |
| 1 (25.40) | 33.78 | 25.91 | 0.79 | 0.89 | 0.99 |
| 1-1/8 (28.58) | 38.10 | 29.08 | 0.79 | 0.89 | 0.99 |
| 1-1/4 (31.75) | 42.32 | 32.26 | 0.79 | 0.89 | 0.99 |
| 1-3/8 (34.93) | 46.56 | 35.31 | 0.79 | 0.89 | 0.99 |
| 1-1/2 (38.10) | 50.80 | 39.88 | 0.79 | 0.89 | 0.99 |

COMPLIES WITH: AMS-DTL-23053/11 Class 1

COLOR: Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request.

CUSTOM SPECIFICATIONS AND TOLERANCES QUOTED UPON REQUEST



WWW.ZEUSINC.COM

FEP Heat Shrink

1.6 to 1 Shrink Ratio

HEAT SHRINKABLE EXTRUSIONS



Dimensions (inches)

| Fractional | Size | | Expanded I.D. Minimum | Recovered I.D. Maximum | Wall Thickness | |
|------------|---------|--|--------------------------|---------------------------|----------------|--------|
| | Decimal | | | | Nom. | Tol. |
| 3/32 | 0.093 | | 0.093 | 0.056 | 0.008 | ±0.003 |
| 1/8 | 0.125 | | 0.125 | 0.075 | 0.010 | ±0.003 |
| 3/16 | 0.188 | | 0.188 | 0.115 | 0.010 | ±0.003 |
| 1/4 | 0.250 | | 0.250 | 0.150 | 0.010 | ±0.003 |
| 3/8 | 0.375 | | 0.375 | 0.225 | 0.012 | ±0.003 |
| 1/2 | 0.500 | | 0.500 | 0.300 | 0.015 | ±0.004 |
| 3/4 | 0.750 | | 0.750 | 0.450 | 0.020 | ±0.004 |
| 1 | 1.000 | | 1.000 | 0.600 | 0.025 | ±0.005 |
| 1-1/2 | 1.500 | | 1.500 | 0.900 | 0.030 | ±0.005 |
| 2 | 2.000 | | 2.000 | 1.200 | 0.030 | ±0.005 |

Metric Dimensions (mm)


| Fractional | Size | | Expanded I.D. Minimum | Recovered I.D. Maximum | Wall Thickness | |
|------------|-------|--|--------------------------|---------------------------|----------------|-------|
| | mm | | | | Nom. | Tol. |
| 3/32 | 2.36 | | 2.36 | 1.42 | 0.20 | ±0.08 |
| 1/8 | 3.18 | | 3.18 | 1.91 | 0.25 | ±0.08 |
| 3/16 | 4.78 | | 4.78 | 2.92 | 0.25 | ±0.08 |
| 1/4 | 6.35 | | 6.35 | 3.81 | 0.25 | ±0.08 |
| 3/8 | 9.53 | | 9.53 | 5.72 | 0.31 | ±0.08 |
| 1/2 | 12.70 | | 12.70 | 7.62 | 0.38 | ±0.10 |
| 3/4 | 19.05 | | 19.05 | 11.43 | 0.51 | ±0.10 |
| 1 | 25.40 | | 25.40 | 15.24 | 0.64 | ±0.13 |
| 1-1/2 | 38.10 | | 38.10 | 22.86 | 0.76 | ±0.13 |
| 2 | 50.80 | | 50.80 | 30.48 | 0.76 | ±0.13 |

COMPLIES WITH: AMS-DTL-I-23053/11 Class 2

COLOR: Supplied in natural unless otherwise specified. Custom Pantone colors or ZEUS standard colors available on request.

CUT PIECES: QUOTED ON REQUEST

CUSTOM SPECIFICATIONS AND TOLERANCES QUOTED UPON REQUEST



WWW.ZEUSINC.COM

FEP Roll Covers

HEAT SHRINKABLE EXTRUSIONS

ZEUS Roll Covers extend the life and reliability of rollers and improve product quality. A brief application of heat molds the cover snugly around the roll, forming a skin-tight, high-strength, impregnable jacket impervious to corrosive chemicals, solvents, acids, shock, abrasion, high temperatures, and moisture. They eliminate sticky build-up problems. With the use of a convenient heat source, such as a hot air gun, ZEUS Roll Covers can be quickly and easily shrunk onto the rolls. Cleaning can be done with a solvent or reagent.



For the printing, paper, textile, and food packaging industries, and others



- No sticking
- No picking
- Low maintenance
- Flexibility
- Excellent chemical resistance
- Handles delicate materials
- Saves labor costs
- Cuts cleaning time
- High temperature resistance

Dimensions (Inches)

Large Diameter

| Ordered As Size | To Cover Roll Dia. Min. | To Cover Roll Dia. Max. |
|-----------------|-------------------------|-------------------------|
| 1-1/4 | 1.0 | 1.3 |
| 1-1/2 | 1.4 | 1.7 |
| 2 | 1.8 | 2.1 |
| 2-1/2 | 2.2 | 2.6 |
| 3 | 2.7 | 3.1 |
| 3-1/2 | 3.2 | 3.6 |
| 4 | 3.5 | 4.2 |
| 5 | 4.4 | 5.2 |
| 6 | 5.4 | 6.2 |
| 7 | 6.4 | 7.2 |

Small Diameter

| Ordered As Size | To Cover Roll Dia. Min. | To Cover Roll Dia. Max. |
|-----------------|-------------------------|-------------------------|
| 1/2 | .440 | .550 |
| 5/8 | .540 | .700 |
| 3/4 | .640 | .800 |
| 7/8 | .760 | .950 |
| 1 | .880 | 1.100 |

Metric Dimensions (mm)

Large Diameter

| Ordered As Size | To Cover Roll Dia. Min. | To Cover Roll Dia. Max. |
|-----------------|-------------------------|-------------------------|
| 1-1/4 | 25.40 | 33.02 |
| 1-1/2 | 35.56 | 43.18 |
| 2 | 45.92 | 53.34 |
| 2-1/2 | 55.88 | 66.04 |
| 3 | 68.58 | 78.74 |
| 3-1/2 | 81.28 | 91.44 |
| 4 | 88.90 | 106.68 |
| 5 | 111.76 | 132.08 |
| 6 | 137.16 | 157.48 |
| 7 | 162.56 | 182.88 |

Small Diameter

| Ordered As Size | To Cover Roll Dia. Min. | To Cover Roll Dia. Max. |
|-----------------|-------------------------|-------------------------|
| 1/2 | 11.18 | 13.97 |
| 5/8 | 13.72 | 17.78 |
| 3/4 | 16.26 | 20.32 |
| 7/8 | 19.30 | 24.13 |
| 1 | 22.35 | 27.94 |

WALL THICKNESS: .020" (.508mm) Nominal

COLOR: Natural. Custom colors available upon request.

Complete technical information provides helpful data to speed production and cut maintenance.



WWW.ZEUSINC.COM


PTFE/FEP Dual-Shrink® Tubing

HEAT SHRINKABLE EXTRUSIONS

Heat Shrink Tubing Offering a Tight, Moisture-Resistant, Wear-Proof Encapsulation



- Outer tubing of PTFE shrinks for tight fit when heat is applied.
- Inner layer of FEP melts and flows to encapsulate parts.



ZEUS Dual-Shrink® tubing of fluoropolymer PTFE/FEP is constructed with an exterior of heat shrink PTFE and an inner layer of FEP. It is easy to apply, and is designed to provide a tight, moisture-proof bond over wires, cables, connectors, splices, terminals, etc. The PTFE shrinks tightly over inserted parts when the covered section is heated, while the FEP melts and flows into a solid or near-

solid encapsulation with a fit so tight that it can withstand the most severe stresses involving pull or vibration. ZEUS Dual-Shrink® tubing provides all the outstanding electrical, chemical, and mechanical properties of PTFE including a service temperature up to 450°F/232°C. Custom specifications and tolerances quoted upon request.



WWW.ZEUSINC.COM

PTFE/FEP Dual-Shrink® Tubing

HEAT SHRINKABLE EXTRUSIONS



Dimensions (inches)

| STANDARD WALL | | | | LIGHTWEIGHT WALL | | | |
|---------------|-----------------------|---|--|------------------|-----------------------|---|--|
| Item No. | As Supplied I.D. Min. | Recovered Dim. I.D. Will Shrink To at Least | After Shrinking Total Wall Thickness-Norm. | Item No. | As Supplied I.D. Min. | Recovered Dim. I.D. Will Shrink To at Least | After Shrinking Total Wall Thickness-Norm. |
| ZDS-S-036 | 0.036 | 0.000 | N/A | ZDS-L-065 | 0.065 | 0.000 | N/A |
| ZDS-S-060 | 0.060 | 0.000 | N/A | ZDS-L-115 | 0.115 | 0.045 | 0.015 |
| ZDS-S-130 | 0.130 | 0.000 | N/A | ZDS-L-130 | 0.130 | 0.060 | 0.015 |
| ZDS-S-160 | 0.160 | 0.000 | N/A | ZDS-L-180 | 0.180 | 0.065 | 0.015 |
| ZDS-S-190 | 0.190 | 0.062 | 0.035 | ZDS-L-190 | 0.190 | 0.070 | 0.015 |
| ZDS-S-250 | 0.250 | 0.125 | 0.035 | ZDS-L-240 | 0.240 | 0.150 | 0.020 |
| ZDS-S-350 | 0.350 | 0.190 | 0.035 | ZDS-L-350 | 0.350 | 0.210 | 0.025 |
| ZDS-S-450 | 0.450 | 0.312 | 0.055 | ZDS-L-480 | 0.480 | 0.315 | 0.032 |
| ZDS-S-700 | 0.700 | 0.440 | 0.055 | ZDS-L-700 | 0.700 | 0.500 | 0.040 |
| ZDS-S-950 | 0.950 | 0.630 | 0.065 | ZDS-L-1000 | 1.000 | 0.700 | 0.045 |

Metric Dimensions (mm)

| STANDARD WALL | | | | LIGHTWEIGHT WALL | | | |
|---------------|-----------------------|---|--|------------------|-----------------------|---|--|
| Item No. | As Supplied I.D. Min. | Recovered Dim. I.D. Will Shrink To at Least | After Shrinking Total Wall Thickness-Norm. | Item No. | As Supplied I.D. Min. | Recovered Dim. I.D. Will Shrink To at Least | After Shrinking Total Wall Thickness-Norm. |
| ZDS-S-036 | 0.91 | 0.000 | N/A | ZDS-L-065 | 1.65 | 0.000 | N/A |
| ZDS-S-060 | 1.52 | 0.000 | N/A | ZDS-L-115 | 2.92 | 1.14 | 0.38 |
| ZDS-S-130 | 3.30 | 0.000 | N/A | ZDS-L-130 | 3.30 | 1.52 | 0.38 |
| ZDS-S-160 | 4.06 | 0.000 | N/A | ZDS-L-180 | 4.57 | 1.65 | 0.38 |
| ZDS-S-190 | 4.83 | 1.57 | 0.89 | ZDS-L-190 | 4.83 | 1.78 | 0.38 |
| ZDS-S-250 | 6.35 | 3.18 | 0.89 | ZDS-L-240 | 6.10 | 3.81 | 0.51 |
| ZDS-S-350 | 8.89 | 4.83 | 0.89 | ZDS-L-350 | 8.89 | 5.33 | 0.64 |
| ZDS-S-450 | 11.43 | 7.92 | 1.40 | ZDS-L-480 | 12.19 | 8.00 | 0.81 |
| ZDS-S-700 | 17.78 | 11.18 | 1.40 | ZDS-L-700 | 17.78 | 12.70 | 1.02 |
| ZDS-S-950 | 24.13 | 16.00 | 1.65 | ZDS-L-1000 | 25.40 | 17.78 | 1.14 |

PACKAGING: Standard 4ft lengths, unless otherwise specified.

Custom Pantone colors or ZEUS standard colors available on request.
Dual-Shrink Tubing is a ZEUS registered trademark.




ZEUS[®]

SPECIALTY PRODUCTS



SPECIALTY PRODUCTS





WWW.ZEUSINC.COM

PTFE Sub-Lite-Wall®


Extruded & Heat Shrinkable Tubing

All Sub-Lite-Wall® is custom ordered

EXTRUDED SIZES

Dimensions (Inches)

| EXTRUDED | | HEAT SHRINK | | |
|------------------------|-----------------------|---------------------------|----------------------------|---------------------------------|
| Inside Diameter Inches | Wall Thickness Inches | Expanded I.D. Min. Inches | Recovered I.D. Max. Inches | Recovered Wall Thickness Inches |
| 0.0020 | 0.0020 | 0.020 | 0.008 | 0.0020 |
| 0.0025 | 0.0020 | 0.025 | 0.010 | 0.0020 |
| 0.0030 | 0.0020 | 0.030 | 0.012 | 0.0020 |
| 0.0040 | 0.0020 | 0.034 | 0.015 | 0.0020 |
| 0.0050 | 0.0030 | 0.038 | 0.018 | 0.0020 |
| 0.0060 | 0.0030 | 0.046 | 0.022 | 0.0020 |
| 0.0080 | 0.0030 | 0.050 | 0.027 | 0.0020 |
| 0.0100 | 0.0030 | 0.055 | 0.032 | 0.0020 |
| 0.0130 | 0.0030 | 0.060 | 0.039 | 0.0020 |
| 0.0160 | 0.0030 | 0.076 | 0.049 | 0.0020 |
| 0.0200 | 0.0020 | 0.093 | 0.061 | 0.0020 |
| 0.0250 | 0.0020 | 0.120 | 0.072 | 0.0020 |
| 0.0320 | 0.0020 | 0.150 | 0.089 | 0.0020 |
| 0.0400 | 0.0015 | 0.191 | 0.112 | 0.0020 |
| 0.0650 | 0.0015 | 0.240 | 0.141 | 0.0025 |
| 0.0730 | 0.0015 | | | |
| 0.0840 | 0.0015 | | | |
| 0.0980 | 0.0020 | | | |
| 0.1100 | 0.0020 | | | |
| 0.1620 | 0.0025 | | | |
| 0.2040 | 0.0035 | | | |
| 0.2580 | 0.0040 | | | |
| 0.3250 | 0.0050 | | | |



Now available in Sub-Lite-Wall® configurations with wall thicknesses down to .001 on many sizes. +/- .0005" (.013mm). Tolerances available in most sizes. Call us for more details.

ZEUS SUB-LITE-WALL® Tubing is available in both regular extruded micro-miniature dimensions, and in heat shrink versions. Inside diameters, outside diameters, and wall thicknesses are uniform throughout. **The dimensions and tolerances shown here are only a guide.** You can write your own specifications with the assurance that ZEUS can meet your requirements completely in either extruded or heat shrink version.



PTFE Sub-Lite-Wall® Extruded & Heat Shrinkable Tubing

All Sub-Lite-Wall® is custom ordered

Metric Dimensions (mm)

| EXTRUDED | | HEAT SHRINK | | |
|----------------------|---------------------|-------------------------|--------------------------|-------------------------------|
| Inside Diameter (mm) | Wall Thickness (mm) | Expanded I.D. Min. (mm) | Recovered I.D. Max. (mm) | Recovered Wall Thickness (mm) |
| 0.051 | 0.051 | 0.508 | 0.203 | 0.051 |
| 0.064 | 0.051 | 0.635 | 0.254 | 0.051 |
| 0.076 | 0.051 | 0.762 | 0.305 | 0.051 |
| 0.102 | 0.051 | 0.864 | 0.381 | 0.051 |
| 0.127 | 0.076 | 0.965 | 0.457 | 0.051 |
| 0.152 | 0.076 | 1.168 | 0.559 | 0.051 |
| 0.203 | 0.076 | 1.270 | 0.686 | 0.051 |
| 0.254 | 0.076 | 1.397 | 0.813 | 0.051 |
| 0.330 | 0.076 | 1.524 | 0.991 | 0.051 |
| 0.406 | 0.076 | 1.930 | 1.245 | 0.051 |
| 0.508 | 0.051 | 2.362 | 1.549 | 0.051 |
| 0.635 | 0.051 | 3.048 | 1.829 | 0.051 |
| 0.813 | 0.051 | 3.810 | 2.261 | 0.051 |
| 1.016 | 0.038 | 4.851 | 2.845 | 0.051 |
| 1.651 | 0.038 | 6.096 | 3.581 | 0.064 |
| 1.854 | 0.038 | | | |
| 2.134 | 0.038 | | | |
| 2.489 | 0.051 | | | |
| 2.794 | 0.051 | | | |
| 4.115 | 0.064 | | | |
| 5.182 | 0.089 | | | |
| 6.553 | 0.102 | | | |
| 8.255 | 0.127 | | | |



Now available in Sub-Lite-Wall® configurations with wall thicknesses down to .001 on many sizes. +/- .0005" (.013mm.) Tolerances available in most sizes. Call us for more details.

ZEUS SUB-LITE-WALL® Tubing is available in both regular extruded micro-miniature dimensions, and in heat shrink versions. Inside diameters, outside diameters, and wall thicknesses are uniform throughout. **The dimensions and tolerances shown here are only a guide.** You can write your own specifications with the assurance that ZEUS can meet your requirements completely in either extruded or heat shrink version.



Now available in Sub-Lite-Wall® configurations with wall thicknesses down to .002 on many sizes. +/- .001" (.025mm) tolerances available in most sizes. Call us for more details.

Dimensions (Inches)


| I.D. | O.D. | Pressure Rating* |
|------|------|------------------|
| .003 | .020 | 2000 psi |
| .005 | .020 | 2000 psi |
| .010 | .020 | 2000 psi |
| .003 | .062 | 5000 psi |
| .005 | .062 | 5000 psi |
| .007 | .062 | 5000 psi |
| .010 | .062 | 5000 psi |
| .020 | .062 | 5000 psi |
| .030 | .062 | 5000 psi |
| .040 | .062 | 5000 psi |
| .055 | .062 | 5000 psi |
| .062 | .125 | 5000 psi |
| .080 | .125 | 3000 psi |

Metric Dimensions (mm)

| I.D. | O.D. | Pressure Rating* |
|-------|-------|------------------|
| .076 | .508 | 2000 psi |
| .127 | .508 | 2000 psi |
| .254 | .508 | 2000 psi |
| .076 | 1.575 | 5000 psi |
| .127 | 1.575 | 5000 psi |
| .178 | 1.575 | 5000 psi |
| .254 | 1.575 | 5000 psi |
| .508 | 1.575 | 5000 psi |
| .762 | 1.575 | 5000 psi |
| 1.016 | 1.575 | 5000 psi |
| 1.397 | 1.575 | 5000 psi |
| 1.575 | 3.175 | 5000 psi |
| 2.032 | 3.175 | 3000 psi |

The dimensions and tolerances shown here are only a guide.

* Suggested maximum safe operating pressure



WWW.ZEUSINC.COM

PEEKshrink®

Heat-Shrinkable Tubing for Challenging Environments

All PEEKshrink is Custom Ordered

FEATURES:

- Continuous service temperature 500°F/260°C
- Translucent recovery shrink temperature 572°F - 644°F (300°C - 340°C)
- Opaque recovery shrink temperature 680°F - 725°F (360°C - 385°C)
- Recovered wall range of 0.004" to 0.010"
- Custom sizes and lengths available upon request

BENEFITS:

- Excellent abrasion resistance
- Extends life of the protected item
- Adhesion to metals
- Available in colors

SAMPLE APPLICATIONS:

- Electrical component covering
- Protective jacketing
- Wire Splicing
- Reusable medical devices

TYPICAL APPLICATIONS:

- Zeus will assist in developing custom heatshrink processes
- Class VI approved materials

| PEEKshrink® 1.4:1 Heat Shrinkable AWG Tubing | | | | | | |
|--|---------------------|---------------------------------|--|---------|---------|---------|
| Zeus P/N | Ordered as AWG Size | As Supplied Inside Diameter Min | Recovered Dimension After Shrinking Wall Thickness | | | |
| | | | Recovered ID Max | Minimum | Nominal | Maximum |
| 85322 | 17 | 0.038 | 0.027 | 0.005 | 0.007 | 0.009 |
| 85318 | 16 | 0.045 | 0.032 | 0.005 | 0.007 | 0.009 |
| 85184 | 15 | 0.055 | 0.039 | 0.005 | 0.007 | 0.009 |
| 85204 | 14 | 0.085 | 0.060 | 0.005 | 0.007 | 0.009 |
| 85197 | 13 | 0.092 | 0.065 | 0.005 | 0.007 | 0.009 |
| 85189 | 12 | 0.101 | 0.072 | 0.005 | 0.007 | 0.009 |
| 85313 | 11 | 0.112 | 0.080 | 0.005 | 0.007 | 0.009 |
| 85310 | 10 | 0.125 | 0.089 | 0.005 | 0.007 | 0.009 |
| 85298 | 9 | 0.137 | 0.098 | 0.005 | 0.007 | 0.009 |
| 85294 | 8 | 0.160 | 0.114 | 0.005 | 0.007 | 0.009 |
| 85146 | 7 | 0.174 | 0.124 | 0.005 | 0.007 | 0.009 |
| 85063 | 6 | 0.200 | 0.143 | 0.005 | 0.007 | 0.009 |
| 85213 | 5 | 0.221 | 0.158 | 0.005 | 0.007 | 0.009 |
| 85236 | 4 | 0.252 | 0.180 | 0.005 | 0.007 | 0.009 |
| 85243 | 3 | 0.277 | 0.198 | 0.005 | 0.007 | 0.009 |
| 85246 | 2 | 0.316 | 0.226 | 0.005 | 0.007 | 0.009 |
| 85255 | 1 | 0.349 | 0.249 | 0.005 | 0.007 | 0.009 |
| 85326 | 0 | 0.392 | 0.280 | 0.005 | 0.007 | 0.009 |

Standard Put Up: 4FtLgth

PEEKshrink® Tubing Properties

| Properties | ASTM | Units | |
|-------------------------|--------------|-------|---------|
| Tensile Modulus | D638 | KSI | 1,309 |
| Tensile Stress at Yield | D638 | PSI | 14,503 |
| Glass Transition Temp | D3418 | °F/°C | 321/161 |
| Dielectric Strength | D149 | V/mil | 3570 |
| Thermal Endurance | NEMA MW 1000 | °F/°C | 752/400 |
| Crystallinity | D3814 | % | 40 |

This data is based on PEEKshrink® recovered on a .575" mandrel. Tubing performance and characteristics may change based on tubing size.



PEEK™ Insulated Wire

Insulated Copper Wire for Challenging Environments

EXTRUDED SIZES

Feature/Capabilities:

- 100% AC spark tested during extrusion
- Round, square & rectangular profiles available
- Various types of wire available, including silver and nickel plated wire as well as custom wire types

Key Properties:

- High continuous operating temperature 500°F/260°C
- Outstanding abrasion resistance
- Excellent dielectric strength
- Exceptional chemical resistance
- Protects against corrosion

| SIZE (AWG) | NOMINAL BARE COPPER DIAMETER (INCHES) | NOMINAL BARE COPPER DIAMETER (MM) |
|------------|---------------------------------------|-----------------------------------|
| 4 | 0.2043 | 5.189 |
| 5 | 0.1819 | 4.620 |
| 6 | 0.1620 | 4.115 |
| 7 | 0.1443 | 3.665 |
| 8 | 0.1285 | 3.264 |
| 9 | 0.1144 | 2.906 |
| 10 | 0.1019 | 2.588 |
| 11 | 0.0907 | 2.304 |
| 12 | 0.0808 | 2.052 |
| 13 | 0.0720 | 1.829 |
| 14 | 0.0641 | 1.628 |
| 15 | 0.0571 | 1.450 |
| 16 | 0.0508 | 1.290 |
| 17 | 0.0453 | 1.151 |
| 18 | 0.0403 | 1.024 |

| SIZE (AWG) | NOMINAL BARE COPPER DIAMETER (INCHES) | NOMINAL BARE COPPER DIAMETER (MM) |
|------------|---------------------------------------|-----------------------------------|
| 19 | 0.0359 | 0.912 |
| 20 | 0.0320 | 0.813 |
| 21 | 0.0285 | 0.724 |
| 22 | 0.0253 | 0.643 |
| 23 | 0.0226 | 0.574 |
| 24 | 0.0201 | 0.511 |
| 25 | 0.0179 | 0.455 |
| 26 | 0.0159 | 0.404 |
| 27 | 0.0142 | 0.361 |
| 28 | 0.0126 | 0.320 |
| 29 | 0.0113 | 0.287 |
| 30 | 0.0100 | 0.254 |
| 31 | 0.0089 | 0.226 |
| 32 | 0.0080 | 0.203 |

*All PEEK Insulated Wire is custom ordered. Wall thicknesses available from 0.001" - 0.026" (0.025mm - 0.660mm) depending on the conductor size.

| ASTM PEEK Insulated Wire Testing | | | |
|----------------------------------|------|-----------------------|--------------------|
| PROPERTIES | ASTM | UNITS | NOMINAL TEST VALUE |
| Resistivity Testing | B3 | Ωlb/mile ² | 859 |
| Dielectric Breakdown | D149 | kV RMS, at 60Hz | 25 |
| Relative Permittivity | D150 | | 2.72 |
| Dissipation Factor | D150 | % | 0.14% |
| DC Resistance | D257 | TΩin | 2.72 |

*AWG 8 with 0.008" (0.203mm) wall. Insulation thickness tested according to ASTM D374. Performance and characteristics may change based on size.

| NEMA PEEK INSULATED WIRE TESTING | | | |
|---|--|-------------------|-----------|
| NEMA MW 1000 Test Section | Requirements (AWG 18 Heavy Build)* | Results | Pass/Fail |
| 3.3 Adherence & Flexibility | No cracks visible in film coating | No cracks visible | Pass |
| 3.5 Heat Shock | No cracks visible in film coating at 280°C | No cracks visible | Pass |
| 3.8 Dielectric Breakdown - Twisted Pair | | | |
| ➤ 260°C | Minimum 5,700 VAC | 11,650 VAC | Pass |
| ➤ Room Temperature | Minimum 5,700 VAC | 12,200 VAC | Pass |
| 3.9 Continuity | Shall not exceed 10 faults | 0 Faults | Pass |

*There are no NEMA requirement values for PEEK Insulated Wire. These requirements are based off the highest temperature rated MW-16C (240°C) from the NEMA MW 1000 standard. Performance and characteristics may change based on size.

*AWG 18 with 0.0015" (0.0381mm) wall



WWW.ZEUSINC.COM

Special Shapes

All Special Shapes are custom ordered


SPECIALTY PRODUCTS



Multi-Lumens: Unique extrusions providing multiple lumens or passages. All multi-lumens are custom designed in different resins including but not limited to: PTFE, ePTFE, FEP, PFA, PEEK™ and more. Design configurations are unlimited and are specific to your needs with all aspects kept confidentially to each customer.

A Multitude Of Multi-Lumen Advantages

- Highly flexible
- Impervious to most corrosives
- Inert • Non-toxic
- Heat resistant to 500°F.
- Superior lubricity
- Biocompatible
- Reliable fluid transfer
- High dielectric strength





Performance Fiber

EXTRUDED SIZES

ZEUS offers an arsenal of fibers designed to perform in diverse and demanding applications. Properties such as high tensile strength, optical clarity, and extreme chemical and temperature resistance define Zeus fiber. These lightweight monofilaments also have superior friction and wear properties, and are ideal for use in abrasive environments. Our standard product offering ranges in size from .003" - .040" and includes fibers made from PEEK, PFA, FEP, ETFE, PVDF and ECTFE. Other resins and customized products are available upon request.

Capitalizing on more than 45+ years of polymer experience, ZEUS continues to provide superior products with the highest standards of quality and control. Whether it's braided for a wiring harness, woven for a filter, or chopped for composites, ZEUS fibers excel in the most demanding environments and applications.

PEEK FIBER

High tensile strength
Abrasion resistant
Lightweight material

FEP FIBER

Very robust
Luminous transmittance of 96%
Excellent lubricity

ECTFE (Halar) Fiber

Impact and temperature resistant
Superior surface smoothness
Excellent value

PFA FIBER

Superior purity
Chemical resistant
Long service life

ETFE (Tefzel) Fiber

Superior mechanical toughness
Chemical inertness
Radiation resistant

PVDF Fiber

UV stability
Mechanically tough
Abrasion resistant

PEEK FIBER SPECIFICATIONS (Natural or Black)

| Specification | 0.010" Diameter | 0.011" Diameter | 0.016" Diameter | Units |
|----------------------------|-----------------|-----------------|-----------------|--------|
| Min OD | 0.0085 | 0.0095 | 0.0145 | inches |
| Max OD | 0.0115 | 0.0125 | 0.0175 | inches |
| Avg OD - 3 STD DEV | 0.0085 | 0.0095 | 0.0145 | inches |
| Avg OD + 3 STD DEV | 0.0115 | 0.0125 | 0.0145 | inches |
| Min Tensile Strength | 4 | 5.5 | 11 | lbs |
| Min Tenacity | 3 | 3.6 | 3.7 | GPD |
| Min Rel Elongation @ 2 GPD | 4 | 5 | 5 | % |
| Max Rel Elongation @ 2 GPD | 9 | 10 | 11 | % |
| Min Elongation @ Break | 18 | 18 | 20 | % |
| Max Elongation @ Break | 30 | 30 | 35 | % |
| Min Shrinkage | 3 | 3 | 2 | % |
| MAX SHRINKAGE | 5 | 5 | 6 | % |

Properties based on standard Zeus PEEK Fiber. Custom colors, diameters, and properties available. Contact Zeus to discuss.



WWW.ZEUSINC.COM


Lay-Flat Tubing

SPECIALTY PRODUCTS



PET, FEP, PEEK™, PE and EVA

Dedicated to fulfilling the changes in the markets our customers serve, ZEUS is pleased to offer lay-flat tubing. Lay-flat tubing was traditionally designed to meet the needs for ultra-thin walls in the lighting and roller industries but now has applications in many medical and industrial markets. Lay-flat tubing made of high quality polymers offer strength, lubricity, chemical inertness and biocompatibility.



Color: Natural. Custom colors available upon request.
Contact a Tech. Acct Manager for details.

PET, FEP, PEEK™ and PE


- Wall Sizes: .004" to .008"
- ID Ranges: .250" to 3.180"
- Lay Flat Widths: .400" to 5.000"
- H/S: Expansion ratios up to 2:1 when applicable
- Put Up: Spooled or cut to length

ZEUS specializes in made-to-order sizes designed for your unique application.





ZEUS Dual Tube® is a superior, easy handling fluoropolymer tubing typically used for water monitoring and other applications. It is produced as a single unit of two independent tubes of similar or variable sizes that stay together until separation is required. Once separated the surface of each tube is smooth and contains no flaws, flat spots, ridges, or other defects that can interfere with sealing.



ZEUS Dual Tube® is supplied in smooth tangle-free, easy-to-handle, extra long lengths that are tough, durable and chemically inert so that sample properties cannot be affected. Long-term exposure to contaminants cannot impair performance, and it is simple to clean and reuse. Samples obtained remain pure and free of mineral and organic sediments. ZEUS Dual Tubes can be manufactured from PTFE, FEP,

Polyethylene and other resins in a variety of configurations.

- Makes monitoring accurate & effective
- Insures consistent sampling results
- Superior reliability
- Non-contaminating
- Protects integrity of sample & well water

ZEUS also has a complete line of **FEP-Lined Polyethylene** (and other resins) tubing developed specifically for the high purity requirements of the environmental monitoring industries. Contact one of our Technical Representatives for more details on this unique product and how it can be beneficial to your application.



Measurements (inches)

| | | |
|-------------------|-----|-------------------|
| 1/2" OD x 3/8" ID | and | 1/2" OD x 3/8" ID |
| 3/8" OD x 1/4" ID | and | 1/4" OD x 1/8" ID |
| 1/4" OD x 1/8" ID | and | 1/4" OD x 1/8" ID |
| 1/2" OD x 3/8" ID | and | 3/8" OD x 1/4" ID |
| 1/2" OD x 3/8" ID | and | 1/4" OD x 1/8" ID |
| 3/8" OD x 1/4" ID | and | 3/8" OD x 1/4" ID |

Metric Measurements (mm)

| | | |
|--------------------|-----|--------------------|
| 12.70 OD x 9.53 ID | and | 12.70 OD x 9.53 ID |
| 9.53 OD x 6.35 ID | and | 6.35 OD x 3.18 ID |
| 6.35 OD x 3.18 ID | and | 6.35 OD x 3.18 ID |
| 12.70 OD x 9.53 ID | and | 9.53 OD x 6.35 ID |
| 12.70 OD x 9.53 ID | and | 6.35 OD x 3.18 ID |
| 9.53 OD x 6.35 ID | and | 9.53 OD x 6.35 ID |

Supplied in a variety of ODs and IDs
Other custom sizes and combinations quoted on request



WWW.ZEUSINC.COM

Splines

Wires, Cables, Coaxial Cores

Snaptube®

SPECIALTY PRODUCT



Splines

ZEUS can provide custom splined extrusions over wire for the coaxial cable manufacturer. With tight tolerances, custom lengths and unique wire cores. All extrusions are done to customer specifications.

Wire, Cables, Coaxial Cores

These extrusions are special and unique because of tolerances, concentricity, finish, lengths and many other considerations. New and unexplored avenues of applications become a reality due to the unmatched capabilities of Zeus' extrusion processes.



- Withstands continuous temperatures to 500°F with PTFE
- Outstanding concentricity
- Shockproof
- Abrasion proof
- Moisture proof



Snaptube® Restores Damaged Conductors

Dimensions (inches)

| Item No. | Nominal I.D. | Nominal Wall Thickness | Recommended Bundle Dia. Max. |
|------------|--------------|------------------------|------------------------------|
| ZST-I-250 | 1/4 | .030 | .200 |
| ZST-I-437 | 7/16 | .030 | .400 |
| ZST-I-562 | 9/16 | .030 | .500 |
| ZST-I-625 | 5/8 | .035 | .600 |
| ZST-I-812 | 1 3/16 | .035 | .750 |
| ZST-I-1000 | 1 | .040 | .975 |
| ZST-I-1375 | 1 3/8 | .045 | 1.350 |

Metric Dimensions (mm)


| Item No. | Nominal I.D. | Nominal Wall Thickness | Recommended Bundle Dia. Max. |
|------------|--------------|------------------------|------------------------------|
| ZST-I-250 | 6.35 | .76 | 5.08 |
| ZST-I-437 | 11.11 | .76 | 10.16 |
| ZST-I-562 | 14.29 | .76 | 12.70 |
| ZST-I-625 | 15.88 | .89 | 15.24 |
| ZST-I-812 | 20.64 | .89 | 19.05 |
| ZST-I-1000 | 25.40 | 1.02 | 24.77 |
| ZST-I-1375 | 34.93 | 1.14 | 34.29 |

Standard Lengths: 5-foot and 10-foot

Custom Sizes: Other lengths, and smaller or larger diameters quoted on request.

Colors: Natural. Other colors are available per MIL-STD-104 and quoted upon request.

SNAPTUBE® is a registered trademark of ZEUS Industrial Products, Inc.





WWW.ZEUSINC.COM

Absorv™ Bioabsorbable Polymers

SPECIALTY PRODUCTS



Zeus is able to process bioabsorbable polymers into virtually any form including tubes, monofilament, sheets, and microporous non-wovens. We are able to extrude bioabsorbable resins into high precision tubular geometries and perform full polymer characterization, providing necessary data to meet regulatory requirements.

Capabilities include tight tolerance extrusion, unique formulations, customization, sophisticated materials science, and tailored degradation profiles. Zeus is able to assist customers with material selection and testing, as well as evaluate possible processing and product forms that are not currently part of its standard offering.

Key Properties

- Modulated degradation rates
- Varying strengths and hardness
- Multiple extrusion forms
- FDA-approved for medical devices
- Tailored to customers' specifications

Zeus Capabilities

- Tight tolerance extrusion
- Sophisticated materials science
- Advanced processing and development
- Multiple combinations of the product

| Material | Tg (C) | Tm (C) | E (Gpa) | σ (MPa) | Mass Loss (months)* |
|------------------|--------|-----------|-------------|---------|---------------------|
| PLLA | 60 | 180 - 190 | 3.0 - 4.0 | 65 | 18 - 36 |
| PGA | 40 | 215 - 225 | 6.0 - 7.0 | 95 | 4 - 6 |
| PDLLA | 55 | amorph | 1.0 - 3.0 | 40 | 12 - 16 |
| PCL | -60 | 55 - 65 | 0.2 - 0.4 | 25 | 24 - 36 |
| PLGA (85L/15G) | 55 | 140 - 150 | 2.0 - 4.0 | 65 | 12 - 18 |
| PLGA (82L/18G) | 50 | 135 - 145 | 2.0 - 4.0 | 60 | 12 - 16 |
| PLGA (10L/90G) | 42 | 202 - 210 | 3.0 - 6.0 | 45 | 3 - 4 |
| PDLGA (50DL/50G) | 45 | amorph | 2.0 - 4.0 | 45 | 1 - 2 |
| PLDLA (80L/20DL) | 60 | 115 - 130 | 2.0 - 4.0 | 50 | 12 - 18 |
| PLC (70L/30C) | 20 | 105 - 115 | 0.02 - 0.04 | 3 | 12 - 24 |

*Approximate values for a small selection of absorbable materials processed by Zeus



WWW.ZEUSINC.COM

Aeos® ePTFE Tubing and Monofilament

SPECIALTY PRODUCTS



ePTFE tubing from ZEUS is made by expanding PTFE tubing, under controlled conditions, during the manufacturing process. This process alters the physical properties of the tubing by creating microscopic pores in the structure of the material. The resulting tubing is imparted with unique physical properties that make it ideal for use in medical devices, electronic insulators, high performance filters, and a host of other applications.



- Excellent radial expansion
- Excellent UV resistance
- Certified USP Class VI resin
- Low coefficient of friction
- Watertight (low pressure)
- Hydrophobic/hydrophilic

ZEUS ePTFE Capabilities

Through extensive investments in R&D, ZEUS has developed a wide range of ePTFE processing capabilities. This broad control over the manufacturing process allows ZEUS to manipulate the physical and mechanical properties of the material. The dimensions of the tubing, as well as the IND and porosity ranges, can be designed to match your proprietary specifications.

Key Properties

ePTFE differs from regular PTFE tubing in that the material is microporous, soft, very flexible, has a lower dielectric constant, increased linear strength, and improved biocompatibility.

- Microporous
- Air permeable
- Soft and flexible
- Biocompatible
- Chemically resistant
- High linear strength
- Chemically inert
- Low dielectric constant



- Tubing:
OD range = <1.5"
ID range = >0.005"
- Monofilament
OD = >0.003"
- IND Range: 1μ-200μ+
- ePTFE Multi-Lumen
- Variable porosity
- Long continuous lengths available
- ePTFE over wire
- Custom material properties
- Chemical impregnation
- Custom colors





WWW.ZEUSINC.COM

Aeos® ePTFE Tubing and Monofilament

SPECIALTY PRODUCTS



ZEUS Support

For over 45+ years, ZEUS has assisted medical device engineers in bringing their concepts and ideas to reality. Today, we work closely with numerous manufacturers to confidentially assist them in the development of new products and technology.


- Test reports
- Technical sales staff
- SEM analysis
- R&D engineering support
- Special certs
- Custom packaging
- Product development
- Medical grade inspection
- Confidential support
- Porosity/filtration testing



cellular ingrowth. ePTFE is well known in medical research papers for its endothelialization and thrombogenic properties. PTFE resin has long been utilized for implantable medical devices due to its biocompatibility and proven track record. ZEUS has performed independent testing and holds USP Class VI certification for our PTFE resins.

Internodal Distance (IND)

The amount of expansion in ePTFE is typically referred to as internodal distance (IND). IND is a measure of the average distance between the material's nodes.



ZEUS is experienced in manufacturing ePTFE with IND sizes ranging from 1μ to over 200μ.

Biocompatibility

The structure of ePTFE is unique in that the material is made up of a number of solid nodes inter-connected by a matrix of thin fibrils. The spacing between the nodes (IND) is what allows the material to excel in applications requiring





ZEUS[®]

VALUE ADDED SERVICES



VALUE
ADDED
SERVICES





WWW.ZEUSINC.COM

Value Added Services

VALUE ADDED SERVICES

The Benefits of ZEUS Value Added Services and Operations

In response to requests from our customers and our inherent knowledge of our product, ZEUS has developed extensive experience in performing a variety of secondary operations and valued added services that allow you to focus on your



core processes. By having ZEUS perform secondary or value added operations, our customers have recognized increased economies of scale, improved yields, and increased manufacturing efficiencies.

Our Value Added operations for our customers have proven to:

- Provide solutions for customers who cannot perform secondary applications in-house
- Reduce labor costs and time
- Improve efficiency
- Reduce material cost (economies of scale)
- Reduce scrap and waste
- Reduce capital expenditure
- Laser-Marking, Pad-Printing, Drawn Fibers

- Reduce need for prototyping because of our high familiarity with tubing
- Increase yields
- Increase gross profits
- Reduce lead time to end user
- Reduce overhead costs

Bump/Draw-down

Utilizing various manufacturing and secondary processes, ZEUS has developed the technology to vary the ID and OD of tubing along the length of the extrusion. Often referred to as "Bump Tubing", "Draw-downs", or "Bubble Tubing", this technology allows for unique design solutions. Some applications for this technology utilize the variability in dimensions for the attachment of fittings and parts as well as adjustments in flexibility.



- Tight tolerances
- Available in thermoplastics and PTFE
- Variable transition lengths
- ID or OD may be modified



WWW.ZEUSINC.COM

Value Added Services

VALUE ADDED SERVICES

Custom Cutting

- Tight tolerances available
- Ability to control ovality
- In-line cutting
- Clean, crisp cuts
- Angle cuts on one/both ends available

Custom Packaging & Labeling

- ZEUS has ability to print labels and bar codes to customer's specifications.
- Ability to package and apply label/bar code using customer supplied materials which reduces/eliminates customers need to repackage
- Blank-package materials for distributors
- Custom packaging to customers specifications available




Drilling

- Custom, clean and burr-free holes
- Single and multiple hole configurations available
- High-speed automation capability



Etching

- Improves the bondability of tubing without effecting mechanical properties
- Can be done over the length of the tube or for specific lengths on the end
- Extrusions can be etched on the ID, OD or tip
- Additional details available in the Technical Information section



Applications include:


- Insulator for fiber optic cable
- Roller covers
- Medical devices
- Anywhere bonding is required

Flaring & Flanging

Flaring and flanging is often used to facilitate the attachment of tubing to fittings or to allow for ease of insertion of items into the inside of the tube.



ZEUS' expertise in manufacturing fluoropolymer tubing has lead to the development of unique capabilities for flaring and flanging tubing. Through an investment in R&D and Engineering, ZEUS has developed automated flaring lines and



WWW.ZEUSINC.COM

Value Added Services

VALUE ADDED SERVICES

special tooling that allows us unsurpassed flaring and flanging capabilities.

Experience, equipment, and capacity are the reason many of our customers have chosen to outsource their secondary operations to ZEUS. Additionally, ZEUS has developed a wide range of tooling parts required to produce many common flare angles and sizes reducing your lead times and costs.



Heat Sealing

In applications such as fluid storage, the ends of a polymer tube often need to be sealed closed. Similar to the process used to seal the end of a toothpaste tube, ZEUS can thermoplastically weld closed the end of thin wall lay-flat tubing.

The end of thicker walled tubing can also be heat sealed together in a process known as tipping.

Heat Shrinking over Mandrels

Our experience at manufacturing precision fluoropolymer heat shrink affords us the unique ability to perform efficient heat shrinking over customer-supplied mandrels. Rather than developing a manufacturing process to achieve the ideal balance of oven time and



temperature many customers have chosen to have ZEUS perform these operations for them. Our heat shrinking processes and equipment allow us to quickly and efficiently shrink tubing over our customer's parts reducing their equipment and labor costs while decreasing their development costs and production time.

Product Analysis & Enhancement

At ZEUS we're committed to helping make our products work in your application. Our customers are continually challenging us to push the properties and tolerances of our products further. To support this challenge ZEUS has assembled an exceptional team of engineers, technicians and polymer experts.



These experts have successfully customized a wide range of polymers for industry applications ranging from cutting-edge medical devices to state of the art electronics applications.

Through a scientific process of resin selection, process modification and resin additives, ZEUS can adjust the ways that a polymer will perform in your application. Common modifications range from the addition of fillers to improve the radiopacity of a polymer to the addition of carbon for static conductivity.



WWW.ZEUSINC.COM

Value Added Services

VALUE ADDED SERVICES

Advanced modifications might include challenges such as increasing the tensile and mechanical properties of a polymer. These challenges are supported by a team of the most experienced polymer experts in the industry, an advanced analytical lab, and a dedicated R&D facility.

Product Assembly - High Volume

As a world leader in fluoropolymer extrusion, ZEUS is the perfect partner to outsource your high-volume parts assembly. Top manufacturers in industries such as automotive and medical devices trust ZEUS to supply them with high volume tubing based subcomponents.

In addition to world-class extrusion capability, ZEUS has developed world-class machining and fabrication capabilities housed in a dedicated facility. Combined with our experienced engineering department ZEUS has successfully automated time consuming parts assembly.

Our capabilities allow us to reduce your overall costs and help speed your product to market. ZEUS has been delivering pre-packaged sub-components to leading manufacturers and is in an ideal position to offer these services to you.

Product Assembly - Light

Our tubing is used in many advanced products ranging from minimally invasive medical devices to high-performance audio cables and automotive sub-components.


As experts in the manufacturing and modification of the tubular products we offer, many companies have turned to ZEUS to supply various tubing-based sub-components. ZEUS has met this request with our light-product assembly value added services.

Retractable Coil Tubing

ZEUS is pleased to offer a wide range of custom fluoropolymer coiled tubing. Resins such as FEP and PFA. These plastics are known for their excellent chemical resistance, non-stick surfaces, as well as a number of other high-performance properties.



Through a proprietary manufacturing process, ZEUS "heat sets" fluoropolymer tubing into a helical coil that allow for a high degree of flexibility and retractability. This heat setting process fuses the tubing into the helical formation and allows the material to stretch and retract to its programmed position. Custom sizes, coils, and colors can all be manufactured to meet the requirements of your application.



WWW.ZEUSINC.COM

Value Added Services

VALUE ADDED SERVICES

Scoring

- Partial slit of a tube's wall running axially along the length
- Facilitates removal of tubing from a device
- Facilitates removal of tubing when used as a manufacturing tool

Slitting

(Longitudinal cut that goes through the entire wall of the tube along its axial length)

- Allows a tube to be slipped over other components and easily removed (easily installed)
- Spiral slitting also available

Striping

(Straight and spiraled axial stripes along the length of a tube)

- Radio opaque stripes available
- Helps identify a tube in a bundle
- Custom widths available
- Able to match custom colors

Thermosetting/Forming

- Use heat to set a tube into a certain shape



Tube Tipping


Tipping the end of a plastic tube is one of the secondary services we perform for our customers. Tipping involves forming a radius or chamfering the end of the tube to facilitate the assembly of parts.



Through an extensive investment in our secondary services and capabilities, ZEUS engineers have developed a broad portfolio of tipping capabilities. Thermoforming technology can be used to radius the tip in a variety of customer-specified designs. Specialty grinding can be used in applications where thermoforming may not be an option.

From pronounced tips to a slight easing of the tube's edges ZEUS can perform a range of tipping operations. Over the years we have explored a broad portfolio of tipping configurations ranging from decreasing the ID of the tube as the tip profile changes to a complete closure of the end of the tube at the tip.






WWW.ZEUSINC.COM

Value Added Services

VALUE ADDED SERVICES



PTFE Slitting and Cuffing

Longitudinal slit convoluted tubing as well as cuffed PTFE convoluted tubing are available upon request. Slitting convoluted tubing allows pre-existing wires to be conveniently slipped into the tubing. Cuffing of ZEUS PTFE convoluted tubing provides the ideal smooth surface to attach mechanical connectors and fittings.

Capabilities include:

- Cuff one or both ends of tubing
- Cuff to specific custom lengths



ZEUS[®]

TECHNICAL INFORMATION



TECHNICAL INFORMATION





WWW.ZEUSINC.COM

Technical Information

Table of Contents

TECHNICAL INFORMATION

Resin Properties 62

| | |
|--|----|
| PTFE - Polytetrafluoroethylene | 62 |
| FEP - Fluorinated ethylene propylene | 63 |
| PFA/MFA - Perfluoroalkoxy | 64 |
| PVDF - Polyvinylidene fluoride | 65 |
| THV - Tetrafluoroethylene hexafluoropropylene vinylidene fluoride | 66 |
| ETFE - Ethylene tetrafluoroethylene | 67 |
| PEEK™ - Polyether ether ketone | 68 |
| PET - Polyethylene Terephthalate Polyester | 69 |
| Nylons | 70 |
| PE - Polyethylene | 71 |

General Information 72

| | |
|---|----|
| Colors | 72 |
| Shelf Life and Storage Requirements | 73 |
| Test Reports/Services | 73 |
| Traceability | 73 |
| Visual Appearance | 74 |

Technical Notes 75

| | |
|---|----|
| Tubing Bend Radius | 75 |
| Biocompatibility and Certified USP Class VI Approved Zeus Medical Grade Products | 75 |
| Burst Pressure | 76 |
| Chemical Compatibility | 76 |
| Concentricity Formula | 76 |
| Etching - Technical Questions | 77 |
| Fillers Used in Fluoropolymer Tubing | 78 |
| Glass | 78 |
| BISMUTH and TUNGSTEN | 78 |
| Barium | 78 |
| Low Temperature Rating | 79 |
| Lubricity | 79 |
| Permeability | 79 |
| Sterilization Methods | 80 |
| UV Compatibility | 80 |



WWW.ZEUSINC.COM

Resin Properties

PTFE - Polytetrafluoroethylene


TECHNICAL INFORMATION

Background

- Originally discovered in the 1930's by DuPont scientist Dr. Roy Plunkett, PTFE was first used in the top secret Manhattan project during WWII. DuPont commercialized PTFE under the tradename Teflon in the late 1940's. Extrudable grades of PTFE were commercialized later and in 1966 ZEUS was founded and began development of advanced manufacturing processes for PTFE.

- As a recognized foundational pioneer of the PTFE tubing market, ZEUS has developed a high performance manufacturing process that allows us to produce a broad range of products for a sizable array of markets and applications

- The unique properties of PTFE has made it the polymer for first choice for many advanced applications. With the lowest coefficient of friction of any polymer and an extremely broad working temperature range, PTFE has been designed into products from advanced medical devices to high temperature industrial equipment. Because of its unparalleled chemical resistance inertness, PTFE has become a choice plastic for the chemical and analytical sciences industries.



Key Properties

- Lowest coefficient of friction of any polymer
- Chemical resistance (all common solvents, acids and bases) and inertness
- ETO and autoclave sterilizability
- Working temperature range -454°F (-270°C) to 500°F (260°C)



Additional Properties

- Excellent dielectric insulating properties
- Biocompatibility- certified USP Class VI
- Flame rating- UL 94 VO
- Limiting oxygen index- greater than 95

ZEUS Capabilities

- Etching capability for bonding
- Fillers available for material modification
 - Radio opaque
 - Carbon
 - Pigments
 - Glass
- Ultra-tight tolerance extrusions
- Extruded forms
 - Tubing
 - Special Profiles
 - Heat shrink
 - Monofilament
 - Multi-lumen



WWW.ZEUSINC.COM

Resin Properties

FEP - Fluorinated ethylene propylene

TECHNICAL INFORMATION

Background

- The development of PTFE was a significant breakthrough in polymer sciences. The special processing requirements of PTFE led researchers to develop a melt-processable version of PTFE resulting in FEP. This new resin was compatible with existing processing methods and equipment. Melt processability also allowed for long continuous extrusions of FEP in applications such as wire and cable.



Key Properties

- Excellent coefficient of friction
- Chemically resistant and inertness
- Gamma, ETO and autoclave sterilizable
- Maximum working temperature 400°F (204°C)
- Excellent transmission of UV rays
- Lower gas and vapor permeability than PTFE
- Low absorption of solvents (less than 1%)

Additional Properties

- Radiation Resistance
- Excellent dielectric insulating properties
- Melt weldability and thermoformability
- Biocompatibility- Certified USP Class VI
- Environmental stability
- Flame rating- UL 94 VO
- Limiting oxygen index- greater than 95

ZEUS Capabilities

- Etching available for bonding
- Fillers available for material modification
 - Radio opaque
 - Carbon
 - UV inhibitors
 - Pigments
- Tight tolerance extrusions
- Extruded forms
 - Tubing
 - Lay-flat tubing
 - Special profiles
 - Heat shrink
 - Monofilament
 - Multi-lumen





WWW.ZEUSINC.COM

Resin Properties

PFA/MFA - Perfluoroalkoxy


TECHNICAL INFORMATION

Background

- PFA was developed to increase the continuous service temperature of FEP resin. Melt processability allows PFA to be processed in longer continuous lengths than PTFE.

Key Properties

- Excellent coefficient of friction
- Chemical resistance to all common solvents and chemical inertness
- Gamma, ETO, e-beam and autoclave sterilizability
- Maximum working temperature 500°F (260°C)
- Low gas permeability
- Maintains a mechanical temperatures
- Available in high purity grades
- Excellent clarity and flexibility
- Combines attributes of PTFE and FEP



Additional Properties

- Melt weldability and thermoformability
- Flame rating- UL 94 VO
- Ultra-low levels of ionic extractables

ZEUS Capabilities

- Etching capability for bonding
- Fillers available for material modification
 - Radio opaque
 - Carbon
 - Pigments
- Tight tolerance extrusions
- Extruded forms
 - Tubing
 - Lay-flat tubing
 - Special profiles
 - Heat shrink
 - Monofilament
 - Multi-lumen





WWW.ZEUSINC.COM

Resin Properties

PVDF - Polyvinylidene fluoride

TECHNICAL INFORMATION

Background

- PVDF was designed primarily for application requiring excellent chemical resistance, high levels of purity and superior mechanical properties. PVDF is often used as a lining or protective barrier in chemical applications.



Key Properties

- Good coefficient of friction
- Chemical resistance (all common solvents, acids and bases) and inertness
- Gamma, ETO, e-beam and autoclave sterilizability
- Maximum service temperature 130° C
- Excellent resistance to creep and fatigue
- Superior tensile properties and impact strengths
- Excellent mechanical properties over a broad temperature range
- Excellent resistance to cut-through

Additional Properties

- Radiation Resistance
- High dielectric strength over a wide temperature range
- Melt weldability and thermoformability
- Biocompatibility- Certified USP Class VI
- Environmental stability
- Flame rating- UL 94 VO
- Limiting oxygen index- greater than 95

ZEUS Capabilities

- Etching capability for bonding
- Fillers available for material modification
 - Radio opaque
 - Carbon
 - Pigments
- Tight tolerance extrusions
- Extruded forms
 - Tubing
 - Lay-flat tubing
 - Monofilament
 - Multi-lumen






WWW.ZEUSINC.COM

Resin Properties

THV - Tetrafluoroethylene hexafluoropropylene vinylidene fluoride

Background

- THV resin is a terpolymer of tetrafluoroethylene, hexafluoropropylene and vinylidene fluoride. THV is the most flexible fluoropolymer available and has the highest degree of optical clarity. Combined with the traditional chemical and environmental resistance of fluoropolymers, THV is an ideal choice for many applications.




Additional Properties

- Melt weldability and thermoformability
- High limiting oxygen index- does not support combustion

ZEUS Capabilities

- Tight tolerance extrusions
- Extruded forms
 - Tubing
 - Lay-flat tubing
 - Monofilament
 - Multi-lumen



Key Properties

- Good coefficient of friction
- Chemical resistance (all common solvents, acids and bases) and inertness
- Maximum service temperature 150° C
- Exceptional optical clarity
- Good UV transmittance



WWW.ZEUSINC.COM


Resin Properties

ETFE - Ethylenetetrafluoroethylene

TECHNICAL INFORMATION

Background

- ETFE is used in applications requiring excellent impact resistance and good resistance to stress cracking. The resin maintains these properties up to its continuous working temperature of 300°F (149°C). ETFE is the resin of choice for applications requiring a fluoropolymer with superior mechanical properties.



Key Properties

- Chemical resistance and inertness
- Gamma, ETO, e-beam and autoclave sterilizability
- Excellent impact resistance
- Increased durability and stiffness over other fluoropolymers
- Higher pressure rating than other fluoropolymers
- Higher tensile strength and creep resistance than other fluoropolymers
- Greater crush resistance than other fluoropolymers

Additional Properties

- Radiation Resistance
- Melt weldability and thermoformability
- Flame rating- UL 94 VO
- Limiting oxygen index- 30

ZEUS Capabilities

- Etching capability for bonding
- Fillers available for material modification
 - Radio opaque
 - Carbon
 - Pigments
- Tight tolerance extrusions
- Extruded forms
 - Tubing
 - Lay-flat tubing
 - Special profiles
 - Monofilament
 - Multi-lumen





WWW.ZEUSINC.COM


Resin Properties

PEEK™ - Polyetheretherketone

TECHNICAL INFORMATION

Background

- PEEK® is a high performance engineered polymer with amazing strength and heat resistant properties. PEEK® has become a popular replacement for metal in



applications such as aerospace where weight is a primary concern. It has also become the gold standard for HPLC analytical science applications due to its purity, high burst pressure, and chemical resistance. In medical applications PEEK's® biocompatibility, high tensile strength, and lubricity have made it an ideal replacement for stainless steel. PEEK® is a very rigid plastic with excellent lubricity and is tan in its natural color.

Key Properties

- Good coefficient of friction
- Gamma and autoclave sterilizability
- Chemical resistance (all common solvents, acids and bases)
- Maximum service temperature 250-260° C
- Excellent impact and wear resistance
- Excellent creep and fatigue resistance
- Idea replacement for stainless steel for weight and chemical compatibility

Additional Properties

- Radiation Resistance
- High temperature resistance
- Low flammability value
- Excellent hydrolysis resistance
- High strength
- Thermoformability
- Exceptional torsional stability
- High strength
- High burst pressure

ZEUS Capabilities

- Fillers available for material modification
 - Radio opaque
 - Carbon
 - Pigments
- Tight tolerance extrusions
- Extruded forms
 - Tubing
 - Lay-flat tubing
 - Special profiles
 - Heat shrink
 - Monofilament
 - Multi-lumen
 - Analytical tubing
 - Sub-Lite-Wall® tubing





WWW.ZEUSINC.COM

Resin Properties

PET - Polyethylene Terephthalate Polyester

Background

PET resin has become the polymer of choice for price sensitive applications requiring excellent mechanical and physical properties. ZEUS specializes in the extrusion of PET heat shrink available in lay-flat form.

Key Properties

- Clarity
- UV resistant (with additive)
- Extremely strong
- Shrink-back temperature begins at 180°F (82°C)
- Operating temperature exceeding 338°F (170°C)
- Low cost resin



Additional Properties

- Excellent dielectric strength
- Very lightweight
- Low water absorption



ZEUS Capabilities

- Fillers available for material modification
 - Radio opaque
 - Carbon
 - Pigments (specialty colors)
 - UV Inhibitors
- Extruded forms
 - Tubing
 - Lay-flat tubing
 - Heat shrink
 - Ultra thin walls



WWW.ZEUSINC.COM

Resin Properties

Nylons

TECHNICAL INFORMATION

Since its development in 1935, Nylon has found a home in applications ranging from automotive and aerospace to life saving medical devices and equipment. Nylon is available in a wide range of grades suited for many custom applications. ZEUS extrudes Nylon tubing and lay-flat tubing and can assist in the selection of the specific grade of Nylon best suited for your application.

Nylon 6

- High elasticity
- High tensile strength
- High resistance to abrasion
- High chemical resistance

Nylon 6/6

- Strongest unreinforced aliphatic nylon
- Most abrasion resistant unreinforced aliphatic nylon
- Better low temperature toughness than Nylon 6 or acetal
- Improved stiffness with addition of glass fiber- unlike acetal
- Good fatigue resistance



Nylon 11

- Low water absorption
- UV resistant
- Good tensile strength
- Heat resistant
- Low impact strength

Nylon 12

- Lowest moisture absorption of any commercial nylon
- Chemical resistance
- Excellent dimensional stability and electrical properties
- Low density
- FDA approved



PEBA

- Available in 35-72 and custom durometers
- Good low temperature properties
- Wide range of flex moduli
- Excellent resistance to fatigue during flexing
- Very good tensile strength
- Material modification:
 - Radio opaque



WWW.ZEUSINC.COM


Resin Properties

PE - Polyethylene

TECHNICAL INFORMATION

HDPE

- Maximum temperature: 150° F (66°C) - short duration; 130°F (54°C) - long duration
- Inherent lubricity
- Excellent chemical resistance
- Hardest and stiffest version of PE
- Resistant to sunlight
- Tensile strength: 3,200 - 4,500 psi



ZEUS Capabilities

- Extruded forms
 - Tubing
 - Dual Tube®
 - Lay-flat tubing
 - Special profiles



LDPE

- Maximum temperature: 150°F (66°C) - short duration; 130° F (54°C) - long duration
- Inherent lubricity
- Excellent chemical resistance
- Softest and most flexible version of PE
- High elongation, thus, excellent impact strength
- Tensile strength: 1,200 - 4,000 psi



WWW.ZEUSINC.COM

General Information

TECHNICAL INFORMATION

Coloring Plastics

Introduction to Coloring Plastics

Color measurement and matching may seem to be simple topics, but they represent some of the greatest challenges and difficulties in the plastics processing industry. Understanding color is more than just picking a Pantone® shade. Getting the appearance of the product or component right is fundamental to getting the product right – it is the first thing a customer sees, and mistakes or errors can result in costly rejects.

Color is not just visually important. Due to increasing legislation, particularly in the area of heavy metal colorants, the replacement of many traditional colorants with alternatives that have different performance characteristics and processing are being created (see our ROHS and WEEE information). Color not only affects our emotional response to a product, it is an emotional subject in its own right.

Standard colors

Standard colors are produced to a Pantone® chart color range. ZEUS can also produce custom colors from tubing samples or other subcomponents to meet your unique specification. ZEUS will work closely with you to match colors to a Pantone® range.

If matching a Pantone® chart color is critical in your application, ZEUS recommends that you have a physical Pantone® chart available on-hand for accurate color results. Pantone® chart colors do not reproduce accurately through the

process of digital reproduction and we do not recommend this approach.

ZEUS uses charts from Pantone, Inc. We use the most current Formula Guide, Solid Uncoated, and Pastel Formula Guide + Chips.

Please note that there may be some color variation due to pigment changes from lot to lot. ZEUS will minimize this variance to best effort. ZEUS has also developed the technology to extrude tubing with an integrated straight or spiral stripe of a contrasting color.

ZEUS Capabilities

- Pantone® chart color matching (please have your own Pantone® chart available for color verification)
- Custom colors from tubing samples
- Striping - Straight or Spiral
- OD-only Striping
- Natural colors available
- Translucent available in some materials
- RoHS and WEEE compliant colors available



WWW.ZEUSINC.COM

General Information

TECHNICAL INFORMATION

Shelf Life and Storage Requirements

Extruded Tubing

Fluoropolymer tubing does not have a determined shelf life. Extensive weathering and aging tests have been conducted and they revealed little to no degradation when exposed to weather, U.V. light, or extreme temperatures. Fluoropolymer tubing contains no antioxidant, plasticizers, U.V. blockers, antistatic agents or other additives which would bleed out during normal storage.

Heat Shrink

PTFE and FEP Heat Shrink tubing conforming to AMS-DTL-23053/11 and /12 are labeled with expiration date on tubing. All ZEUS products are labeled with date of manufacture.

Test Reports/Services

ZEUS' quality is the standard that other manufacturers aim for. Our quality control procedures surpass the industry standards in both the quality of the product and quality and detail of the documentation. ZEUS tubing runs through laser micrometers, making statistical process control data available upon request. Some of the state-of-the-art test equipment available through ZEUS testing labs include:

- Scanning Electron Microscope (SEM)
- Contact Angle Testers
- Laser Micrometers

- Dielectric Tester
- Optical Comparator
- Instron® Tensile Tester
- Differential Scanning Calorimeter
- Melt Flow Index Tester
- Specific Gravity Tester
- Vacuum/Pressure Tester
- Other Specialized and Proprietary Testers

A Certificate of Compliance is sent with every shipment, and test reports certifying conformance to military and commercial specifications are available upon request. Etched tubing is shipped with a certificate of etch, assuring you that the tubing has met ZEUS' rigorous quality standards. Additionally, ZEUS can offer customized testing and certification for the most challenging applications.

Traceability

We at ZEUS take great pride in our ability to maintain full traceability on all parts that we manufacture. Complete traceability is ensured through our ERP system. We can track equipment, inspectors, date of shipment as well as the resin lot that the material was produced from. Through our unsurpassed quality control, we have the ability to trace each lot to its origins as well as supply all test data from each individual lot. ZEUS lot numbers appear on all packaging and shipping containers.



WWW.ZEUSINC.COM

General Information

TECHNICAL INFORMATION

Visual Appearance

ZEUS specializes in manufacturing tubing from a variety of fluoropolymer resins for numerous applications. The finished tubing from these different resins can be visually similar, especially if the tubing has had pigment added to it.

The following describes several aspects of the visual appearance of ZEUS tubing that may be helpful in choosing and working with the finished products.

Most fluoropolymer tubing, whether it be PTFE (Polytetrafluoroethylene), FEP (Fluorinated ethylene propylene), PFA (Perfluoroalkoxy), ETFE (Ethylene tetrafluoroethylene), or one of the many other resins ZEUS extrudes, appears a clear to milky white color in its natural, unpigmented state. The clearest fluoropolymer resin is FEP, which allows for a high level of light transmission. PFA is quite clear as well, while PTFE material tends to be more milky in color.



Levels of clarity can be modified to some extent through different processing methods and the use of a variety of grades of resin at ZEUS.

Pigmented tubing is available in virtually any color you desire. From the brightest fluorescent yellows, pinks and oranges to the most opaque blues and blacks, ZEUS offers the widest range of colors available in fluoropolymer tubing. Levels of translucency and transparency can be modified to meet your specifications, and samples of many colors are available for inspection at no charge. ZEUS can even match a specific color currently at use in your product line through the use of color swatches. We also

manufacture pigmented tubing to specific colors on the Munsell® and Pantone® color charts.

ZEUS inspection procedures insure all tubing meets the stringent quality standards our customers require. Medical Grade Inspection is available for all products ZEUS manufactures, whether or not a medical application is the end use. We constantly inspect for any particulate matter that may limit performance in your application. Our ISO Class 7 certified clean room assures you of the utmost attention to your purity needs. ZEUS exceeds the highest cleanliness standards set forth in the most demanding industries and applications. You can be assured of the purest, highest quality tubing available when using ZEUS tubing.

All ZEUS tubing is inline visually inspected 100 percent by our highly trained inspection personnel, as well as by our exclusive array of dual axis Zumbach laser micrometers. We are constantly inspecting for any particulate matter that may limit performance in your application. ZEUS routinely limits particulate matter to less than .020", and we strive to supply the cleanest tubing available for the most stringent requirements possible. As a pioneer in fluoropolymer extrusion technology, ZEUS provides virtually flawless products unrivaled in the industry.





WWW.ZEUSINC.COM

Technical Notes

TECHNICAL INFORMATION

Tubing Bend Radius

The question is often raised as to what is the minimum bend radius of a specific size of tubing. The bend radius is established primarily by three different factors: diameter, wall thickness, and resin. ZEUS prides itself in its sample program through which we work with companies to find the right material and perfect size.

As a general guide, however, we have performed a series of bend tests that we hope will guide you in determining the size that is most suitable for you.

The following is a guide to the bend radius of our PTFE Industrial Wall tubing: Based on a minimum of 36" lengths:

| Size | Diameter* |
|------------------|-----------|
| 1/32" Industrial | .660" |
| 1/16" Industrial | 1.375" |
| 3/32" Industrial | 2.00" |
| 1/8" Industrial | 3.25" |
| 3/16" Industrial | 4.00" |
| 1/4" Industrial | 6.50" |
| 5/16" Industrial | 8.00" |
| 3/8" Industrial | 9.00" |
| 7/16" Industrial | 9.50" |
| 1" Industrial | 12.00" |

*Please Note: The bend radius is 1/2 the diameter.

Biocompatibility and Certified USP Class VI Approved Resins

ZEUS is proud to offer USP Class VI resin to meet the unique requirements of the medical device manufacturing community.

The following resins are certified USP Class VI approved, used for medical, diagnostic, and analytical applications consisting of extruded tubing, heat shrink tubing, profiles and multi-lumens:

- PTFE - Polytetrafluoroethylene
- FEP - Fluorinated ethylene propylene
- PFA - Perfluoroalkoxy
- ETFE - Ethylenetetrafluoroethylene
- PEEK™ - Polyetheretherketone

In addition, ZEUS has certified USP Class VI tests for many pigments and compounds used in conjunction with USP Class VI-tested resins.

ZEUS has tested the resins and pigments meet the following USP Plastics Class VI requirements:

Biological Reactivity

- Systemic Injection (Acute Systemic Toxicity, Mice)
- Intracutaneous Test (Intracutaneous Toxicity, Rabbits)
- Implantation Test (Implant, Rabbits)

In addition to the extensive testing ZEUS does on their resins, we offer 100 percent traceability on all your orders. You can be assured that when you purchase your tubing from ZEUS, it will pass subsequent traceability test requirements. Additional testing may also be available for certain resins.





WWW.ZEUSINC.COM

Technical Notes

TECHNICAL INFORMATION

Burst Pressure

ZEUS has been supplying fluoropolymer tubing to manufacturers of high pressure devices since our inception. The innate strength of all fluoropolymers make their use in these kinds of applications an ideal choice. Below, you will find a formula for calculating the maximum burst pressure by using Tensile Strength Values.

The theoretical burst pressure of tubing at ambient temperature can be calculated by using the ID and OD dimensions in inches and the tensile strength at yield in pounds per square inch.

The following formula is to be used as a guide in the design process. It does not consider factors such as steam pressure and elevated temperature, altitude, etc., and it is calculated at ambient room temperature. The burst pressure result is meant as a guideline in design, not a definitive number.

$$P = \frac{T (OD^2 - ID^2)}{OD^2 + ID^2}$$

P = Theoretical Burst Pressure, psi
T = Tensile Strength at Yield, psi

Chemical Compatibility

Fluoropolymer resins are essentially chemically inert. This has long been one of the greatest assets of these plastics. Fluoropolymers are an ideal transport medium for today's highly volatile chemical compounds and exotic fluids. The widespread acceptance within the chemical, environmental, defense, aerospace, and medical industries is a testament to fluoropolymers' unique ability to withstand and resist a wide variety of liquid and gaseous compounds.

There are very few chemicals, such as molten alkali metals, turbulent liquid or gaseous fluorine, chlorine trifluoride, or oxygen difluoride, that are known to react with fluoropolymers.

To a lesser degree, halogenated organic chemicals may be absorbed by fluoropolymer resins. This will cause a very slight change in weight or possibly a slight swelling. This phenomenon is less evident in FEP and PFA extrusions because they are relatively less permeable than PTFE extrusions.

Concentricity Formula

To determine a tube's concentricity use the following formula:

W min is the minimum wall thickness and W max is the maximum wall thickness of the sleeve as taken from any location of the wall of a tubing's cross section. This can be measured using a toolmakers micrometer or optical comparator.

- ASTM D 2671 11.3

$$C = 100 \times \frac{(W \text{ min})}{(W \text{ max})}$$



WWW.ZEUSINC.COM

Technical Notes

TECHNICAL INFORMATION

Etching - Technical Questions

Why would I need to etch tubing?

Fluoropolymers such as PTFE, FEP, and PFA (often called Teflon®) are very lubricious (slippery). This lubricity and the chemical composition of fluoropolymers reduces their bondability. Etching alters the surface properties of the polymer allowing it to be bonded with conventional adhesives.

How does it work?

Etching is performed by the chemical reaction between a sodium solution and the fluorine molecules on the surface of the tubing. Fluorine molecules are stripped from the carbon backbone of the fluoropolymer. This leaves the carbon atoms with a deficiency of electrons. When the etched material is exposed to air, oxygen molecules, water vapor, and hydrogen allow restoration of the electrons. This restoration process results in a group of organic molecules responsible for adhesion.



Will etching change the properties of my tubing?

The etching process only penetrates to a depth of a few angstroms so the properties of the tubing will remain mostly unaffected. However the etching process will darken the surface of the material, usually to a brown or tan shade. Surface lubricity is also reduced by the etching process.

How should I store etched tubing?

Etched fluoropolymers will "grab" molecules from the air to repair their electron


deficiency. This results in a weakening of the surface etching. For this reason, all etched materials should be stored in their original sealed bags. ZEUS ships all etched tubing orders in sealed black protective bags to prevent degradation from UV radiation.

Does a darker color mean a better etch?

Color is not a reliable indicator of etch quality. For this reason ZEUS includes etch certifications with each order shipped.

How is the etch tested?

The etched material is tested using the contact angle method. Contact angle measurements of liquid droplets on substrate surfaces are used to characterize surface wettability. As shown in Figure 1 below, the contact angle is defined as the angle between the substrate support surface and the tangent line at the point of contact of the liquid droplet with the substrate. In this picture, example "B" demonstrates a more effective etch than example "A" .



ZEUS performs contact angle tests on all etched tubing orders and includes a Certificate of Compliance with the material.



WWW.ZEUSINC.COM

Technical Notes

TECHNICAL INFORMATION

What is the shelf life on etch products?

Many etched products have an almost unlimited shelf life when stored properly. ZEUS recommends following good inventory practices, rotating stock, and using inventory as soon as possible.

Fillers Used in Fluoropolymer Tubing

There are a number of reasons why a filler may enhance the performance of ZEUS tubing, such as increased tensile strength, higher resistance, and increased rigidity. The following information may help to choose the filler that best suits your application. Contact a ZEUS Technical Account Manager for more information.

INDUSTRIAL USES

GLASS

Glass fillers are used to increase abrasion resistance in potentially harsh mechanical applications. Small glass beads are added to the resin and are blended in during the extrusion process. The finished tubing is extremely strong and resistant to the many sources of wear fluoropolymer tubing may be subjected to in an industrial application. Glass also increases the corrosion resistance at high temperatures. ZEUS has also developed a special technology to produce glass-filled PTFE with a smooth surface finish.

MEDICAL USES

BISMUTH and TUNGSTEN

Bismuth is used to allow PTFE, Pebax®, and other tubing to be visualized on a fluoroscopic screen during invasive procedures. This allows the physicians to see the surgical implantable device both during and after the procedure has been completed. Visualizing the device allows the physician to guide and maneuver the device for proper placement or alignment. Bismuth will also allow the device to be visualized on routine diagnostic radiographs. Bismuth is well accepted in the medical profession to be in contact with the body.

BARIUM

Barium is used in FEP and other tubing as bismuth is used in PTFE tubing above. Surgical or implantable devices can be viewed on fluoroscopic screens during and after surgeries and on diagnostic radiographs. And, as bismuth, it is medically accepted for contact with the body.





WWW.ZEUSINC.COM

Technical Notes

TECHNICAL INFORMATION

Low Temperature Rating

Fluoropolymer resins maintain their lubricity, abrasion resistance, and strength at temperatures below freezing. Extensive testing at 0°F (-18°C) and lower have shown that PTFE is the ideal choice for cryogenic applications. With a low temperature range of -450°F (-268°C), showing little or no embrittlement, PTFE remains highly flexible at temperatures below -100°F (-73°C).

Lubricity (*Coefficient of Friction*)

Lubricity is defined in the Webster's New World Dictionary as "slipperiness; smoothness". It is more widely known in our industry as the coefficient of friction. Lubricity is one of many unique characteristics of fluoropolymers that separates itself from other polymers. The fluoropolymers have a smooth surface with a slippery feel.

Because of the low coefficient of friction, there have been many practical non-lubricated and minimally-lubricated mechanical systems developed around fluoropolymers. The low coefficient of friction is a result of low interfacial forces between its surface and other materials and the comparatively low force of deform.

Fluoropolymer's low coefficient of friction properties are tremendous advantages in increasing flow rates, reducing friction in critical applications, and allow the materials to be cleaned easily. In fact, PTFE has a coefficient of friction that is, amazingly enough, comparable to ice on ice, and it even remains stable under severe load.

Permeability

Definition:

1. The flux of a small penetrate molecule (permeate) through a matrix which accounts for chemical interaction between the permeate and the matrix.
2. The property of a material quantization the flux of a small penetrate molecules (permeate) through a material such as a polymer by a sufficient chemical and concentration gradient.
3. The product of the Diffusion (interaction-less transport of a small diffusion molecule through a matrix based on a concentration gradient) and the Solubility (the interaction between the solubility diffusion and the matrix).
4. To get a true test of permeation, the test should be run on the final component, due to the impact of morphology of the polymer matrix and the many variables that can impact permeability.

Water Absorption

Water absorption in polymers can be effected by the polymer selected, fillers used, and processing method. A range of typical water absorption properties can be reviewed in our summary of properties sheet at the end of this catalog. If water absorption is a key concern please contact a ZEUS Technical Account Manager for advice in selecting the ideal resin for your application.



WWW.ZEUSINC.COM

Technical Notes

TECHNICAL INFORMATION

Relationship for gaseous permeation is:

$$P = D S$$

P is the permeability (cm³(STP)/sec-cm-cm Hg)

D is the diffusion coefficient (sm²/sec)

S is the solubility coefficient (cm³(STP)/cm³-cm Hg)

Sterilization Methods

Please see the following table to select the best material suited for your sterilization method of choice.

Sterilization methods:

ETO, Autoclave, and Gamma

| Resin | ETO | Autoclave | Gamma |
|--------------|-----------|-----------|--------------|
| PTFE | Excellent | Average | Poor |
| FEP | Excellent | Excellent | Good |
| PFA | Excellent | Excellent | Poor |
| ETFE | Excellent | Excellent | Good |
| PVDF | Excellent | Excellent | Good |
| PEEK™ | Excellent | Excellent | Excellent |
| Polyethylene | Excellent | Excellent | Good* |

*High density grades not as stable as medium and low grades

UV Compatibility

ZEUS tubing is virtually unaffected by weather or prolonged exposure to ultraviolet light. Independent testing on samples exposed to virtually all climatic conditions confirm the weather resistant properties of fluoropolymer tubing. Where applications demand complete dependability in these conditions, fluoropolymers are the answer. Resistance to extreme heat, cold, and ultraviolet light encountered in radar and other electronic components, such as antenna bushings, are excellent examples of the value of this material in these applications.

Ultraviolet transmittance can be another useful aspect of fluoropolymer tubing. While levels of UV transmittance vary among the fluoropolymer resin family, ZEUS tubing is used in applications such as water purification with excellent results. Crystallinity and wall thickness also affect the level of transmittance tubing will allow. Contact a ZEUS Technical Account Manager for more information on this very useful property of fluoropolymer tubing.

Summary Of Properties

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. Property characteristics are dramatically impacted by geometry and processing method; therefore the properties of extruded parts may vary. This table is only meant to serve as a general guideline; users should evaluate the material to determine the suitability for their own particular application.

| PHYSICAL | ASTM | PTFE | FEP | PFA | THV | PVDF | EFEP | ETFE | PEEK |
|--|-------------|-------------|------------|------------|------------|-------------|-------------|-------------|-------------|
| Density (g/cc) | D792 | 2.16 -2.22 | 2.12-2.17 | 2.12-2.17 | 1.95-2.06 | 1.76-1.88 | 1.74 | 1.7-1.86 | 1.1-1.48 |
| Water Absorption (%) | D570 | 0 | 0.004 | <0.03 | <0.03 | 0.01-0.06 | 0.1 max | 0.007 | 0.1-0.45 |
| Standard Percent Crystallinity (%) | | >90 | 70 | 48-70 | 26-29 | 35-70 | 10 | 50 | 25-35 |
| Refractive Index | | 1.35 | 1.33-1.35 | 1.35 | 1.3502 | 1.42 | 1.338-1.34 | 1.34 | --- |
| Radiation Resistance (MRad) | | 1 | 10 | 1-10 | 20 | 1000 | --- | 50 | 1000 |
| Oxygen Index (%) | D2863 | >95 | 95 min | 95 min | 65-75 | 44-80 | 31 | 30-46 | 35 |
| | | | | | | | | | |
| MECHANICAL | ASTM | PTFE | FEP | PFA | THV | PVDF | EFEP | ETFE | PEEK |
| Hardness, Shore D | D2240 | 50-65 | 55-65 | 55-60 | 44-58 | 65-82 | 75 | 63-72 | >85 |
| Ultimate Tensile Strength (MPa) | D638 | 20-35 | 18-34 | 25-35 | 20-29 | 17-48 | 40-50 | 37-50 | 75-97 |
| Elongation at Break (%) | D638 | 200-550 | 245-400 | 250-420 | 420-600 | 50-400 | 420-460 | 200-550 | 96-110 |
| Modulus of Elasticity (GPa) | D638 | 0.39-0.6 | 0.44-0.64 | 0.45 | 0.24 | 0.5-5 | 0.490-0.78 | 0.49-0.78 | 2.3-4.3 |
| Flexural Modulus (GPa) | D790 | 0.275-0.7 | 0.58-0.62 | 0.6-0.7 | 0.032-0.52 | 1.3-7 | 0.88-1.37 | 0.7-1.2 | 3.6-4.1 |
| Coefficient of Friction | | 0.02-0.2 | 0.04-0.2 | 0.04-0.2 | 0.8 | 0.14-0.23 | 0.055-0.078 | 0.05-0.4 | 0.34 |
| | | | | | | | | | |
| ELECTRICAL | ASTM | PTFE | FEP | PFA | THV | PVDF | EFEP | ETFE | PEEK |
| Volume Resistivity (Ω -cm) | D257 | 1e14-1e19 | 1e17 -1e18 | 1e18 | >1e15 | 1.5-2e14 | 1e16 | 1e17 | 4.9e16 |
| Dielectric Constant 1MHz | D150 | 2.1 | 2-2.1 | 1.9-2.1 | 2.4-6.6 | 7 | 2.6 | 2.5-2.6 | 2.8-2.2 |
| Dielectric Strength (V/mil) | D149 | 189-610 | 500-2000 | 500-2000 | 1220-1570 | 800-1700 | 400 | 400-1800 | 500 |
| | | | | | | | | | |
| THERMAL | ASTM | PTFE | FEP | PFA | THV | PVDF | EFEP | ETFE | PEEK |
| Conductivity (W/m-K) | C117 | 0.167-0.3 | 0.19-0.25 | 0.15-0.25 | -- | 0.17-0.19 | 0.24 | 0.24 | 0.25 |
| Maximum Service Temp, Air ($^{\circ}$ C) | | 260 | 200-205 | 260 | 150 | 100-130 | 150 | 150 | 250-260 |
| Minimum Service Temp, Air ($^{\circ}$ C) | | -200--240 | -200--240 | -200 | -50 | | --- | -100--1890 | |
| Melt Temperature ($^{\circ}$ C) | | 327-342 | 265-275 | 300-315 | 120-185 | 172 | 160-195 | 230-280 | 343 |
| Glass Temperature ($^{\circ}$ C) | | 127 | 80 | 100 | 5-36 | -30--40 | -40-50 | 40-80 | 143 |
| Decomposition Temperature ($^{\circ}$ C) | E1131 | 400-500 | 380-430 | 475 | 420-440 | 375-400 | 350 | 350-380 | 540 |
| CTE, linear 20 $^{\circ}$ (μ m/m- $^{\circ}$ C) | D696 | 126-180 | 100-135 | 120-140 | --- | 90-144 | 50-90 | 50-90 | 47 |



P. O. Box 2167, 3737 Industrial Blvd, Orangeburg, SC 29116-2167, USA
1-800-526-3842 • 1-803-268-9500 • FAX: 1-803-533-5694 • www.zeusinc.com

This is an uncontrolled copy and may not be the most recent version. Please refer to www.zeusinc.com or contact Zeus at (800) 526-3842 for our most recent information.

QF7.2-012 Rev. G