


EE CORES



TYPE		EE13	EE16	EEL16	EE19	EEL19	EF20	EF25
DIMENSIONS (mm)	A	13.0±0.3	16.0±0.3	16.0±0.3	19.15±0.3	19.0±0.3	20.1±0.7	25.1±0.8
	B	10.0min	11.7min	11.7min	14.2min	13.7min	14.4±0.4	17.5min
	C	2.7±0.2	4.0±0.2	4.0±0.2	4.65±0.25	4.85±0.25	5.7±0.2	7.25±0.25
	D	6.1±0.2	4.9±0.2	4.75±0.25	4.8±0.25	4.85±0.25	5.7±0.2	7.2±0.3
	2E	9.5±0.5	10.6±0.4	20.5±0.5	11.1±0.3	22.6±0.6	12.8±0.4	18±0.6
	2F	12.4±0.4	14.6±0.4	24.5±0.4	15.8±0.6	27.1±0.6	18.4±0.4	25.2±0.6
CORE FACTOR	$C_1(\text{mm}^{-1})$	1.84	1.79	2.93	1.74	2.64	1.36	1.11
EFFECTIVE LENGH	$l(\text{mm})$	31.1	34.8	55.3	39.6	61.7	43.16	57.8
EFFECTIVE AREA	$A_e(\text{mm}^2)$	16.9	19.4	18.9	22.8	23.4	31.73	51.8
EFFECTIVE VOLUME	$V_e(\text{mm}^3)$	524	678	1044	903	1443	1370	2990
APPROX WEIGHT/set	W(g)	3	3.6	5.3	4.7	7.4	7.1	15.6
A_L VALUE (nH ± 25%)	JP4A	900min	850min	600min	900min	670min	1700	1900
	JH5	1250min	1700	1500		1600		
	JH7		2000	1800		2000		
	JH10							