

#### **Overview**


KEMET's X7R dielectric features a 125°C maximum operating temperature and is considered "temperature stable." The Electronics Components, Assemblies & Materials Association (EIA) characterizes X7R dielectric as a Class II material. Components of this classification are fixed, ceramic dielectric capacitors suited for bypass and decoupling applications or for frequency discriminating circuits where Q and stability of capacitance characteristics are not critical. X7R exhibits a predictable change in capacitance with respect to time and voltage and boasts a minimal change in capacitance with reference to ambient temperature. Capacitance change is limited to  $\pm 15\%$  from  $-55^{\circ}$ C to  $+125^{\circ}$ C.

## **Benefits**

- -55°C to +125°C operating temperature range
- · Lead (Pb)-Free, RoHS, and REACH Compliant
- Temperature stable dielectric
- EIA 0402, 0603, 0805, 1206, 1210, 1808, 1812, 1825, 2220, and 2225 case sizes
- DC voltage ratings of 6.3 V, 10 V, 16 V, 25 V, 35 V, 50 V, 100 V, 200 V, and 250 V
- Capacitance offerings ranging from 10 pF to 47  $\mu\text{F}$
- Available capacitance tolerances of  $\pm 5\%$ ,  $\pm 10\%$ , and  $\pm 20\%$
- Non-polar device, minimizing installation concerns
- 100% pure matte tin-plated termination finish allowing for excellent solderability
- SnPb termination finish option available upon request (5% Pb minimum)

# Applications

Typical applications include decoupling, bypass, filtering and transient voltage suppression.



С	1206	С	106	М	4	R	А	С	TU
Ceramic	Case Size (L" x W")	Specification/ Series <sup>1</sup>	Capacitance Code (pF)	Capacitance Tolerance	Rated Voltage (VDC)	Dielectric	Failure Rate/ Design	Termination Finish <sup>2</sup>	Packaging/ Grade (C-Spec)
	0402 0603 0805 1206 1210 1808 1812 1825 2220 2225	C = Standard	Two significant digits + number of zeros.	J = ±5% K = ±10% M = ±20%	$9 = 6.3 \\ 8 = 10 \\ 4 = 16 \\ 3 = 25 \\ 6 = 35 \\ 5 = 50 \\ 1 = 100 \\ 2 = 200 \\ A = 250$	R = X7R	A = N/A	C = 100% Matte Sn	See "Packaging C-Spec Ordering Options Table" below

<sup>1</sup> Flexible termination option is available. Please see FT-CAP product bulletin C1013\_X7R\_FT-CAP\_SMD.

<sup>2</sup> Additional termination finish options may be available. Contact KEMET for details.

# **Ordering Information**

## Packaging C-Spec Ordering Options Table


Packaging Type <sup>1</sup>	Packaging/Grade Ordering Code (C-Spec)
Bulk Bag / Unmarked	Not required (Blank)
7" Reel / Unmarked	TU
13" Reel / Unmarked	7411 (EIA 0603 and smaller case sizes) 7210 (EIA 0805 and larger case sizes)
7" Reel / Marked	ТМ
13" Reel / Marked	7040 (EIA 0603 and smaller case sizes) 7215 (EIA 0805 and larger case sizes)
7" Reel / Unmarked / 2mm pitch <sup>2</sup>	7081
13" Reel / Unmarked / 2mm pitch <sup>2</sup>	7082

<sup>1</sup> Default packaging is "Bulk Bag". An ordering code C-Spec is not required for "Bulk Bag" packaging.

<sup>1</sup> The terms "Marked" and "Unmarked" pertain to laser marking option of capacitors. All packaging options labeled as "Unmarked" will contain capacitors that have not been laser marked. Please contact KEMET if you require a laser marked option. For more information see "Capacitor Marking".

<sup>2</sup> The 2 mm pitch option allows for double the packaging quantity of capacitors on a given reel size. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information".

#### **Dimensions – Millimeters (Inches)**



EIA Size Code	Metric Size Code	L Length	W Width	T Thickness	B Bandwidth	S Separation Minimum	Mounting Technique
0402	1005	1.00 (0.040) ±0.05 (0.002)	0.50 (0.020) ±0.05 (0.002)		0.30 (0.012) ±0.10 (0.004)	0.30 (0.012)	Solder Reflow Only
0603	1608	1.60 (0.063) ±0.15 (0.006)	0.80 (0.032) ±0.15 (0.006)		0.35 (0.014) ±0.15 (0.006)	0.70 (0.028)	
0805	2012	2.00 (0.079) ±0.20 (0.008)	1.25 (0.049) ±0.20 (0.008)		0.50 (0.02) ±0.25 (0.010)	0.75 (0.030)	Solder Wave or Solder Reflow
1206	3216	3.20 (0.126) ±0.20 (0.008)	1.60 (0.063) ±0.20 (0.008)		0.50 (0.02) ±0.25 (0.010)		
1210 <sup>1</sup>	3225	3.20 (0.126) ±0.20 (0.008)	2.50 (0.098) ±0.20 (0.008)	See Table 2	0.50 (0.02) ±0.25 (0.010)		
1808	4520	4.70 (0.185) ±0.50 (0.020)	2.00 (0.079) ±0.20 (0.008)	for Thickness	0.60 (0.024) ±0.35 (0.014)		
1812	4532	4.50 (0.177) ±0.30 (0.012)	3.20 (0.126) ±0.30 (0.012)		0.60 (0.024) ±0.35 (0.014)	N/A	Solder Reflow
1825	4564	4.50 (0.177) ±0.30 (0.012)	6.40 (0.252) ±0.40 (0.016)		0.60 (0.024) ±0.35 (0.014)		Only
2220	5650	5.70 (0.224) ±0.40 (0.016)	5.00 (0.197) ±0.40 (0.016)	1	0.60 (0.024) ±0.35 (0.014)		
2225	5664	5.60 (0.220) ±0.40 (0.016)	6.40 (0.248) ±0.40 (0.016)	1	0.60 (0.024) ±0.35 (0.014)		

<sup>1</sup> For capacitance values  $\geq$  4.7  $\mu$ F add 0.02 (0.001) to the width tolerance dimension and 0.10 (0.004) to the length tolerance dimension.

© KEMET Electronics Corporation • P.O. Box 5928 • Greenville, SC 29606 (864) 963-6300 • www.kemet.com



## **Qualification/Certification**

Commercial Grade products are subject to internal qualification. Details regarding test methods and conditions are referenced in Table 4, Performance & Reliability.

## **Environmental Compliance**

Lead (Pb)-Free, RoHS, and REACH compliant without exemptions.

### **Electrical Parameters/Characteristics**

Item	Parameters/Characteristics
Operating Temperature Range	-55°C to +125°C
Capacitance Change with Reference to +25°C and 0 Vdc Applied (TCC)	±15%
<sup>1</sup> Aging Rate (Maximum % Capacitance Loss/Decade Hour)	3.0%
<sup>2</sup> Dielectric Withstanding Voltage (DWV)	250% of rated voltage (5 ± 1 seconds and charge/discharge not exceeding 50mA)
<sup>3</sup> Dissipation Factor (DF) Maximum Limit @ 25°C	See Dissipation Factor Limit Table
<sup>₄</sup> Insulation Resistance (IR) Minimum Limit @ 25°C	See Insulation Resistance Limit Table (Rated voltage applied for 120 ± 5 secs @ 25°C)

<sup>1</sup>Regarding Aging Rate: Capacitance measurements (including tolerance) are indexed to a referee time of 48 or 1,000 hours. Please refer to a part number specific datasheet for referee time details.

<sup>2</sup>DWV is the voltage a capacitor can withstand (survive) for a short period of time. It exceeds the nominal and continuous working voltage of the capacitor. <sup>3</sup>Capacitance and dissipation factor (DF) measured under the following conditions:

1 kHz  $\pm$ 50 Hz and 1.0  $\pm$ 0.2 Vrms if capacitance  $\leq$  10  $\mu$ F

120 Hz  $\pm$ 10 Hz and 0.5  $\pm$ 0.1 Vrms if capacitance > 10  $\mu$ F

<sup>4</sup>To obtain IR limit, divide  $M\Omega$ - $\mu$ F value by the capacitance and compare to G $\Omega$  limit. Select the lower of the two limits.

Note: When measuring capacitance it is important to ensure the set voltage level is held constant. The HP4284 and Agilent E4980 have a feature known as Automatic Level Control (ALC). The ALC feature should be switched to "ON."

### Insulation Resistance Limit Table (X7R Dielectric)

EIA Case Size	1,000 Megohm Microfarads or 100 GΩ	500 Megohm Microfarads or 10 GΩ
0201	N/A	ALL
0402	< 0.012 µF	≥ 0.012 µF
0603	< 0.047 µF	≥ 0.047 µF
0805	< 0.15 µF	≥ 0.15 µF
1206	< 0.47 µF	≥ 0.47 µF
1210	< 0.39 µF	≥ 0.39 µF
1808	ALL	N/A
1812	< 2.2 µF	≥ 2.2 µF
1825	ALL	N/A
2220	< 10 µF	≥ 10 µF
2225	ALL	N/A

## **Post Environmental Limits**

	High Temp	erature Life, E	Biased Humid	lity, Moisture	Resistance	
Dielectric	Case Size	Rated DC Voltage	Capacitance Value	Dissipation Factor (Maximum %)	Capacitance Shift	Insulation Resistance
		< 16		7.5		
	0402	16 / 25	All	5.0		
		> 25		3.0		
		< 16		7.5		
		16 / 25	< 1.0 µF	5.0		
	0603	> 25		3.0		
		< 16	≥ 1.0 µF	20.0		
		16 / 25	= 1.0 μ1			
		< 16	< 2.2 µF	7.5		
		16 / 25		5.0		
	0805	> 25	< 1.0 µF	3.0		
	0003	< 16	≥ 2.2 µF			
		16 / 25		20.0		
X7R		> 25	≥ 1.0 µF		± 20%	10% of Initial
		< 16		7.5	1 2070	Limit
		16 / 25	< 10 µF	5.0		
	1206	> 25	ļ	3.0		
	1200		≥ 2.2 µF			
			> 10 µF	20.0		
		$1206 \qquad 35 / 50 \geq 2$	_ 10 µ1			
	$\begin{array}{c c c c c c c c c c c c c c c c c c c $					
				3.0		
		< 16	≥ 22 µF	20.0		
		16 / 25				
		< 16		7.5		
	1808-2225	16 / 25	All	5.0		
		> 25		3.5		



# **Dissipation Factor (DF) Limit Table**

EIA Case Size	Rated DC Voltage	Capacitance	Dissipation Factor (Maximum %)
	< 16	All	5.0
	16	All	3.5
0402	25	< 0.1 µF	3.5
	25	≥ 0.1 µF	10.0
	> 25	All	2.5
	< 16		5.0
	16 / 25	< 1.0 µF	3.5
0603	> 25		2.5
	< 16	>10r	10.0
	16 / 25	≥ 1.0 µF	10.0
	< 16	- <u>2</u> 2 μ.Γ	5.0
	16 / 25	< 2.2 µF	3.5
0005	> 25	< 1.0 µF	2.5
0805	< 16	> 2 2F	
	16 / 25	≥ 2.2 µF	10.0
	> 25	≥ 1.0 µF	
	< 16		5.0
	16 / 25	< 10 µF	3.5
1007	> 25		2.5
1206	35 / 50	≥ 2.2 µF	10.0
	< 16	> 10	10.0
	16 / 25	≥10 µF	10.0
	< 16		5.0
	16 / 25	< 22 µF	3.5
1210	> 25		2.5
	< 16	> 00	10.0
	16 / 25	≥ 22 µF	10.0
	< 16		5.0
1808-2225	16 / 25	All	3.5
	> 25		2.5



## Table 1A – Capacitance Range/Selection Waterfall (0402 – 1206 Case Sizes)

	_		se Si ierie			C	)402	2 <b>C</b>				C	)60	3C						С	080	5C							C	120	6C			
Сар	Сар	Volt	tage C	ode	9	8	4	3	5	9	8	4	3	5	1	2	9	8	4	3	6	5	1	2	Α	9	8	4	3	6	5	1	2	Α
	Code		ed Volt (VDC)	tage	6.3	9	16	25	50	6.3	10	16	25	50	100	200	6.3	9	16	25	35	50	100	200	250	6.3	9	16	25	35	50	100	200	250
		Сар	Tolera	ance		F	Prod	uct	Ava	aila	bilit	y a	nd (	Chip	Th	ickı	nes	s Co	de	s – :	See	Tał	ble 2	2 foi	r Ch	nip 1	Thic	kne	ess	Dim	ens	ion	s	
10 - 20 pF*	100 - 200*	J	К	М	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF			DN								EB	EB		EB	EB	EB	EB	EB	
22 pF	220	J	K	M	BB	BB	BB	BB	BB	CF	DM	DM	DM		DM	DM	DN	DN		EB														
24 - 91pF	240 - 910* 101 - 151**	J	K K	M M	BB BB	BB	BB BB	BB BB	BB	CF CF	CF CF	CF	CF	CF CF	CF CF	CF CF	DN	DN	DN	DN	DN	DN	DN	DN		EB EB	EB EB	EB	EB EB	EB	EB	EB EB	EB EB	
100 - 150 pF** 180 - 820 pF**	101 - 151 181 - 821**	J	K	M	BB	BB BB	BB	BB	BB BB	CF	CF	CF CF	CF CF	CF	CF	CF	DN DN	DN DN	DN DN	DN DN	DN DN	DN DN	DN DN	DN DN	DN	EB	EB	EB EB	EB	EB EB	EB EB	EB	EB	
1000 020 pi 1000pF	101 021	J	K	M	BB	BB	BB	BB	BB	CF	DN	DN	DN	DN	DN			DN	DN	EB														
1200 pF	122	Ĵ	ĸ	M	BB	BB	BB	BB	BB	CF	DN	DN	DN	DN	DN	DN		DN	DN	EB														
1500 pF	152	J	К	М	BB	BB	BB	BB	BB	CF	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB														
1800 pF	182	J	К	М	BB	BB	BB	BB	BB	CF	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB														
2200 pF	222	J	К	М	BB	BB	BB	BB	BB	CF	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB														
2700 pF	272	J	K	М	BB	BB	BB	BB	BB	CF	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB														
3300 pF	332	J	K	M	BB	BB	BB	BB	BB	CF	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB														
3900 pF	392	J	K	M	BB	BB	BB	BB	BB	CF	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB														
4700 pF	472	J	K K	M	BB BB	BB	BB BB	BB BB	BB BB	CF	CF CF	CF	CF	CF CF	CF CF	CF CF	DN DN	DN DN	DN	DN	DN DN	DN	DN	DN	DN	EB EB	EB EB	EB EB	EB EB	EB EB	EB	EB EB	EB EB	EB EB
5600 pF 6800 pF	562 682	J	K	M	BB	BB BB	BB	BB	BB	CF CF	CF	CF CF	CF CF	CF	CF	CF	DN	DN	DN DN	DN DN	DN	DN DN	DN DN	DN DN	DN DN	EB	EB	EB	EB	EB	EB EB	EB	EB	EB
8200 pF	822	J	K	M	BB	BB	BB	BB	BB	CF	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB														
10000 pF	103	J	ĸ	M	BB	BB	BB	BB	BB	CF	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB														
12000 pF	123	Ĵ	ĸ	M	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF	0.	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB								
15000 pF	153	J	к	М	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF		DN	DN	DN	DN	DN	DN	DN	DN	DN	EB								
18000 pF	183	J	K	М	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF		DN	DN	DN	DN	DN	DN	DN	DN	DN	EB								
22000 pF	223	J	K	Μ	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF		DN	DN	DN	DN	DN	DN	DN	DN	DN	EB								
27000 pF	273	J	K	М	BB	BB	BB	BB		CF	CF	CF	CF	CF	CF		DN	DN	DN	DN	DN	DN	DP	DE		EB								
33000 pF	333	J	K	М	BB	BB	BB	BB		CF	CF	CF	CF	CF	CF		DN	DN	DN	DN	DN	DN	DP	DE		EB								
39000 pF	393	J	K	M	BB	BB	BB	BB		CF	CF	CF	CF	CF	CF		DN	DN	DN	DN	DN	DN	DP	DE		EB	EB	EB	EB	EB	EB	EC	EB	EB
47000 pF	473	J	K	M	BB BB	BB	BB	BB		CF	CF	CF	CF	CJ	CF		DO DP	DO DP	DO	DO DP	DO DP	DO	DE	DG		EB	EB	EB	EB	EB	EB	EC	ED	ED
56000 pF 68000 pF	563 683	J	K K	M	BB	BB BB	BB BB			CF CF	CF CF	CF CF	CF CF	CF CF			DP	DP	DP DP	DP	DP	DP DP	DE DE	DG		EB EB	ED ED	ED ED						
82000 pF	823	J	K	M	BB	BB	BB			CF	CF	CF	CF	CF			DP	DP	DP	DP	DP	DP	DE			EB	ED	ED						
0.1 µF	104	J	K	M	BB	BB	BB	BB1		CF	CF	CF	CF	CF			DN	DN	DN	DN	DN	DN	DE			EB	EM	EM						
0.12 µF	124	J	K	M						CF	CF	CF	CF	CF			DN	DN	DN	DN	DP	DP	DG			EC	EG							
0.15 µF	154	J	К	М	1					CF	CF	CF	CF	CF			DN	DN	DN	DN	DP	DP	DG			EC	EG							
0.18 µF	184	J	К	М						CF	CF	CF	CF				DN	DN	DN	DN	DG	DG	DG			EC								
0.22 μF	224	J	K	М						CF	CF	CF	CF				DN	DN	DN	DN	DG	DG	DG			EC								
0.27 μF	274	J	K	М						CF	CF	CF					DP	DP	DP	DP	DP	DP				EB	EB	EB	EB	EC	EC	EM		
0.33 µF	334	J	K	M						CF	CF	CF					DG	DG	DG	DG	DP	DP				EB	EB	EB	EB	EC	EC	EG		
0.39 µF	394	J	K	M						CF	CF	CF	000				DG	DG	DG	DG	DE	DE				EB	EB	EB	EB	EC	EC	EG		
0.47 µF	474	J	K	M						CF	CF	CF	CG1				DG DP	DG DP	DG DP	DG DG	DE	DE DH				EC	EC ED	EC ED	EC ED	EC EC	EC EC	EG EM		
0.56 μF 0.68 μF	564 684	J	K K	M													DP	DP	DP	DG	DH DH					ED EE	ED	ED	ED	ED	ED	EM		
0.88 µF	824	J	K	M													DP	DP	DP	DG						EF	EF	EF	EF	ED	_	EIVI		
0.02 μι 1 μF	105	J	K	M						CG1	CG1	CG1	CD1					DP			DG1	DG <sup>1</sup>				EP	EP		EP		ED			
1.2 μF	125	Ĵ	K	M														DE										ED						
1.5 µF	155	J	К	М													DG	DG	DG							ED	ED	ED	EG	EH	EH			
1.8 µF	185	J	К	М													DG	DG	DG								ED	ED	EF	EH	EH			
2.2 µF	225	J	К	М						CG1	CG1						DG	DG	DG	DG1						EH		EH1		EH	EH			
2.7 µF	275	J	K	Μ																						i –		EN	-					
	Con		ed Volt (VDC)		6.3	9	16	25	20	6.3	9	9	25	20	ģ	200	6.3	9	16	25	35	20	ģ	200	250	6.3	9	16	25	35	20	10	200	250
Сар	Cap Code		Voltage Code     9     8     4     3     5       Case Size/     October     October							9	8	4	3	5	1	2	9	8	4	3	6	5	1	2	Α	9	8	4	3	6	5	1	2	Α
			se Si Serie			С	0402	2C				С	060	3C						С	080	5C							C	1206	6C			

\*Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91) \*\*Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)

KEMET reserves the right to substitute product with an improved temperature characteristic, tighter capacitance tolerance and/or higher voltage capability within the same form factor (configuration and dimensions).

*xx*<sup>1</sup> Available only in K, M tolerance.

 $xx^2$  Available only in M tolerance.



## Table 1A – Capacitance Range/Selection Waterfall (0402 – 1206 Case Sizes) cont'd

			se S erie	ize/ s		С	)402	2C				С	)60	3C						C	080	5C							C	120	6 <b>C</b>			
Сар	Сар	Volt	age C	ode	9	8	4	3	5	9	8	4	3	5	1	2	9	8	4	3	6	5	1	2	A	9	8	4	3	6	5	1	2	А
oup	Code		ed Vol (VDC)		6.3	10	16	25	50	6.3	9	16	25	50	100	200	6.3	5	16	25	35	50	<u>6</u>	200	250	6.3	9	16	25	35	50	100	200	250
		Сар	Toler	ance		P	rod	uct	Ava	aila	bilit	y aı	nd (	hip	Th	ickı	nes	s Co	ode	s –	See	Tab	ole 2	2 fo	r Ch	nip 1	Γhic	kne	ess	Dim	ens	ion	s	
3.3 µF	335	J	Κ	М																						ED	ED	ED	EH					
3.9 µF	395	J	K	M																						EF	EF	EF	EH					
4.7 μF	475	J	Κ	M													DG1	DG <sup>1</sup>	DG <sup>1</sup>							EH1	EH1	EH1	EH1	EH1	EH1			
5.6 µF	565	J	Κ	M																						EH	EH	EH						
6.8 µF	685	J	Κ	M																						EH	EH	EH						
8.2 µF	825	J	Κ	M																						EH	EH	EH						
10 µF	106	J	Κ	M													DG1	DG <sup>1</sup>								EH	EH	EH	EH1					
22 µF	226	J	Κ	M																						EH1	EH1							
			ed Vol (VDC)		6.3	9	16	25	50	6.3	9	16	25	50	100	200	6.3	9	16	25	35	50	100	200	250	6.3	9	16	25	35	50	100	200	250
Сар	Cap Code	Volt	age C	ode	9	8	4	3	5	9	8	4	3	5	1	2	9	8	4	3	6	5	1	2	A	9	8	4	3	6	5	1	2	А
			se S Serie			С	)402	2C				С	060	BC						С	080	5C							C.	120	6C			

## Table 1B – Capacitance Range/Selection Waterfall (1210 – 2225 Case Sizes)

	0		se Si Serie				(	C12	100	;			<b>C</b> 1	808	8C		Cŕ	1812	2C		(	C18	250	)		C2	222	OC		(	C22	250	;
Сар	Сар	Vo	tage C	ode	9	8	4	3	5	1	2	Α	5	1	2	3	5	1	2	A	5	1	2	A	3	5	1	2	Α	5	1	2	Α
	Code	Rat	ed Volt (VDC)		6.3	10	16	25	50	100	200	250	50	100	200	25	50	100	200	250	50	100	200	250	25	50	100	200	250	50	100	200	250
		Cap	Tolera	ance		Pr	odu	ct /	\vai	labi	ility	and	d Cr	nip 1	Thic	kne	ss	Cod	les ·	- Se	e Ta	able	e 2 f	or C	Chip	Th	ickr	ness	s Di	mer	isio	ns	
10 - 91 pF*	100 - 910*	J	K	M	FB	FB	FB	FB	FB	FB	FB														1								
11 pF	110	J	K	M	FB	FB	FB	FB	FB	FB	FB																						
12 pF	120	J	K	M	FB	FB	FB	FB	FB	FB	FB																						
13 pF	130	J	K	M	FB	FB	FB	FB	FB	FB	FB																						
15 pF	150	J	K	M	FB	FB	FB	FB	FB	FB	FB																						
16 pF	160	J	K	Μ	FB	FB	FB	FB	FB	FB	FB																						
18 pF	180	J	K	M	FB	FB	FB	FB	FB	FB	FB																						
20 pF	200	J	K	M	FB	FB	FB	FB	FB	FB	FB																						
22 pF	220	J	K	M	FB	FB	FB	FB	FB	FB	FB																						
24 pF	240	J	K	M	FB	FB	FB	FB	FB	FB	FB																						
27 pF	270	J	K	Μ	FB	FB	FB	FB	FB	FB	FB																						
30 pF	300	J	K	M	FB	FB	FB	FB	FB	FB	FB										1												
33 pF	330	J	K	M	FB	FB	FB	FB	FB	FB	FB					1					1												
36 pF	360	J	K	M	FB	FB	FB	FB	FB	FB	FB					1					1												
39 pF	390	J	K	M	FB	FB	FB	FB	FB	FB	FB					1					1												
43 pF	430	J	K	М	FB	FB	FB	FB	FB	FB	FB																						
47 pF	470	J	K	M	FB	FB	FB	FB	FB	FB	FB																						
51 pF	510	J	K	M	FB	FB	FB	FB	FB	FB	FB					1																	
56 pF	560	J	К	M	FB	FB	FB	FB	FB	FB	FB					1																	
		Rat	ed Volt (VDC)		6.3	10	16	25	50	100	200	250	50	100	200	25	50	100	200	250	50	100	200	250	25	50	100	200	250	50	100	200	250
Сар	Cap Code	Vol			9	8	4	3	5	1	2	Α	5	1	2	3	5	1	2	A	5	1	2	A	3	5	1	2	Α	5	1	2	Α
	0000		se Si Serie					C12	10C	,			C,	1808	BC		C	1812	2C			C18	250	;		C	2220	C		(	C22	25C	;

\*Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91)

\*\*Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)

KEMET reserves the right to substitute product with an improved temperature characteristic, tighter capacitance tolerance and/or higher voltage capability within the same form factor (configuration and dimensions).

xx<sup>1</sup> Available only in K, M tolerance.

 $xx^2$  Available only in M tolerance.



## Table 1B – Capacitance Range/Selection Waterfall (1210 – 2225 Case Sizes) cont'd

	Сар		se Si Serie				(	C12	100	;			C1	808	BC		<b>C</b> 1	1812	2C		(	C18	250	;		C2	2220	OC		(	C22	250	
Сар	Code	Vol	tage C	ode	9	8	4	3	5	1	2	A	5	1	2	3	5	1	2	Α	5	1	2	A	3	5	1	2	A	5	1	2	Α
	Code	Rat	ed Volt (VDC)	tage	6.3	10	16	25	50	100	200	250	50	100	200	25	50	100	200	250	50	100	200	250	25	50	100	200	250	50	100	200	250
		Сар	Tolera	ance		Pre	odu	ct A	Vai	labi	ility	and	d Ch	ip T	Thic	kne	ss (	Cod	les -	- Se	e Ta	able	e 2 f	or C	hip	Thi	ickr	ness	s Di	men	nsio	ns	
62 pF	620	J	K	М	FB																												
68 pF	680	J	K	M	FB																												
75 pF	750	J	K	M	FB																												
82 pF	820	J	K	M	FB																												
91 pF	910	J	K	M	FB																												
100 - 270 pF**	101 - 271**	J	K	M	FB																												
110 pF	111	J	K	M	FB																												
120 pF 130 pF	121 131	J	K K	M	FB FB																												
130 pF 150 pF	151	J	K	M	FB																												
150 pF 180 pF	181	J	K	M	FB																												
220 pF	221	J	K	M	FB																												
270 pF	271	J	K	M	FB																												
330 pF	331	J	K	M	FB		LF	LF	LF																								
390 pF	391	J	K	M	FB		LF	LF	LF																								
470 - 1,200 pF**	471 - 122**	J	K	M	FB		LF	LF	LF	GB	GB	GB	GB																				
560 pF	561	J	K	M	FB		LF	LF	LF	GB	GB	GB	GB																				
680 pF	681	J	К	M	FB		LF	LF	LF	GB	GB	GB	1																				
820 pF	821	J	К	M	FB		LF	LF	LF	GB	GB	GB	GB																				
1,000 pF	102	J	К	M	FB		LF	LF	LF	GB	GB	GB	GB																				
1,200 pF	122	J	K	M	FB		LF	LF	LF	GB	GB	GB	GB																				
1,500 pF	152	J	K	M	FB	FB	FB	FB	FB	FB	FE		LF	LF	LF	GB	GB	GB	GB														
1,800 pF	182	J	K	M	FB	FB	FB	FB	FB	FB	FE		LF	LF	LF	GB	GB	GB	GB														
2,200 pF	222	J	K	M	FB	LF	LF	LF	GB	GB	GB	GB																					
2,700 pF	272	J	K	M	FB	LF	LF	LF	GB	GB	GB	GB																					
3,300 pF	332	J	K	M	FB	LF	LF		GB	GB	GB	GB																					
3,900 pF	392	J	K	M	FB	LF	LF		GB	GB	GB	GB			HB	HB																	
4,700 pF	472	J	K	M	FB	LD	LD	LD	GB	GB	GB	GD			HB	HB							KE	KE	KE								
5,600 pF	562	J	K	M	FB	LD	LD	LD	GB	GB	GB	GH			HB	HB							KE	KE	KE								
6,800 pF	682	J	K	M	FB	LD	LD	LD	GB	GB	GB	GB			HB	HB		JE	JE	JE			KE	KE	KE								
8,200 pF	822	J	K	M	FB	LD	LD	LD	GB	GB	GB	GB		HB	HB	HB		JE	JE	JE			KE	KE	KE								
10,000 pF	103	J	K	M	FB	LD	LD	LD	GB	GB	GB	GB		HB	HB	HE		JE	JE	JE			KE	KE	KE								
12,000 pF	123	J	K	M	FB	LD	LD	LD	GB	GB	GB	GB		HB	HB	HE		JE	JE	JE			KE	KE	KE								
15,000 pF	153	J	K	M	FB	FB	FB	FB FB	FB	FB	FB FB	FB	LD LD	LD	LD LD	GB	GB	GB	GB		HB	HB			JE JE	JE JE	JE JE			KE	KE	KE	
18,000 pF 22,000 pF	183 223	J	K K	M	FB FB	FB FB	FB FB	FB	FB FB	FB FB	FB	FB FB	LD	LD LD	LD	GB GB	GB GB	GB GB	GB GB		HB HB	HE HB	μр	НВ	JE	JE	JE			KE KE	KE KE		
22,000 pF 27,000 pF	223	J	K	M	FB	LD	LD		GB	GB	GB	GB		HВ	HB	HB HB	HB	JE	JE	JE			KE	KE									
27,000 pF 33,000 pF	333	J	K	M	FB	LD	LD		GB	GB	GB	GB		НВ	HB	НВ	НВ	JB	JB	JB			KE	INL.									
39,000 pF	393	J	K	M	FB	FB	FB	FB	FB		FB			LD		GB	GB				HB		HB	HB	JB	JB	JB						
47,000 pF	473	.1	K	M	FB	FB	FB	FB	FB		FC	FC				GB					HB		HB		JB	JB	JB						
56,000 pF	563	J	K	M	FB	FB	FB	FB					LD								HB					JB	JB						
68,000 pF	683	J	K	M	FB	FB	FB	FB		FB	FC	-									HB				JB	JB	JB						
82,000 pF	823	J	K	M	FB	FB	FB	FB	FB	FC	FF		LD								HB				JC	JC	JC	JC	JC				
0.10 µF	104	J	K	M	FB	FB		FB				FG									HB				JC	JC				КС	KC	KC	KC
0.12 µF	124	J	К	M	FB		FB	FB	FB	FD	FH					GB	GB	GB	GB	GB	HB	HB	HB	HB	JC	JC	JC		JC	KC	KC	KC	
			ed Voli (VDC)		6.3	10	16	25	50	100	200	250	50	100	200	25	50	100	200	250	50	100	200	250	25	50	100	200	250	50	100	200	250
Сар	Cap Codo	Vol	Itage C	ode	9	8	4	3	5	1	2	Α	5	1	2	3	5	1	2	Α	5	1	2	A	3	5	1	2	Α	5	1	2	Α
	Code	Ca	Case Size/ Series						10C	;		1		808				1812				C18					2220					25C	;

\*Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91) \*\*Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)

KEMET reserves the right to substitute product with an improved temperature characteristic, tighter capacitance tolerance and/or higher voltage capability within the same form factor (configuration and dimensions).

*xx*<sup>1</sup> Available only in K, M tolerance.

 $xx^2$  Available only in M tolerance.



## Table 1B – Capacitance Range/Selection Waterfall (1210 – 2225 Case Sizes) cont'd

	Сар		se S Serie				(	C12	100	;			C1	808	BC		Cŕ	1812	2C		(	C18	250	2		C	222	0C	1	(	C22	250	;
Сар		Vol	ltage C	ode	9	8	4	3	5	1	2	Α	5	1	2	3	5	1	2	A	5	1	2	A	3	5	1	2	A	5	1	2	A
	Code	Rat	ed Vol (VDC)		6.3	9	16	25	50	100	200	250	50	100	200	25	20	<u>1</u> 00	200	250	50	100	200	250	25	50	100			50	100	200	250
		Cap	Tolera	ance		Pr	odu	ct /	\vai	labi	lity	and	d Ch	ip T	hic	kne	ss	Cod	les	– Se	e T	able	e 2 f	or (	Chip	) Th	ick	nes	s Di	mer	nsio	ns	
0.15 µF	154	J	K	M	FC	FC	FC	FC	FC	FD	FM	FM	LD			GB	GB	GB	GE	GE	HB	HB	HB	HB	JC	JC	JC	JC	JC	KC	KC	KC	KC
0.18 µF	184	J	K	M	FC	FC	FC	FC	FC	FD	FK	FK	LD			GB	GB	GB	GG	GG	HB	HB	HB	HB	JC	JC	JC	JC	JC	KC	KC	KC	KC
0.22 µF	224	J	K	M	FC	FC	FC	FC	FC	FD	FK	FK				GB	GB	GB	GG	GG	HB	HB	HB	HB	JC	JC	JC	JC	JC	КС	KC	KC	KC
0.27 µF	274	J	K	M	FC	FC	FC	FC	FC	FD						GB	GB	GG	GG	GG	ΗВ	HB	HB	HB	JC	JC	JC	JC	JC	КВ	KC	KC	КС
0.33 µF	334	J	К	M	FD	FD	FD	FD	FD	FD						GB	GB	GG	GG	GG	ΗВ	HB	HB	HB	JC	JC	JC	JC	JC	КВ	KC	КС	КС
0.39 µF	394	J	К	M	FD	FD	FD	FD	FD	FD						GB	GB	GG	GG	GG	ΗВ	HB	HD	HD	JC	JC	JC	JC	JC	КВ	KC	КС	КС
0.47 µF	474	J	K	M	FD	FD	FD	FD	FD	FD						GB	GB	GG	GJ	GJ	HB	HB	HD	HD	JC	JC	JC	JC	JC	KB	KC	KD	KD
0.56 µF	564	J	K	M	FD	FD	FD	FD	FD	FF						GC	GC	GG			HB	HD	HD	HD	JC	JC	JC	JD	JD	КВ	KC	KD	KD
0.68 µF	684	J	К	M	FD	FD	FD	FD	FD	FG						GC	GC	GG			HB	HD	HD	HD	JC	JC	JD	JD	JD	КВ	КС	KD	KD
0.82 µF	824	J	К	M	FF	FF	FF	FF	FF	FL						GE	GE	GG			HB	HF	HF	HF	JC	JC	JF	JF	JF	КВ	КС	KE	KE
1.0 µF	105	j	К	M	FH	FH	FH	FH	FH	FM						GE	GE	GG			НВ	HF	HF	HF	JC	JC	JF	JF	JF	КВ	KD	KE	KE
1.2 µF	125	J	К	М	FH	FH	FH	FH	FG	FH						GB	GB	GB			ΗВ				JC	JC				КВ	KE	KE	KE
1.5 µF	155	Ĵ	к	М	FH	FH	FH	FH	FG	FM						GC	GC	GC			нс				JC	JC				кс			'
1.8 µF	185	Ĵ	к	М	FH	FH	FH	FH	FG	FJ						GE	GE	GE			HD				JD	JD				КD			'
2.2 µF	225	Ĵ	к	М	FJ	FJ	FJ	FJ	FG	FT <sup>1</sup>						GO	GO	GO1			HF				JF	JF				KD			'
2.7 µF	275	Ĵ	K	M	FE	FE	FE	FG	FH							GJ	GJ	GJ												···-			
3.3 µF	335	Ĵ	K	М	FF	FF	FF	FM	FM							GL	GL	GL															
3.9 µF	395	Ĵ	К	M	FG	FG	FG	FG	FK																								
4.7 μF	475	Ĵ	K	M	FC	FC	FC	FG	FS							GK	GK								JF	JF							
5.6 µF	565	Ĵ	K	M	FF	FF	FF	FH																									
6.8 µF	685	Ĵ	K	M	FG	FG		FM																									
8.2 µF	825	J	K	M	FH	FH.	FH	FK	_						_			_		_		_	_										
10 µF	106	Ĵ	K	M		FT1			ES1							GK									JF	JO							
12 µF	126	Ĵ	ĸ	M												ÖN									0.								
15 µF	156	Ĵ	K	M	FΜ	FM																			JO	JO							
18 µF	186	J	ĸ	M																					1	"							1
22 µF	226	j	K	M	FS	FS	FS <sup>1</sup>	ES1																	JO								
47 μF	476	J	K	M	FS <sup>1</sup>			10																	100								
- η μι	170	<u> </u>									_	-			-			_	-	-		_	-	-				-	-		_		
		Rat	ed Vol (VDC)		6.3	9	16	25	50	100	200	250	50	100	200	25	50	10	200	250	50	10 10	200	250	25	50	10	200	250	50	100	200	250
Сар	Cap Code	Vo	ltage C	ode	9	8	4	3	5	1	2	Α	5	1	2	3	5	1	2	A	5	1	2	A	3	5	1	2	A	5	1	2	Α
			se Si Serie					C12	10C	;			C1	808	C		C	1812	2C			C18	250	;		C	222	0C			C22	25C	;

\*Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82 and 91) \*\*Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68 and 82)

KEMET reserves the right to substitute product with an improved temperature characteristic, tighter capacitance tolerance and/or higher voltage capability within the same form factor (configuration and dimensions).

xx<sup>1</sup> Available only in K, M tolerance.

xx<sup>2</sup> Available only in M tolerance.



## Table 2A – Chip Thickness/Tape & Reel Packaging Quantities

Thickness	Case	Thickness ±	Paper Q	luantity <sup>1</sup>	Plastic (	Quantity
Code	Size <sup>1</sup>	Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel
BB	0402	0.50 ± 0.05	10,000	50,000	0	0
CF	0603	$0.80 \pm 0.07^{*}$	4,000	15,000	0	0
CG	0603	$0.80 \pm 0.10^{*}$	4,000	15,000	0	0
CD	0603	0.80 ± 0.15	4,000	10,000	0	0
CJ	0603	0.80 ± 0.15*	4,000	15,000	0	0
DM	0805	$0.70 \pm 0.20^{*}$	4,000	15,000	0	0
DN	0805	$0.78 \pm 0.10^{*}$	4,000	15,000	0	0
DO	0805	$0.80 \pm 0.10^{*}$	4,000	15,000	0	0
DP	0805	$0.90 \pm 0.10^{*}$	4,000	15,000	0	0
DE DG	0805 0805	$1.00 \pm 0.10$	0	0	2,500 2,500	10,000 10,000
DG	0805	$1.25 \pm 0.15$	0	0	2,500	10,000
EB	1206	$1.25 \pm 0.20$	4,000	10,000	4,000	10,000
ED	1206	0.78 ± 0.10 0.90 ± 0.10			4,000	10,000
EC	1206	$0.90 \pm 0.10$ $0.95 \pm 0.10$	0 0	0 0	4,000	10,000
EN	1206	$0.95 \pm 0.10$ $1.00 \pm 0.10$	0	0	2,500	10,000
EE	1200	$1.00 \pm 0.10$ $1.10 \pm 0.10$	0	0	2,500	10,000
EF	1206	$1.20 \pm 0.15$	0	0	2,500	10,000
EP	1206	$1.20 \pm 0.13$ $1.20 \pm 0.20$	0	0	2,500	10,000
EM	1206	$1.25 \pm 0.15$	0	0	2,500	10,000
EG	1206	$1.60 \pm 0.15$	0	0	2,000	8,000
EH	1206	$1.60 \pm 0.20$	0	0	2,000	8,000
FB	1210	0.78 ± 0.10	0	0	4,000	10,000
FC	1210	0.90 ± 0.10	0	0	4,000	10,000
FD	1210	0.95 ± 0.10	0	0	4,000	10,000
FE	1210	1.00 ± 0.10	0	0	2,500	10,000
FF	1210	1.10 ± 0.10	0	0	2,500	10,000
FG	1210	1.25 ± 0.15	0	0	2,500	10,000
FL	1210	1.40 ± 0.15	0	0	2,000	8,000
FH	1210	1.55 ± 0.15	0	0	2,000	8,000
FM	1210	1.70 ± 0.20	0	0	2,000	8,000
FJ	1210	1.85 ± 0.20	0	0	2,000	8,000
FT	1210	1.90 ± 0.20	0	0	2,000	8,000
FK	1210	2.10 ± 0.20	0	0	2,000	8,000
FS	1210	$2.50 \pm 0.30$	0	0	1,000	4,000
NA	1706	$0.90 \pm 0.10$	0	0	4,000	10,000
NC	1706	$1.00 \pm 0.15$	0	0 0	4,000	10,000
LD LF	1808 1808	$0.90 \pm 0.10$ 1 00 + 0 15	0 0	0	2,500 2,500	10,000 10,000
GB	1808	1.00 ± 0.15 1.00 ± 0.10	0	0	2,500	4,000
GC	1812	$1.00 \pm 0.10$ $1.10 \pm 0.10$	0	0	1,000	4,000
GD	1812	$1.10 \pm 0.10$ $1.25 \pm 0.15$	0	0	1,000	4,000 4,000
GE	1812	$1.25 \pm 0.15$ $1.30 \pm 0.10$	0	0	1,000	4,000
GH	1812	$1.40 \pm 0.15$	0	0	1,000	4,000
GG	1812	$1.55 \pm 0.10$	0	0	1,000	4,000
GK	1812	$1.60 \pm 0.20$	0	0	1,000	4,000
GJ	1812	$1.70 \pm 0.15$	0 0	0	1,000	4,000
GL	1812	$1.90 \pm 0.20$	0	0	500	2,000
GO	1812	$2.50 \pm 0.20$	0	0	500	2,000
HB	1825	1.10 ± 0.15	0	0	1,000	4,000
HC	1825	1.15 ± 0.15	0	0	1,000	4,000
Thickness	Thickness Case		7" Reel	13" Reel	7" Reel	13" Reel
Code	Size <sup>1</sup>	Thickness ± Range (mm)	Banar O		Plaatie (	Quantity
	3126	- , ,	Paper Q	uantity <sup>1</sup>	Plastic	Quantity

Package quantity based on finished chip thickness specifications.

<sup>1</sup> If ordering using the 2 mm Tape and Reel pitch option, the packaging quantity outlined in the table above will be doubled. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information".



Thickness	Case	Thickness ±	Paper Q	uantity	Plastic (	Quantity
Code	Size <sup>1</sup>	Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel
HD	1825	1.30 ± 0.15	0	0	1,000	4,000
HE	1825	1.40 ± 0.15	0	0	1,000	4,000
HF	1825	1.50 ± 0.15	0	0	1,000	4,000
JB	2220	1.00 ± 0.15	0	0	1,000	4,000
JC	2220	1.10 ± 0.15	0	0	1,000	4,000
JD	2220	1.30 ± 0.15	0	0	1,000	4,000
JE	2220	1.40 ± 0.15	0	0	1,000	4,000
JF	2220	1.50 ± 0.15	0	0	1,000	4,000
JO	2220	2.40 ± 0.15	0	0	500	2,000
KB	2225	1.00 ± 0.15	0	0	1,000	4,000
KC	2225	1.10 ± 0.15	0	0	1,000	4,000
KD	2225	1.30 ± 0.15	0	0	1,000	4,000
KE	2225	1.40 ± 0.15	0	0	1,000	4,000
Thickness	ickness Case Thickness ±		7" Reel	13" Reel	7" Reel	13" Reel
Code	Size <sup>1</sup>	Range (mm)	Paper Q	Paper Quantity <sup>1</sup> Plastic Quantit		

#### Table 2A – Chip Thickness/Tape & Reel Packaging Quantities cont'd

Package quantity based on finished chip thickness specifications.

<sup>1</sup> If ordering using the 2 mm Tape and Reel pitch option, the packaging quantity outlined in the table above will be doubled. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information".

## Table 2B – Bulk Packaging Quantities

Desheet	T	Loose Packaging				
Раскаді	ng Type	Bulk Bag (default)				
Packagin	g C-Spec <sup>1</sup>	N/	Ά <sup>2</sup>			
Case	Size	Packaging Quantities (	pieces/unit packaging)			
EIA (in)	Metric (mm)	Minimum	Maximum			
0402	1005					
0603	1608					
0805	2012		50,000			
1206	3216					
1210	3225	1				
1808	4520	I				
1812	4532					
1825	4564		20,000			
2220	5650					
2225	5664					

<sup>1</sup> The "Packaging C-Spec" is a 4 to 8 digit code which identifies the packaging type and/or product grade. When ordering, the proper code must be included in the 15th through 22nd character positions of the ordering code. See "Ordering Information" section of this document for further details. Commercial Grade product ordered without a packaging C-Spec will default to our standard "Bulk Bag" packaging. Contact KEMET if you require a bulk bag packaging option for Automotive Grade products. <sup>2</sup> A packaging C-Spec (see note 1 above) is not required for "Bulk Bag" packaging (excluding Anti-Static Bulk Bag and Automotive Grade products). The 15th through 22nd character positions of the ordering code should be left blank. All product ordered without a packaging C-Spec will default to out standard "Bulk Bag" packaging.



#### Table 3 – Chip Capacitor Land Pattern Design Recommendations per IPC–7351


EIA Size Code	Metric Size Code		Density Level A: Maximum (Most) Land Protrusion (mm)			Density Level B: Median (Nominal) Land Protrusion (mm)				Density Level C: Minimum (Least) Land Protrusion (mm)						
		С	Y	Х	V1	V2	С	Y	Х	V1	V2	С	Y	Х	V1	V2
0402	1005	0.50	0.72	0.72	2.20	1.20	0.45	0.62	0.62	1.90	1.00	0.40	0.52	0.52	1.60	0.80
0603	1608	0.90	1.15	1.10	4.00	2.10	0.80	0.95	1.00	3.10	1.50	0.60	0.75	0.90	2.40	1.20
0805	2012	1.00	1.35	1.55	4.40	2.60	0.90	1.15	1.45	3.50	2.00	0.75	0.95	1.35	2.80	1.70
1206	3216	1.60	1.35	1.90	5.60	2.90	1.50	1.15	1.80	4.70	2.30	1.40	0.95	1.70	4.00	2.00
1210	3225	1.60	1.35	2.80	5.65	3.80	1.50	1.15	2.70	4.70	3.20	1.40	0.95	2.60	4.00	2.90
1210 <sup>1</sup>	3225	1.50	1.60	2.90	5.60	3.90	1.40	1.40	2.80	4.70	3.30	1.30	1.20	2.70	4.00	3.00
1808	4520	2.30	1.75	2.30	7.40	3.30	2.20	1.55	2.20	6.50	2.70	2.10	1.35	2.10	5.80	2.40
1812	4532	2.15	1.60	3.60	6.90	4.60	2.05	1.40	3.50	6.00	4.00	1.95	1.20	3.40	5.30	3.70
1825	4564	2.15	1.60	6.90	6.90	7.90	2.05	1.40	6.80	6.00	7.30	1.95	1.20	6.70	5.30	7.00
2220	5650	2.75	1.70	5.50	8.20	6.50	2.65	1.50	5.40	7.30	5.90	2.55	1.30	5.30	6.60	5.60
2225	5664	2.70	1.70	6.90	8.10	7.90	2.60	1.50	6.80	7.20	7.30	2.50	1.30	6.70	6.50	7.00

#### <sup>1</sup> Only for capacitance values $\geq$ 22 $\mu$ F

Density Level A: For low-density product applications. Recommended for wave solder applications and provides a wider process window for reflow solder processes. KEMET only recommends wave soldering of EIA 0603, 0805, and 1206 case sizes.

Density Level B: For products with a moderate level of component density. Provides a robust solder attachment condition for reflow solder processes. Density Level C: For high component density product applications. Before adapting the minimum land pattern variations the user should perform qualification testing based on the conditions outlined in IPC Standard 7351 (IPC–7351).

Image below based on Density Level B for an EIA 1210 case size.





### **Soldering Process**

#### **Recommended Soldering Technique:**


- Solder wave or solder reflow for EIA case sizes 0603, 0805 and 1206
- · All other EIA case sizes are limited to solder reflow only

#### **Recommended Reflow Soldering Profile:**

KEMET's families of surface mount multilayer ceramic capacitors (SMD MLCCs) are compatible with wave (single or dual), convection, IR or vapor phase reflow techniques. Preheating of these components is recommended to avoid extreme thermal stress. KEMET's recommended profile conditions for convection and IR reflow reflect the profile conditions of the IPC/J-STD-020 standard for moisture sensitivity testing. These devices can safely withstand a maximum of three reflow passes at these conditions.

Profile Feature	Terminati	on Finish
	SnPb	100% Matte Sn
Preheat/Soak		
Temperature Minimum (T <sub>Smin</sub> )	100°C	150°C
Temperature Maximum (T <sub>Smax</sub> )	150°C	200°C
Time (t <sub>s</sub> ) from $T_{Smin}$ to $T_{Smax}$	60 – 120 seconds	60 – 120 seconds
Ramp-Up Rate ( $T_L$ to $T_P$ )	3°C/second maximum	3°C/second maximum
Liquidous Temperature $(T_L)$	183°C	217°C
Time Above Liquidous ( $t_L$ )	60 – 150 seconds	60 – 150 seconds
Peak Temperature (T <sub>P</sub> )	235°C	260°C
Time Within 5°C of Maximum Peak Temperature (t <sub>P</sub> )	20 seconds maximum	30 seconds maximum
Ramp-Down Rate ( $T_P$ to $T_L$ )	6°C/second maximum	6°C/second maximum
Time 25°C to Peak Temperature	6 minutes maximum	8 minutes maximum

Note 1: All temperatures refer to the center of the package, measured on the capacitor body surface that is facing up during assembly reflow.



## Table 4 – Performance & Reliability: Test Methods and Conditions


Stress	Reference		Test or Inspection M	ethod					
Terminal Strength	JIS-C-6429	Appendix 1, Note: Force of 1.8	kg for 60 seconds.						
Board Flex	JIS-C-6429		Appendix 2, Note: Standard termination system – 2.0 mm (minimum) for all except 3 mm for COG. Flexible termination system – 3.0 mm (minimum).						
		Magnification 50 X. Conditions	:						
Caldanahilita		a) Method B, 4 hours at	155°C, dry heat at 235°C						
Solderability	J-STD-002	b) Method B at 215°C ca	tegory 3						
		c) Method D, category 3	at 260°C						
Temperature Cycling	JESD22 Method JA-104	1,000 Cycles (-55°C to +125°C	). Measurement at 24 hours +	-/- 4 hours after test conclusion.					
Biased Humidity	MIL-STD-202 Method 103	Load Humidity: 1,000 hours 85°C/85% RH and rated voltage. Add 100 K ohm resistor. Measurement at 24 hours +/- 4 hours after test conclusion. Low Volt Humidity: 1,000 hours 85°C/85% RH and 1.5 V. Add 100 K ohm resistor. Measurement at 24 hours +/- 4 hours after test conclusion.							
Moisture Resistance	MIL-STD-202 Method 106	t = 24 hours/cycle. Steps 7a and 7b not required. Measurement at 24 hours +/- 4 hours after test conclusion.							
Thermal Shock	MIL-STD-202 Method 107	-55°C/+125°C. Note: Number of Dwell time – 15 minutes. Air –		mum transfer time – 20 seconds.					
		1,000 hours at 125°C with 2 X rated voltage applied excluding the following:							
	MIL-STD-202 Method 108	Case Size	Capacitance	Applied Voltage					
High Temperature Life	/EIA–198	0603 & 0805	≥ 1.0 µF	- 1.5 X					
		1206 & 1210	≥ 10 µF	1.5 A					
Storage Life	MIL-STD-202 Method 108	150°C, 0 VDC for 1,000 hours.							
Vibration	MIL-STD-202 Method 204	5 g's for 20 minutes, 12 cycles each of 3 orientations. Note: Use 8" X 5" PCB 0.031" thick 7 secure points on one long side and 2 secure points at corners of opposite sides. Parts mounted within 2" from any secure point. Test from 10 – 2,000 Hz							
Mechanical Shock	MIL-STD-202 Method 213	Figure 1 of Method 213, Condi	tion F.						
Resistance to Solvents	MIL-STD-202 Method 215	Add aqueous wash chemical, (	OKEM Clean or equivalent.						

### **Storage & Handling**

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature– reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. Temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.



## **Construction (Typical)**





## **Capacitor Marking (Optional):**


These surface mount multilayer ceramic capacitors are normally supplied unmarked. If required, they can be marked as an extra cost option. Marking is available on most KEMET devices but must be requested using the correct ordering code identifier(s). If this option is requested, two sides of the ceramic body will be laser marked with a "K" to identify KEMET, followed by two characters (per EIA–198 - see table below) to identify the capacitance value. EIA 0603 case size devices are limited to the "K" character only.

Laser marking option is <u>not</u> available on:

- COG, Ultra Stable X8R and Y5V dielectric devices
- EIA 0402 case size devices
- EIA 0603 case size devices with Flexible Termination option.
- KPS Commercial and Automotive Grade stacked devices.
- · X7R dielectric products in capacitance values outlined below

EIA Case Size	Metric Size Code	Capacitance
0603	1608	≤ 170 pF
0805	2012	≤ 150 pF
1206	3216	≤ 910 pF
1210	3225	≤ 2,000 pF
1808	4520	≤ 3,900 pF
1812	4532	≤ 6,700 pF
1825	4564	≤ 0.018 µF
2220	5650	≤ 0.027 µF
2225	5664	≤ 0.033 µF

Marking appears in legible contrast. Illustrated below is an example of an MLCC with laser marking of "KA8", which designates a KEMET device with rated capacitance of 100  $\mu$ F. Orientation of marking is vendor optional.






# Capacitor Marking (Optional) cont'd

	Capacitance (pF) For Various Alpha/Numeral Identifiers											
						Numera	al					
Alpha	9	0	1	2	3	4	5	6	7	8		
Character	Capacitance (pF)											
A	0.1	10	10	100	1,000	10,000	100,000	1,000,000	10,000,000	100,000,000		
В	0.11	1.1	11	110	1,100	11,000	110,000	1,100,000	11,000,000	110,000,000		
С	0.12	12	12	120	1,200	12,000	120,000	1,200,000	12,000,000	120,000,000		
D	0.13	13	13	130	1,300	13,000	130,000	1,300,000	13,000,000	130,000,000		
E	0.15	15	15	150	1,500	15,000	150,000	1,500,000	15,000,000	150,000,000		
F	0.16	16	16	160	1,600	16,000	160,000	1,600,000	16,000,000	160,000,000		
G	0.18	18	18	180	1,800	18,000	180,000	1,800,000	18,000,000	180,000,000		
Н	0.2	20	20	200	2,000	20,000	200,000	2,000,000	20,000,000	200,000,000		
J	0.22	2 2	22	220	2,200	22,000	220,000	2,200,000	22,000,000	220,000,000		
К	0.24	2.4	24	240	2,400	24,000	240,000	2,400,000	24,000,000	240,000,000		
L	0.27	2.7	27	270	2,700	27,000	270,000	2,700,000	27,000,000	270,000,000		
М	0.3	3 0	30	300	3,000	30,000	300,000	3,000,000	30,000,000	300,000,000		
N	0.33	3 3	33	330	3,300	33,000	330,000	3,300,000	33,000,000	330,000,000		
Р	0.36	36	36	360	3,600	36,000	360,000	3,600,000	36,000,000	360,000,000		
Q	0.39	39	39	390	3,900	39,000	390,000	3,900,000	39,000,000	390,000,000		
R	0.43	43	43	430	4,300	43,000	430,000	4,300,000	43,000,000	430,000,000		
S	0.47	4.7	47	470	4,700	47,000	470,000	4,700,000	47,000,000	470,000,000		
Т	0.51	5.1	51	510	5,100	51,000	510,000	5,100,000	51,000,000	510,000,000		
U	0.56	56	56	560	5,600	56,000	560,000	5,600,000	56,000,000	560,000,000		
V	0.62	62	62	620	6,200	62,000	620,000	6,200,000	62,000,000	620,000,000		
W	0.68	68	68	680	6,800	68,000	680,000	6,800,000	68,000,000	680,000,000		
Х	0.75	75	75	750	7,500	75,000	750,000	7,500,000	75,000,000	750,000,000		
Y	0.82	8 2	82	820	8,200	82,000	820,000	8,200,000	82,000,000	820,000,000		
Z	0.91	9.1	91	910	9,100	91,000	910,000	9,100,000	91,000,000	910,000,000		
а	0.25	2 5	25	250	2,500	25,000	250,000	2,500,000	25,000,000	250,000,000		
b	0.35	3 5	35	350	3,500	35,000	350,000	3,500,000	35,000,000	350,000,000		
d	0.4	4 0	40	400	4,000	40,000	400,000	4,000,000	40,000,000	400,000,000		
e	0.45	4 5	45	450	4,500	45,000	450,000	4,500,000	45,000,000	450,000,000		
f	0.5	50	50	500	5,000	50,000	500,000	5,000,000	50,000,000	500,000,000		
m	0.6	60	60	600	6,000	60,000	600,000	6,000,000	60,000,000	600,000,000		
n	0.7	70	70	700	7,000	70,000	700,000	7,000,000	70,000,000	700,000,000		
t	0.8	8 0	80	800	8,000	80,000	800,000	8,000,000	80,000,000	800,000,000		
у	0.9	90	90	900	9,000	90,000	900,000	9,000,000	90,000,000	900,000,000		



# **Tape & Reel Packaging Information**

KEMET offers multilayer ceramic chip capacitors packaged in 8, 12 and 16 mm tape on 7" and 13" reels in accordance with EIA Standard 481. This packaging system is compatible with all tape-fed automatic pick and place systems. See Table 2 for details on reeling quantities for commercial chips.



# Table 5 – Carrier Tape Configuration, Embossed Plastic & Punched Paper (mm)

	Таре	Embosse	ed Plastic	Punched Paper		
EIA Case Size	Size (W)*	7" Reel	13" Reel	7" Reel	13" Reel	
		Pitch	(P <sub>1</sub> )*	Pitch	(P <sub>1</sub> )*	
01005 – 0402	8			2	2	
0603	8			2/4	2/4	
0805	8	4	4	4	4	
1206 – 1210	8	4	4	4	4	
1805 – 1808	12	4	4			
≥ 1812	12	8	8			
KPS 1210	12	8	8			
KPS 1812 & 2220	16	12	12			
Array 0508 & 0612	8	4	4			

\*Refer to Figures 1 & 2 for W and  $P_1$  carrier tape reference locations. \*Refer to Tables 6 & 7 for tolerance specifications.

#### New 2 mm Pitch Reel Options\*

Packaging Ordering Code (C-Spec)	Packaging Type/Options
C-3190	Automotive grade 7" reel unmarked
C-3191	Automotive grade 13" reel unmarked
C-7081	Commercial grade 7" reel unmarked
C-7082	Commercial grade 13" reel unmarked


\* 2 mm pitch reel only available for 0603 EIA case size.

2 mm pitch reel for 0805 EIA case size under development.

#### Benefits of Changing from 4 mm to 2 mm Pitching Spacing

- Lower placement costs
- Double the parts on each reel results in fewer reel changes and increased efficiency
- Fewer reels result in lower packaging, shipping and storage costs, reducing waste

# Figure 1 – Embossed (Plastic) Carrier Tape Dimensions



### Table 6 – Embossed (Plastic) Carrier Tape Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)										
Tape Size	D <sub>0</sub>	D <sub>1</sub> Minimum Note 1	E <sub>1</sub>	P <sub>0</sub>	P <sub>2</sub>	R Reference Note 2	S <sub>1</sub> Minimum Note 3	T Maximum	T <sub>1</sub> Maximum		
8 mm		1.0 (0.039)				25.0 (0.984)					
12 mm	1.5 +0.10/-0.0 (0.059 +0.004/-0.0)	1.5	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	30	0.600 (0.024)	0.600 (0.024)	0.100 (0.004)		
16 mm		(0.059)				(1.181)					
			Variable Dime	ensions — Mil	limeters (Inch	es)					
Tape Size	Pitch	B <sub>1</sub> Maximum Note 4	E <sub>2</sub> Minimum	F	P <sub>1</sub>	T <sub>2</sub> Maximum	W Maximum	A <sub>0</sub> , B <sub>0</sub>	, & К <sub>о</sub>		
8 mm	Single (4 mm)	4.35 (0.171)	6.25 (0.246)	3.5 ±0.05 (0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	2.5 (0.098)	8.3 (0.327)				
12 mm	Single (4 mm) & Double (8 mm)	8.2 (0.323)	10.25 (0.404)	5.5 ±0.05 (0.217 ±0.002)	8.0 ±0.10 (0.315 ±0.004)	4.6 (0.181)	12.3 (0.484)	Note 5			
16 mm	Triple (12 mm)	12.1 (0.476)	14.25 (0.561)	7.5 ±0.05 (0.138 ±0.002)	12.0 ±0.10 (0.157 ±0.004)	4.6 (0.181)	16.3 (0.642)				

1. The embossment hole location shall be measured from the sprocket hole controlling the location of the embossment. Dimensions of embossment location and hole location shall be applied independent of each other.

2. The tape with or without components shall pass around R without damage (see Figure 6).

3. If S<sub>1</sub> < 1.0 mm, there may not be enough area for cover tape to be properly applied (see EIA Standard 481 paragraph 4.3 section b).

4. B, dimension is a reference dimension for tape feeder clearance only.

5. The cavity defined by  $A_{\alpha}$ ,  $B_{\alpha}$  and  $K_{\alpha}$  shall surround the component with sufficient clearance that:

(a) the component does not protrude above the top surface of the carrier tape.

(b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.

(c) rotation of the component is limited to 20° maximum for 8 and 12 mm tapes and 10° maximum for 16 mm tapes (see Figure 3).


(d) lateral movement of the component is restricted to 0.5 mm maximum for 8 and 12 mm wide tape and to 1.0 mm maximum for 16 mm tape (see Figure 4).

(e) for KPS Series product,  $A_0$  and  $B_0$  are measured on a plane 0.3 mm above the bottom of the pocket.

(f) see Addendum in EIA Standard 481 for standards relating to more precise taping requirements.



#### Figure 2 – Punched (Paper) Carrier Tape Dimensions



## Table 7 – Punched (Paper) Carrier Tape Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)										
Tape Size	$D_0$ $E_1$ $P_0$ $P_2$ $T_1$ Maximum G Minimum										
8 mm	1.5 +0.10 -0.0 (0.059 +0.004 -0.0)	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	0.10 (0.004) Maximum	0.75 (0.030)	25 (0.984)				
		Variable D	)imensions — M	illimeters (Inche	es)						
Tape Size	Pitch	E2 Minimum	F	P <sub>1</sub>	T Maximum	W Maximum	$A_0B_0$				
8 mm	Half (2 mm)	6.25	3.5 ±0.05	2.0 ±0.05 (0.079 ±0.002)	1.1	8.3 (0.327)	Note 1				
8 mm	Single (4 mm)	(0.246)	(0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	(0.098)	8.3 (0.327)					

1. The cavity defined by  $A_{\alpha}$ ,  $B_{\alpha}$  and T shall surround the component with sufficient clearance that:

a) the component does not protrude beyond either surface of the carrier tape.

b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.

c) rotation of the component is limited to 20° maximum (see Figure 3).

d) lateral movement of the component is restricted to 0.5 mm maximum (see Figure 4).

e) see Addendum in EIA Standard 481 for standards relating to more precise taping requirements.

2. The tape with or without components shall pass around R without damage (see Figure 6).




## **Packaging Information Performance Notes**

- 1. Cover Tape Break Force: 1.0 Kg minimum.
- 2. Cover Tape Peel Strength: The total peel strength of the cover tape from the carrier tape shall be:


Tape Width	Peel Strength	
8 mm	0.1 to 1.0 Newton (10 to 100 gf)	
12 and 16 mm	0.1 to 1.3 Newton (10 to 130 gf)	

The direction of the pull shall be opposite the direction of the carrier tape travel. The pull angle of the carrier tape shall be  $165^{\circ}$  to  $180^{\circ}$  from the plane of the carrier tape. During peeling, the carrier and/or cover tape shall be pulled at a velocity of  $300 \pm 10$  mm/minute. **3. Labeling:** Bar code labeling (standard or custom) shall be on the side of the reel opposite the sprocket holes. *Refer to EIA Standards* 556 and 624.


#### **Figure 3 – Maximum Component Rotation**




### Figure 4 – Maximum Lateral Movement



## Figure 5 – Bending Radius



## Figure 6 – Reel Dimensions



Note: Drive spokes optional; if used, dimensions B and D shall apply.


### Table 8 – Reel Dimensions

Metric will govern


Constant Dimensions — Millimeters (Inches)					
Tape Size	А	B Minimum	С	D Minimum	
8 mm	178 ±0.20 (7.008 ±0.008) or 330 ±0.20 (13.000 ±0.008)	1.5 (0.059)	13.0 +0.5/-0.2 (0.521 +0.02/-0.008)	20.2 (0.795)	
12 mm					
16 mm					
Variable Dimensions — Millimeters (Inches)					
Tape Size	N Minimum	W <sub>1</sub>	W <sub>2</sub> Maximum	W <sub>3</sub>	
8 mm	50 (1.969)	8.4 +1.5/-0.0 (0.331 +0.059/-0.0)	14.4 (0.567)	Shall accommodate tape width without interference	
12 mm		12.4 +2.0/-0.0 (0.488 +0.078/-0.0)	18.4 (0.724)		
16 mm		16.4 +2.0/-0.0 (0.646 +0.078/-0.0)	22.4 (0.882)		



## Figure 7 – Tape Leader & Trailer Dimensions



### Figure 8 – Maximum Camber





## KEMET Corporation World Headquarters

2835 KEMET Way Simpsonville, SC 29681

Mailing Address: P.O. Box 5928 Greenville, SC 29606

www.kemet.com Tel: 864-963-6300 Fax: 864-963-6521

#### **Corporate Offices**

Fort Lauderdale, FL Tel: 954-766-2800

### **North America**

Northeast Wilmington, MA Tel: 978-658-1663

Southeast Lake Mary, FL Tel: 407-855-8886

**Central** Novi, MI Tel: 248-994-1030

Irving, TX Tel: 972-915-6041

West Milpitas, CA Tel: 408-433-9950

Mexico

Guadalajara, Jalisco Tel: 52-33-3123-2141

#### Europe

**Southern Europe** Sasso Marconi, Italy Tel: 39-051-939111

Skopje, Macedonia Tel: 389-2-55-14-623

**Central Europe** Landsberg, Germany Tel: 49-8191-3350800

Kamen, Germany Tel: 49-2307-438110

Northern Europe Wyboston, United Kingdom Tel: 44-1480-273082

Espoo, Finland Tel: 358-9-5406-5000

#### Asia

Northeast Asia Hong Kong Tel: 852-2305-1168

Shenzhen, China Tel: 86-755-2518-1306

Beijing, China Tel: 86-10-5877-1075

Shanghai, China Tel: 86-21-6447-0707

Seoul, South Korea Tel: 82-2-6294-0550

Taipei, Taiwan Tel: 886-2-27528585

Southeast Asia Singapore Tel: 65-6701-8033

Penang, Malaysia Tel: 60-4-6430200

Bangalore, India Tel: 91-806-53-76817

Note: KEMET reserves the right to modify minor details of internal and external construction at any time in the interest of product improvement. KEMET does not assume any responsibility for infringement that might result from the use of KEMET Capacitors in potential circuit designs. KEMET is a registered trademark of KEMET Electronics Corporation.

## Disclaimer

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed.

All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute – and KEMET specifically disclaims – any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicted or that other measures may not be required.