



SPECIFICATION SEALS COMPANY

## SPEC SEALS TECHNICAL REPORT S500-70 SILICONE COMPOUND

### GENERAL PROPERTIES

SPEC SEALS Silicones offer a broad temperature range, from -80° F to +400° F, and excellent dry heat resistance. Our Silicone compounds are inert and guarantee complete compliance to ASTM, and Military and FDA Specifications required by food, medical, electrical and filter manufacturers. They are not used in dynamic seals because of relatively poor tensile, tear and abrasion resistance.

		<b>SPEC SEALS S500-70</b>	
<b>ASTM</b>		<b>ASTM D2000</b>	<b>LABORATORY</b>
<b>Designation</b>	<b>ORIGINAL PROPERTIES</b>	<b>SPECIFICATION</b>	<b>PROPERTY</b>
	Durometer, Shore A	70 +/- 5	71
	Tensile, psi (MPa), Minimum	870 (6)	995 (6.9)
	Elongation, % Minimum	150	175
	Specific Gravity		1.43
A19	<u>HEAT AGE, 70 HRS @ 225 C</u>		
	Durometer Change, Points	+10	+4
	Tensile Strength Change, %	-25	-14.3
	Elongation Change, % Maximum	-30	-18.4
B37	<u>COMPRESSION SET, 22 HRS @ 175 C</u>		
	Original Deflection, % Maximum	25	12.4
	<u>COMPRESSION SET, 70 HRS @ 150C</u>		
	Original Deflection, % Maximum		19.4
EO16	<u>ASTM #1 OIL, 70 HRS @ 150 C</u>		
	Durometer Change, Points	0/-15	-7
	Tensile Change, % Maximum	-20	-2.9
	Elongation Change, % Maximum	-20	0
	Volume Change, %	0/+10	+6.4
EO36	<u>ASTM #3 OIL, 70 HRS. @ 150 C</u>		
	Durometer Change, points	-30	-20
	Volume Change, % Maximum	+60	+35
EA14	<u>WATER RESISTANCE 70 HRS @ 100 C</u>		
	Durometer Change, Points	+/-5	-1
	Volume Change, %	+/-5	+2.5
F19	<u>LOW TEMPERATURE BRITTLINESS</u>		
	ASTM D2137, Method A		
	3 Minutes @ -55 C	Non-Brittle	Pass
	3 Minutes @ -65 C		Pass
G11	<u>Tear Resis., Die B, ppi (kN/m)</u>	51(9)	107 (18.8)

### SPECIFICATIONS MET

- ASTM D2000-01 Grade M5GE706 A19 B37 EO16 EO36 EA14 F19 G11
- ZZ-R-765B Class 2a & 2b, Grade 70 and FDA CFR 177.2600
- AMS 3304 (Size per AS3582 which replaced MS 9068) Specification